



Offices and Factories in Korea

Headquarters & Incheon Factory
620-8 Namchon-dong, Namdong-gu,
Incheon, Korea
Tel. +82-32-450-8770 Fax. +82-32-450-8870

Pyeongtaek Factory
148-40, Goryeom-ri, Cheongbuk-myeon, Pyeongtaek-si,
Gyeonggi-do, Korea
Tel. +82-31-683-2466 Fax. +82-31-683-2465

Cheongju Factory
8-8 Poongjung-ri, Naesu-eup, Cheongwon-gun,
Chungbuk, Korea
Tel. +82-43-213-8801 Fax. +82-43-213-8807



Offices and Factories Overseas

CHINA

Weihai Factory
Changxing Road, First Industrial Complex, Huanshan RD,
Economic Technological Development Zone,
Weihai City, Shandong Province, China
Tel. +86-631-596-5931 Fax. +86-631-596-8160

Dongguan Office
2Floor, Innovation Park of SongYuan Technology,
No.1, GuanLong Road YuWu Section, DongCheng District,
DongGuan City, GuangDong Province, China
Tel. +86-769-8352-1800 Fax. +86-869-8352-1803

JAPAN

Tokyo Office
Bansui Ken Bldg, 5F, Toranomon 1-6-6,
Minato-Ku Tokyo, Japan 105-0001
Tel. +81-3-5512-5380 Fax. +81-3-5512-5381

MAGNETIC POWDER CORES

100% PREMIUM
MATERIALS



MAGNETIC POWDER CORES

Moving Forward with Chang Sung Corporation

Through continuous innovations and steadfast advancements in technology, we have become one of the leading suppliers of cutting edge products to companies around the world at the forefront of next generation energy solutions.

**CSC SOFT MAGNETIC POWDER CORES
ARE AT THE FOREFRONT
OF ADVANCED
INDUSTRIES**





TABLE OF CONTENTS

NEW MATERIAL

| | |
|------------------|-----|
| · HS Cores | 004 |
| · KS Cores | 008 |
| · KH Cores | 012 |

TOROIDAL CORES

| | |
|----------------------------------|-----|
| · Materials | 019 |
| · Part Number Description | 022 |
| · Magnetic Design Formulas | 024 |
| -Permeability vs DC Bias | 024 |
| -Permeability vs Frequency | 028 |
| -Core Loss | 029 |
| -Temperature Stability | 035 |
| -Winding Information | 037 |
| · Part List | 038 |

SPECIAL SHAPES

| | |
|--------------------------------------|-----|
| · Block Cores | 076 |
| · Ellipse Cores | 078 |
| · Cylinder + Round Block Cores | 080 |
| · Cylinder Cores | 081 |
| · EE Cores | 082 |
| · EER Cores | 083 |
| · EQ Cores | 084 |
| · ER II Cores | 085 |
| · U Cores | 086 |
| · Washer Cores | 087 |
| · Big Toroidal Cores | 088 |

| | |
|-------------------|-----|
| TERMINOLOGY | 091 |
|-------------------|-----|

NEW MATERIALS

HS CORES
KS CORES
KH CORES

TOLERANCE OF AL VALUE

| Core Size | HS |
|-----------------|----|
| OD035 ~ OD095 | NA |
| OD036 ~ OD778 | ±8 |
| OD1013 ~ OD1625 | ±8 |

HS CORES

CSC has recently released its new HS series of iron alloy powder cores. The 14,000 gauss saturation level of HS cores exhibits similar DCB characteristics to High Flux cores. HS cores with permeability of 19 μ and 26 μ show outstanding DCB performance for high current applications such as UPS. Especially, the core losses of HS 19 μ and 26 μ are significantly lower than any other material, even lower than MPP. HS cores with 19 μ and 26 μ offer good solutions for applications requiring high efficiency such as UPS, ESS and similar industrial uses. HS cores over 60 μ have good DCB characteristics and lower core losses than Sendust cores. They provide an economic solution for applications requiring high efficiency including high power desktop PCs, Server PCs, automotive parts, and solar power parts. They can be a good alternative to Amorphous cores, and also present excellent thermal properties without any thermal aging effects found in other soft magnetic powder cores. Finished HS cores are coated with a dark blue epoxy.


KS CORES

The range of permeability for KS cores is relatively low, 26 μ ~60 μ , but the 14,000 gauss saturation level allows them to exhibit similar DCB characteristics to High Flux cores. KS cores can be widely used for solar inverters, because they are economic and have a great level of efficiency. They have especially come into the spotlight for large capacity solar inverters. Recently, KS cores have been used in the automobile electricity fields as well. Finished KS cores are coated with a dark blue epoxy.

KH CORES


The range of permeability for KH cores is 26 μ ~90 μ . The 15,000 gauss saturation level of KH cores exhibits similar DCB characteristics to High Flux cores, which exhibit the best DCB characteristics among existing materials including Sendust, MPP, and Mega Flux cores. They also have lower losses than Fe-Si based permalloy cores as well as greater frequency characteristics that allow them to be used at a higher frequency. Since KH cores have greater DCB characteristics and a low level of loss, they are most suitable for UPS and ESS applications and other industrial uses. Finished KH cores are coated with a dark blue epoxy.

TOROIDAL POWDER CORES



| PART NO. | Before Finish Dimensions | | | After Finish Dimensions | | | Path length (cm) | Cross Section Area (cm ²) | AL value (nH/N ²)±8% | | | |
|----------|--------------------------|------------|------------|-------------------------|------------|------------|------------------|---------------------------------------|----------------------------------|------|------|------|
| | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | | | 026μ | 060μ | 075μ | 090μ |
| HS096 | 9.65 | 4.78 | 3.18 | 10.29 | 4.27 | 3.81 | 2.18 | 0.0752 | 11 | 25 | 32 | 38 |
| HS097 | 9.65 | 4.78 | 3.96 | 10.29 | 4.27 | 4.57 | 2.18 | 0.0945 | 14 | 32 | 40 | 48 |
| HS102 | 10.16 | 5.08 | 3.96 | 10.80 | 4.57 | 4.57 | 2.38 | 0.1000 | 14 | 32 | 40 | 48 |
| HS112 | 11.18 | 6.35 | 3.96 | 11.90 | 5.89 | 4.72 | 2.69 | 0.0906 | 11 | 26 | 32 | 38 |
| HS127 | 12.70 | 7.62 | 4.75 | 13.46 | 6.99 | 5.51 | 3.12 | 0.114 | 12 | 27 | 34 | 40 |
| HS166 | 16.51 | 10.16 | 6.35 | 17.4 | 9.53 | 7.11 | 4.11 | 0.192 | 15 | 35 | 43 | 52 |
| HS172 | 17.27 | 9.65 | 6.35 | 18.03 | 9.02 | 7.11 | 4.14 | 0.232 | 19 | 43 | 53 | 64 |
| HS203 | 20.32 | 12.7 | 6.35 | 21.1 | 12.07 | 7.11 | 5.09 | 0.226 | 14 | 32 | 41 | 49 |
| HS229 | 22.86 | 13.97 | 7.62 | 23.62 | 13.39 | 8.38 | 5.67 | 0.331 | 19 | 43 | 54 | 65 |
| HS234 | 23.57 | 14.4 | 8.89 | 24.3 | 13.77 | 9.7 | 5.88 | 0.388 | 22 | 51 | 63 | 76 |
| HS270 | 26.92 | 14.73 | 11.18 | 27.7 | 14.1 | 11.99 | 6.35 | 0.654 | 32 | 75 | 94 | 113 |
| HS330 | 33.02 | 19.94 | 10.67 | 33.83 | 19.3 | 11.61 | 8.15 | 0.672 | 28 | 61 | 76 | 91 |
| HS343 | 34.29 | 23.37 | 8.89 | 35.2 | 22.6 | 9.83 | 8.95 | 0.454 | 16 | 38 | 47 | 57 |
| HS358 | 35.81 | 22.35 | 10.46 | 36.7 | 21.5 | 11.28 | 8.98 | 0.678 | 24 | 56 | 70 | 84 |
| HS400 | 39.88 | 24.13 | 14.48 | 40.7 | 23.3 | 15.37 | 9.84 | 1.072 | 35 | 81 | 101 | 121 |
| HS467 | 46.74 | 24.13 | 18.03 | 47.6 | 23.3 | 18.92 | 10.74 | 1.99 | 59 | 135 | 169 | 202 |
| HS468 | 46.74 | 28.7 | 15.24 | 47.6 | 27.9 | 16.13 | 11.63 | 1.34 | 37 | 86 | 107 | 128 |
| HS508 | 50.8 | 31.75 | 13.46 | 51.7 | 30.9 | 14.35 | 12.73 | 1.25 | 32 | 73 | 91 | 109 |
| HS571 | 57.15 | 26.39 | 15.24 | 58 | 25.6 | 16.1 | 12.5 | 2.29 | 60 | 138 | 172 | 206 |
| HS572 | 57.15 | 35.56 | 13.97 | 58 | 34.7 | 14.86 | 14.3 | 1.444 | 33 | 75 | 94 | 112 |
| HS610 | 62 | 32.6 | 25 | 63.1 | 31.37 | 26.27 | 14.37 | 3.675 | 83 | 192 | 240 | 288 |
| HS740 | 74.1 | 45.3 | 35 | 75.2 | 44.07 | 36.27 | 18.38 | 5.04 | 89 | 206 | 257 | 309 |
| HS777 | 77.8 | 49.23 | 12.7 | 78.9 | 48 | 13.97 | 20 | 1.77 | 30 | 68 | 85 | 102 |
| HS778 | 77.8 | 49.23 | 15.9 | 78.9 | 48 | 17.02 | 20 | 2.27 | 37 | 85 | 107 | 128 |

BIG TOROIDAL CORES





Features

- Excellent DC bias characteristics
- Low core losses
- Large energy storage capacity
- Good temperature stability

Applications


- Below 26 μ : UPS, power inductors for large currents
- Over 60 μ : PFC or output chokes for server PCs, industrial powers

■ Product Identification






| PART NO. | Before Finish Dimensions | | | After Finish Dimensions | | | Path length (cm) | Cross Section Area (cm ²) | AL value (nH/N ²) ± 8% | | |
|---------------|--------------------------|---------------|---------------|-------------------------|---------------|---------------|------------------|---------------------------------------|------------------------------------|-----------|-----------|
| | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | | | 019 μ | 026 μ | 060 μ |
| HS1013 | 101.6 | 57.2 | 13.6 | 103.1 | 55.7 | 14.9 | 24.27 | 2.972 | 29 | 40 | 92 |
| HS1016 | 101.6 | 57.2 | 16.5 | 103.1 | 55.7 | 17.8 | 24.27 | 3.522 | 35 | 48 | 112 |
| HS1027 | 101.6 | 57.2 | 27.2 | 103.1 | 55.7 | 28.5 | 24.27 | 5.944 | 58 | 80 | 184 |
| HS1033 | 101.6 | 57.2 | 33.0 | 103.1 | 55.7 | 34.3 | 24.27 | 7.044 | 70 | 96 | 224 |
| HS1320 | 132.5 | 78.6 | 20.3 | 134.2 | 77.0 | 21.7 | 32.42 | 5.347 | 39 | 54 | 124 |
| HS1325 | 132.5 | 78.6 | 25.4 | 134.2 | 77.0 | 26.8 | 32.42 | 6.710 | 49 | 68 | 156 |
| HS1333 | 132.5 | 78.6 | 33.0 | 134.2 | 77.0 | 34.4 | 32.42 | 8.717 | 64 | 88 | 202 |
| HS1340 | 132.5 | 78.6 | 40.6 | 134.2 | 77.0 | 42.0 | 32.42 | 10.694 | 79 | 108 | 248 |
| HS1625 | 165.0 | 88.9 | 25.4 | 167.2 | 86.9 | 27.3 | 38.65 | 9.460 | 58 | 80 | 184 |

■ Permeability vs DC Bias Curves




■ Permeability vs Frequency Curve



■ Core Loss 19, 26μ**■ Core Loss 60μ**

TOROIDAL POWDER CORES



Features

- Low core loss at high current
- Good DC Bias characteristics
- Economical price

Applications

- Desktop PCs, Server PCs
- Automotive parts, solar power parts
- UPS and ESS

| PART NO. | Before Finish Dimensions | | | After Finish Dimensions | | | 26μ | | 40μ | | 60μ | | Path length (cm) | Cross Section Area (cm²) | AL value (nH/N²) | | |
|--------------|--------------------------|------------|------------|-------------------------|------------|------------|--------------|--------------|--------------|--------------|--------------|--------------|------------------|--------------------------|------------------|------|------|
| | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | | | 026μ | 040μ | 060μ |
| KS096 | 9.65 | 4.78 | 3.18 | 10.29 | 4.27 | 3.81 | 1.05 | 1.08 | 1.10 | 1.13 | 1.12 | 1.15 | 2.18 | 0.0752 | 11 | 17 | 25 |
| KS097 | 9.65 | 4.78 | 3.96 | 10.29 | 4.27 | 4.57 | 1.30 | 1.34 | 1.37 | 1.41 | 1.39 | 1.43 | 2.18 | 0.0945 | 14 | 21 | 32 |
| KS102 | 10.16 | 5.08 | 3.96 | 10.80 | 4.57 | 4.57 | 1.44 | 1.49 | 1.52 | 1.56 | 1.54 | 1.59 | 2.38 | 0.1000 | 14 | 21 | 32 |
| KS112 | 11.18 | 6.35 | 3.96 | 11.90 | 5.89 | 4.72 | 1.56 | 1.61 | 1.64 | 1.69 | 1.67 | 1.72 | 2.69 | 0.0906 | 11 | 17 | 26 |
| KS127 | 12.70 | 7.62 | 4.75 | 13.46 | 6.99 | 5.51 | 2.29 | 2.36 | 2.41 | 2.48 | 2.45 | 2.52 | 3.12 | 0.114 | 12 | 18 | 27 |
| KS166 | 16.51 | 10.16 | 6.35 | 17.4 | 9.53 | 7.11 | 5.1 | 5.3 | 5.4 | 5.6 | 5.5 | 5.6 | 4.11 | 0.192 | 15 | 23 | 35 |
| KS172 | 17.27 | 9.65 | 6.35 | 18.03 | 9.02 | 7.11 | 6.2 | 6.3 | 6.5 | 6.7 | 6.6 | 6.8 | 4.14 | 0.232 | 19 | 29 | 43 |
| KS203 | 20.32 | 12.7 | 6.35 | 21.1 | 12.07 | 7.11 | 7.5 | 7.7 | 7.9 | 8.1 | 8.0 | 8.2 | 5.09 | 0.226 | 14 | 21 | 32 |
| KS229 | 22.86 | 13.97 | 7.62 | 23.62 | 13.39 | 8.38 | 11.6 | 11.9 | 12.2 | 12.5 | 12.4 | 12.7 | 5.67 | 0.331 | 19 | 29 | 43 |
| KS234 | 23.57 | 14.4 | 8.89 | 24.3 | 13.77 | 9.7 | 14.6 | 15.0 | 15.3 | 15.8 | 15.6 | 16.1 | 5.88 | 0.388 | 22 | 34 | 51 |
| KS270 | 26.92 | 14.73 | 11.18 | 27.7 | 14.1 | 11.99 | 26.4 | 27.2 | 27.8 | 28.6 | 28.3 | 29.1 | 6.35 | 0.654 | 32 | 50 | 75 |
| KS330 | 33.02 | 19.94 | 10.67 | 33.83 | 19.3 | 11.61 | 34.5 | 35.5 | 36.3 | 37.4 | 36.9 | 38.0 | 8.15 | 0.672 | 28 | 41 | 61 |
| KS343 | 34.29 | 23.37 | 8.89 | 35.2 | 22.6 | 9.83 | 26.3 | 27.1 | 27.7 | 28.5 | 28.1 | 29.0 | 8.95 | 0.454 | 16 | 25 | 38 |
| KS358 | 35.81 | 22.35 | 10.46 | 36.7 | 21.5 | 11.28 | 38.6 | 39.7 | 40.6 | 41.8 | 41.3 | 42.5 | 8.98 | 0.678 | 24 | 37 | 56 |
| KS400 | 39.88 | 24.13 | 14.48 | 40.7 | 23.3 | 15.37 | 69 | 69 | 73 | 73 | 74 | 74 | 9.84 | 1.072 | 35 | 54 | 81 |
| KS467 | 46.74 | 24.13 | 18.03 | 47.6 | 23.3 | 18.92 | 139 | 139 | 146 | 147 | 149 | 149 | 10.74 | 1.99 | 59 | 90 | 135 |
| KS468 | 46.74 | 28.7 | 15.24 | 47.6 | 27.9 | 16.13 | 98 | 98 | 103 | 104 | 105 | 105 | 11.63 | 1.34 | 37 | 57 | 86 |
| KS508 | 50.8 | 31.75 | 13.46 | 51.7 | 30.9 | 14.35 | 100 | 100 | 105 | 105 | 107 | 107 | 12.73 | 1.25 | 32 | 49 | 73 |
| KS571 | 57.15 | 26.39 | 15.24 | 58 | 25.6 | 16.1 | 189 | 189 | 199 | 199 | 202 | 202 | 12.5 | 2.29 | 60 | 92 | 138 |
| KS572 | 57.15 | 35.56 | 13.97 | 58 | 34.7 | 14.86 | 134 | 135 | 141 | 142 | 144 | 144 | 14.3 | 1.444 | 33 | 50 | 75 |
| KS610 | 62 | 32.6 | 25 | 63.1 | 31.37 | 26.27 | 332 | 333 | 350 | 351 | 356 | 357 | 14.37 | 3.675 | 83 | 128 | 192 |
| KS740 | 74.1 | 45.3 | 35 | 75.2 | 44.07 | 36.27 | 564 | 565 | 594 | 595 | 603 | 605 | 18.38 | 5.04 | 89 | 137 | 206 |
| KS777 | 77.8 | 49.23 | 12.7 | 78.9 | 48 | 13.97 | 220 | 220 | 231 | 232 | 235 | 236 | 20.00 | 1.77 | 30 | 45 | 68 |
| KS778 | 77.8 | 49.23 | 15.9 | 78.9 | 48 | 17.02 | 277 | 278 | 292 | 293 | 297 | 298 | 20.00 | 2.27 | 37 | 57 | 85 |
| KS888 | 88.9 | 66 | 15.9 | 90 | 64.74 | 17.2 | 268 | 269 | 282 | 283 | 287 | 287 | 24.01 | 1.830 | 24 | 38 | 57 |

BIG TOROIDAL CORES





Features

- Excellent DC bias characteristics
- Low core losses
- Large energy storage capacity
- Good temperature stability

Applications


- Below 26 μ : UPS, power inductors for large currents
- Over 60 μ : PFC or output chokes for server PCs, industrial powers

■ Product Identification




| PART NO. | Before Finish Dimensions | | | After Finish Dimensions | | | 26 μ | | 40 μ | | 60 μ | | Path length (cm) | Cross Section Area (cm ²) | AL value (nH/N ²) | | |
|----------|--------------------------|---------------|---------------|-------------------------|---------------|---------------|--------------|--------------|--------------|--------------|--------------|--------------|------------------|---------------------------------------|-------------------------------|-----------|-----------|
| | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | | | 026 μ | 040 μ | 060 μ |
| KS1013 | 101.6 | 57.2 | 13.6 | 103.1 | 55.7 | 14.9 | 459 | 461 | 484 | 485 | 492 | 493 | 24.27 | 2.972 | 40 | 61 | 92 |
| KS1016 | 101.6 | 57.2 | 16.5 | 103.1 | 55.7 | 17.8 | 557 | 559 | 587 | 589 | 596 | 598 | 24.27 | 3.522 | 48 | 75 | 112 |
| KS1027 | 101.6 | 57.2 | 27.2 | 103.1 | 55.7 | 28.5 | 919 | 922 | 968 | 970 | 983 | 986 | 24.27 | 5.944 | 80 | 123 | 184 |
| KS1033 | 101.6 | 57.2 | 33.0 | 103.1 | 55.7 | 34.3 | 1115 | 1118 | 1174 | 1177 | 1196 | 1193 | 24.27 | 7.044 | 96 | 149 | 224 |
| KS1320 | 132.5 | 78.6 | 20.3 | 134.2 | 77.0 | 21.7 | 1099 | 1102 | 1157 | 1161 | 1179 | 1176 | 32.42 | 5.347 | 54 | 83 | 124 |
| KS1325 | 132.5 | 78.6 | 25.4 | 134.2 | 77.0 | 26.8 | 1357 | 1379 | 1448 | 1452 | 1471 | 1476 | 32.42 | 6.710 | 68 | 104 | 156 |
| KS1333 | 132.5 | 78.6 | 33.0 | 134.2 | 77.0 | 34.4 | 1786 | 1792 | 1881 | 1887 | 1912 | 1917 | 32.42 | 8.717 | 88 | 135 | 202 |
| KS1340 | 132.5 | 78.6 | 40.6 | 134.2 | 77.0 | 42.0 | 2197 | 2204 | 2314 | 2321 | 2351 | 2358 | 32.42 | 10.694 | 108 | 165 | 248 |
| KS1625 | 165.0 | 88.9 | 25.4 | 167.2 | 86.9 | 27.3 | 2354 | 2361 | 2479 | 2487 | 2519 | 2527 | 38.65 | 9.460 | 80 | 123 | 184 |


■ Permeability vs DC Bias Curves




■ Core loss - 26μ



■ Core Loss 40 μ



■ Core Loss 60 μ



TOROIDAL POWDER CORES



Features

- Low core loss at high current
- Good DC Bias characteristics
- Economical price

Applications

- Desktop PCs, Server PCs
- Automotive parts, solar power parts
- UPS and ESS



| PART NO. | Before Finish Dimensions | | | After Finish Dimensions | | | 26μ | | 40μ | | 60μ | | 60μ | | Path length (cm) | Cross Section Area (cm²) | AL value (nH/N²) | | |
|----------|--------------------------|---------------|---------------|-------------------------|---------------|---------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|------------------|--------------------------|------------------|------|------|
| | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | | | 026μ | 040μ | 060μ |
| KH096 | 9.65 | 4.78 | 3.18 | 10.29 | 4.27 | 3.81 | 1.08 | 1.11 | 1.14 | 1.18 | 1.19 | 1.22 | 1.22 | 1.26 | 2.18 | 0.0752 | 11 | 17 | 25 |
| KH097 | 9.65 | 4.78 | 3.96 | 10.29 | 4.27 | 4.57 | 1.34 | 1.38 | 1.42 | 1.47 | 1.48 | 1.52 | 1.52 | 1.57 | 2.18 | 0.0945 | 14 | 21 | 32 |
| KH102 | 10.16 | 5.08 | 3.96 | 10.80 | 4.57 | 4.57 | 1.49 | 1.54 | 1.58 | 1.63 | 1.64 | 1.69 | 1.69 | 1.74 | 2.38 | 0.1000 | 14 | 21 | 32 |
| KH112 | 11.18 | 6.35 | 3.96 | 11.90 | 5.89 | 4.72 | 1.61 | 1.66 | 1.71 | 1.76 | 1.77 | 1.83 | 1.83 | 1.88 | 2.69 | 0.0906 | 11 | 17 | 26 |
| KH127 | 12.70 | 7.62 | 4.75 | 13.46 | 6.99 | 5.51 | 2.37 | 2.44 | 2.51 | 2.58 | 2.60 | 2.68 | 2.68 | 2.76 | 3.12 | 0.114 | 12 | 18 | 27 |
| KH166 | 16.51 | 10.16 | 6.35 | 17.4 | 9.53 | 7.11 | 5.3 | 5.5 | 5.6 | 5.8 | 5.8 | 6.0 | 6.0 | 6.2 | 4.11 | 0.192 | 15 | 23 | 35 |
| KH172 | 17.27 | 9.65 | 6.35 | 18.03 | 9.02 | 7.11 | 6.3 | 6.5 | 6.7 | 6.9 | 6.9 | 7.1 | 7.1 | 7.3 | 4.14 | 0.232 | 19 | 29 | 43 |
| KH203 | 20.32 | 12.7 | 6.35 | 21.1 | 12.07 | 7.11 | 7.7 | 7.9 | 8.2 | 8.4 | 8.5 | 8.7 | 8.7 | 9.0 | 5.09 | 0.226 | 14 | 21 | 32 |
| KH229 | 22.86 | 13.97 | 7.62 | 23.62 | 13.39 | 8.38 | 12.0 | 12.3 | 12.7 | 13.0 | 13.1 | 13.5 | 13.5 | 13.9 | 5.67 | 0.331 | 19 | 29 | 43 |
| KH234 | 23.57 | 14.4 | 8.89 | 24.3 | 13.77 | 9.7 | 15.1 | 15.5 | 15.9 | 16.4 | 16.5 | 17.0 | 17.0 | 17.6 | 5.88 | 0.388 | 22 | 34 | 51 |
| KH270 | 26.92 | 14.73 | 11.18 | 27.7 | 14.1 | 11.99 | 27.3 | 28.1 | 28.9 | 29.8 | 30.0 | 30.9 | 30.9 | 31.8 | 6.35 | 0.654 | 32 | 50 | 75 |
| KH330 | 33.02 | 19.94 | 10.67 | 33.83 | 19.3 | 11.61 | 35.6 | 36.7 | 37.7 | 38.9 | 39.2 | 40.3 | 40.3 | 41.6 | 8.15 | 0.672 | 28 | 41 | 61 |
| KH343 | 34.29 | 23.37 | 8.89 | 35.2 | 22.6 | 9.83 | 27.2 | 28.0 | 28.8 | 29.6 | 29.9 | 30.8 | 30.8 | 31.7 | 8.95 | 0.454 | 16 | 25 | 38 |
| KH358 | 35.81 | 22.35 | 10.46 | 36.7 | 21.5 | 11.28 | 39.9 | 41.0 | 42.2 | 43.5 | 43.8 | 45.1 | 45.1 | 46.5 | 8.98 | 0.678 | 24 | 37 | 56 |
| KH400 | 39.88 | 24.13 | 14.48 | 40.7 | 23.3 | 15.37 | 71 | 72 | 76 | 76 | 78 | 79 | 81 | 81 | 9.84 | 1.072 | 35 | 54 | 81 |
| KH467 | 46.74 | 24.13 | 18.03 | 47.6 | 23.3 | 18.92 | 144 | 144 | 152 | 153 | 158 | 158 | 163 | 163 | 10.74 | 1.99 | 59 | 90 | 135 |
| KH468 | 46.74 | 28.7 | 15.24 | 47.6 | 27.9 | 16.13 | 102 | 102 | 107 | 108 | 112 | 112 | 115 | 115 | 11.63 | 1.34 | 37 | 57 | 86 |
| KH508 | 50.8 | 31.75 | 13.46 | 51.7 | 30.9 | 14.35 | 103 | 103 | 109 | 109 | 113 | 114 | 117 | 117 | 12.73 | 1.25 | 32 | 49 | 73 |
| KH571 | 57.15 | 26.39 | 15.24 | 58 | 25.6 | 16.1 | 195 | 195 | 206 | 207 | 214 | 215 | 221 | 221 | 12.5 | 2.29 | 60 | 92 | 138 |
| KH572 | 57.15 | 35.56 | 13.97 | 58 | 34.7 | 14.86 | 139 | 139 | 147 | 147 | 152 | 153 | 157 | 157 | 14.3 | 1.444 | 33 | 50 | 75 |
| KH610 | 62 | 32.6 | 25 | 63.1 | 31.37 | 26.27 | 340 | 341 | 360 | 361 | 374 | 375 | 385 | 386 | 14.37 | 3.675 | 83 | 128 | 192 |
| KH740 | 74.1 | 45.3 | 35 | 75.2 | 44.07 | 36.27 | 583 | 584 | 617 | 619 | 640 | 642 | 660 | 662 | 18.38 | 5.04 | 89 | 137 | 206 |
| KH777 | 77.8 | 49.23 | 12.7 | 78.9 | 48 | 13.97 | 227 | 228 | 240 | 241 | 249 | 250 | 257 | 258 | 20.00 | 1.77 | 30 | 45 | 68 |
| KH778 | 77.8 | 49.23 | 15.9 | 78.9 | 48 | 17.02 | 287 | 288 | 304 | 305 | 315 | 316 | 325 | 326 | 20.00 | 2.27 | 37 | 57 | 85 |
| KH888 | 88.9 | 66 | 15.9 | 90 | 64.74 | 17.2 | 277 | 278 | 293 | 294 | 304 | 305 | 313 | 314 | 24.01 | 1.830 | 24 | 38 | 57 |

BIG TOROIDAL CORES




Features

- Excellent DC bias characteristics
- Low core losses
- Large energy storage capacity
- Good temperature stability

Applications

- Below 26 μ : UPS, power inductors for large currents
- Over 60 μ : PFC or output chokes for server PCs, industrial powers

■ Product Identification



KH 1013 060


Permeability : 60 μ Available Perm : 26, 60, 75, 90 μ

Core Size


KH Core



| PART NO. | Before Finish Dimensions | | | After Finish Dimensions | | | 26 μ | | 40 μ | | 60 μ | | 90 μ | | Path length (cm) | Cross Section Area (cm ²) | Al value (nH/N ²) | | |
|---------------|--------------------------|---------------|---------------|-------------------------|---------------|---------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|------------------|---------------------------------------|-------------------------------|-----------|-----------|
| | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | OD(mm) MAX | ID(mm) MIN | HT(mm) MAX | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | Weight (B.F) | Weight (A.F) | | | 026 μ | 040 μ | 060 μ |
| KH1013 | 101.6 | 57.2 | 13.6 | 103.1 | 55.7 | 14.9 | 457 | 476 | 503 | 504 | 522 | 523 | | | 24.27 | 2.972 | 40 | 61 | 92 |
| KH1016 | 101.6 | 57.2 | 16.5 | 103.1 | 55.7 | 17.8 | 576 | 578 | 610 | 612 | 633 | 635 | | | 24.27 | 3.522 | 48 | 75 | 112 |
| KH1027 | 101.6 | 57.2 | 27.2 | 103.1 | 55.7 | 28.5 | 950 | 953 | 1005 | 1009 | 1044 | 1047 | | | 24.27 | 5.944 | 80 | 123 | 184 |
| KH1033 | 101.6 | 57.2 | 33.0 | 103.1 | 55.7 | 34.3 | 1152 | 1156 | 1220 | 1224 | 1266 | 1270 | | | 24.27 | 7.044 | 96 | 149 | 224 |
| KH1320 | 132.5 | 78.6 | 20.3 | 134.2 | 77.0 | 21.7 | 1136 | 1139 | 1203 | 1206 | 1248 | 1252 | | | 32.42 | 5.347 | 54 | 83 | 124 |
| KH1325 | 132.5 | 78.6 | 25.4 | 134.2 | 77.0 | 26.8 | 1421 | 1426 | 1505 | 1509 | 1562 | 1567 | | | 32.42 | 6.710 | 68 | 104 | 156 |
| KH1333 | 132.5 | 78.6 | 33.0 | 134.2 | 77.0 | 34.4 | 1847 | 1852 | 1955 | 1961 | 2029 | 2035 | | | 32.42 | 8.717 | 88 | 135 | 202 |
| KH1340 | 132.5 | 78.6 | 40.6 | 134.2 | 77.0 | 42.0 | 2271 | 2278 | 2405 | 2412 | 2496 | 2504 | | | 32.42 | 10.694 | 108 | 165 | 248 |
| KH1625 | 165.0 | 88.9 | 25.4 | 167.2 | 86.9 | 27.3 | 2434 | 2441 | 2576 | 2584 | 2674 | 2682 | | | 38.65 | 9.460 | 80 | 123 | 184 |


■ Permeability vs DC Bias Curves



■ Core loss -26μ



■ Core Loss 40 μ **■ Core Loss 60 μ** 

Core Loss 90μ

TOROIDAL MAGNETIC POWDER CORES

Tolerance of A_L value

| Core Size | Sendust | MPP | High Flux | Mega Flux® |
|--------------|---------|------|-----------|------------|
| OD035~OD046 | ±15% | ±12% | ±12% | NA |
| OD063~OD112 | ±12% | ±8% | ±8% | ±8% |
| OD127~OD1625 | ±8% | ±8% | ±8% | ±8% |

Inductance Calculation by A_L vs NI Curves;

- Inductor specification**
- Core : CM270125
 - Number of Winding : 22Turns
 - Current : DC 10Amperes

Solution

a) Calculate NI [Ampere-Turns] $NI = 22\text{Turns} \times 10\text{Ampere} = 220$

b) Read the A_L value of CM270125 using the A_L vs NI curve on page 56.

A_L value of CM270125 yields 100.4 when NI is 220.

c) Calculate L at 10Ampere by using formula; $LN = A_L \times N^2 \times 10^{-3}[\mu\text{H}]$

 Therefore,


$$\begin{aligned}L(@10A) &= 100.4 \times 22^2 \times 0.001 \\&= 48.6[\mu\text{H}]\end{aligned}$$

CHANG SUNG CORPORATION'S ADVANCED TECHNOLOGY ENABLES US TO FULFILL THE DIVERSE NEEDS OF OUR CLIENTS FOR SOFT MAGNETIC POWDER CORES.

Powder cores are distributed air gap cores made from ferrous alloy powders for low losses at high frequencies. Small air gaps distributed evenly throughout the cores increase the amount of Direct Current (DC) that can be passed through the winding before core saturation occurs. Molybdenum Permalloy Powder (MPP) cores are ideal for low loss inductors such as switching regulators and noise filters. High Flux, Sendust and Mega Flux® cores are the preferred choices for Power Factor Correction (PFC), switching regulator inductors, in-line noise filters, pulse and flyback transformers and many other applications requiring low losses at high frequencies.

▼ Products

Cross Sectional View



Core Materials

- MPP Cores : Ni-Fe-Mo alloy
- High Flux Cores : Fe-Ni alloy
- Sendust Cores : Fe-Si-Al alloy
- Mega Flux® Cores : Fe-Si alloy
- HS, KS, KH Cores : Fe alloy

Core Shapes




- Toroids : From 3.5mm to 165mm OD
- Special : Ellipse, Block, Cylinder Washer, ER II, U, EE, EER, EQ

Permeability

- MPP : 26, 60, 125, 147, 160, 173, 200 μ
- High Flux : 26, 60, 125, 147, 160 μ
- Sendust : 26, 60, 75, 90, 125 μ
- Mega Flux® : 26, 50, 60, 75, 90 μ
- HS : 19, 26, 60, 75, 90 μ
- KS : 26, 40, 60 μ
- KH : 26, 40, 60, 90 μ

Core Finishes

- Finish : Epoxy, Parylene-C, Plastic Case
- Color - MPP : Gray
 - High Flux : Khaki
 - Sendust : Black
 - Mega Flux® : Dark Brown
 - HS, KS, KH : Dark Blue
- Break-Down Voltage : 500V min.



OUTSTANDING PRODUCTS BEGIN WITH A STANDARDIZED PRODUCTION LINE AND A STRICT QUALITY CONTROL PROCESS

Chang Sung Corporation manufactures four types of soft magnetic powder cores including the Molybdenum Permalloy (MPP), High Flux, Sendust and Mega Flux®, which are mainly used for inductors and transformers requiring low losses and inductance stability under high DC bias conditions. A fully standardized production management system under strict quality control of the raw materials (nickel, iron, molybdenum, aluminum and silicon) enables CSC to guarantee consistent quality and thus build greater confidence in our company's product line.



MPP

Ni-Fe-Mo alloy powder cores are made from alloy powders of nickel, iron and molybdenum.

MPP cores exhibit a highly sustainable level of stability in temperature and inductance under high DC magnetization or high DC Bias conditions. They offer the highest permeability among our materials and the lowest core loss compared to any other core material. MPP cores are also considered to be a premium material for direct current output inductors for SMPS including high Q filters, loading coils and EMI/RFI filters. Finished toroid cores are coated with a gray epoxy to provide dielectric protection and added physical strength.



HIGH FLUX

Ni-Fe alloy powder cores are made from alloy powders of nickel and iron.

The 15,000 Gauss saturation level of High Flux cores has a higher energy storage capability and more effective permeability when compared to the performance of gapped ferrite or powdered iron cores of a similar size. The excellent DC bias characteristics and low core losses of High Flux cores offer a reduction in size and the number of winding turns as well as superior magnetic properties. CSC High Flux cores are an excellent choice for applications such as PFC reactors, switching regulator inductors, in-line noise filters, pulse transformers and flyback transformers. Finished High Flux cores are coated with a Khaki epoxy and come in a variety of shapes and sizes.



SENDUST

Fe-Si-Al alloy powder cores are made from alloy powders of iron, silicon and aluminum.

Near-zero magnetostriction makes Sendust cores ideal for eliminating audible noise in filter inductors. Core losses of Sendust cores are significantly lower than those of powdered iron cores. Especially Sendust E shapes provide a higher energy storage capability than gapped Ferrite E cores. Gap losses and eddy current losses are minimized with Sendust E cores compared to gapped ferrite E shapes. Sendust cores are a smart choice for PFC circuits. Other major applications include switching regulator inductors, In-line noise filters, pulse transformers and flyback transformers. Finished Sendust cores are coated in a black epoxy.



MEGA FLUX®


Fe-Si alloy powder cores are made from an alloy of iron and silicon.

CSC is the first company in the world to develop magnetic powder cores made from iron and silicon. The innovative design of these unique Mega Flux cores includes a smaller size, higher current and higher energy storage capability. Mega Flux cores have a higher flux density than any other magnetic material, 16,000 gauss compared to 15,000 gauss for High Flux cores and 10,000 gauss for Sendust cores. The excellent DC bias characteristics provide the best solution for high end applications including buck/boost inductors for high power supply systems, smoothing chokes for inverters and reactors for electric vehicles. Mega Flux cores are pressed without organic binders and have significantly lower core losses than powdered iron cores and Fe-Si strip cores. They also present excellent thermal properties with no thermal aging effects. Finished Mega Flux cores are coated with a dark brown epoxy.


■ Comparison of Core Materials

| Materials | | Perm. (μ_i) | Bs(kg) | Core Loss | DC Bias | Relative Cost | Temp. Stability | Curie Temp(°C) |
|-----------|--------------------------|-------------------|--------|-----------|---------|---------------|-----------------|----------------|
| Powder | MPP | 26-200 | 7 | Lower | Good | High | Best | 450 |
| | High Flux | 26-160 | 15 | Low | Best | Medium | Better | 500 |
| | Sendust | 26-125 | 10 | Low | Good | Low | Good | 500 |
| | Mega Flux® | 26-90 | 16 | Medium | Best | Low | Better | 700 |
| | HS | 19-90 | 14 | Low | Better | Medium | Better | 500 |
| | KS | 26-60 | 14 | Medium | Better | Low | Good | 500 |
| | KH | 26-60 | 15 | Medium | Best | Medium | Good | 600 |
| | Iron | 10-100 | 10 | High | Poor | Lowest | Poor | 770 |
| Strip | Fe-Si Strip (Gap) | | 20 | High | Better | Lowest | Good | 740 |
| | Amorphous (Gap) | | 15 | Low | Better | Medium | Good | 399 |
| | Ferrite (Gap) | | 3-5 | Lowest | Poor | Lowest | Poor | 100~300 |

■ Permeability vs DC Bias



■ Core Loss (at 50kHz)



■ CSC's Core Designation

Toroidal Core Designation



CM 270 125 E

| | | |
|----------|---------------------|--|
| | Epoxy coated | Core finish E : Epoxy, P : Parylene-C, C : Plastic Case |
| | Permeability : 125μ | Available perm. 26, 50, 60, 75, 90, 125, 147, 160, 173, 200μ |
| | OD size : 27.0mm | Available size 3.5mm ~ 165.0mm (OD) |
| MPP core | | Core material CM : MPP, CH : High Flux, CS : Sendust, CK : Mega Flux® |

■ Nominal Inductance Table (AL Value)

(nH/N²)

| Permeability Part No. | 26μ 026 | 60μ 060 | 75μ 075 | 90μ 090 | 125μ 125 | 147μ 147 | 160μ 160 | 173μ 173 | 200μ 200 |
|--------------------------|------------|------------|------------|------------|-------------|-------------|-------------|-------------|-------------|
| C □ 035 □□□ | - | 13 | 16 | 19 | 26 | 31 | 33 | 36 | 42 |
| C □ 039 □□□ | - | 17 | 21 | 25 | 35 | 41 | 45 | 48 | 56 |
| C □ 046 □□□ | - | 20 | 25 | 30 | 42 | 49 | 53 | 57 | 67 |
| C □ 063 □□□ | 10 | 24 | 30 | 36 | 50 | 59 | 64 | 69 | 80 |
| C □ 066 □□□ | 11 | 26 | 32 | 39 | 54 | 64 | 69 | 75 | 86 |
| C □ 067 □□□ | 21 | 50 | 62 | 74 | 103 | 122 | 132 | 144 | 165 |
| C □ 068 □□□ | 14 | 33 | 42 | 50 | 70 | 81 | 89 | 95 | 112 |
| C □ 078 □□□ | 11 | 25 | 31 | 37 | 52 | 62 | 66 | 73 | 83 |
| C □ 096 □□□ | 11 | 25 | 32 | 38 | 53 | 63 | 68 | 74 | 84 |
| C □ 097 □□□ | 14 | 32 | 40 | 48 | 66 | 78 | 84 | 92 | 105 |
| C □ 102 □□□ | 14 | 32 | 40 | 48 | 66 | 78 | 84 | 92 | 105 |
| C □ 112 □□□ | 11 | 26 | 32 | 38 | 53 | 63 | 68 | 74 | 85 |
| C □ 127 □□□ | 12 | 27 | 34 | 40 | 56 | 67 | 72 | 79 | 90 |
| C □ 147 □□□ | 14 | 32 | 40 | 48 | 67 | 78 | 85 | 92 | 107 |
| C □ 166 □□□ | 15 | 35 | 43 | 52 | 72 | 88 | 92 | 104 | 115 |
| C □ 172 □□□ | 19 | 43 | 53 | 64 | 89 | 105 | 114 | 123 | 142 |
| C □ 203 □□□ | 14 | 32 | 41 | 49 | 68 | 81 | 87 | 96 | 109 |
| C □ 229 □□□ | 19 | 43 | 54 | 65 | 90 | 106 | 115 | 124 | 144 |
| C □ 234 □□□ | 22 | 51 | 63 | 76 | 105 | 124 | 135 | 146 | 169 |
| C □ 252 □□□ | 27 | 62 | 78 | 93 | 130 | 152 | 166 | 179 | 207 |
| C □ 270 □□□ | 32 | 75 | 94 | 113 | 157 | 185 | 201 | 217 | 251 |
| C □ 300 □□□ | 29 | 68 | 85 | 102 | 141 | 166 | 181 | 195 | - |
| C □ 330 □□□ | 28 | 61 | 76 | 91 | 127 | 150 | 163 | 176 | - |
| C □ 343 □□□ | 16 | 38 | 47 | 57 | 79 | 93 | 101 | 109 | - |
| C □ 358 □□□ | 24 | 56 | 70 | 84 | 117 | 138 | 150 | 162 | - |
| C □ 378 □□□ | 30 | 70 | 87 | 104 | 145 | 170 | 185 | 201 | - |
| C □ 400 □□□ | 35 | 81 | 101 | 121 | 168 | 198 | 215 | 233 | - |
| C □ 434 □□□ | 40 | 92 | 115 | 138 | 191 | 225 | 245 | - | - |
| C □ 467 □□□ | 59 | 135 | 169 | 202 | 281 | 330 | 360 | - | - |
| C □ 468 □□□ | 37 | 86 | 107 | 128 | 178 | 210 | 228 | - | - |
| C □ 488 □□□ | 44 | 101 | 126 | 151 | 210 | 247 | 269 | - | - |
| C □ 508 □□□ | 32 | 73 | 91 | 109 | 152 | 179 | 195 | - | - |
| C □ 540 □□□ | 44 | 102 | 128 | 153 | 213 | 250 | 272 | - | - |
| C □ 571 □□□ | 60 | 138 | 172 | 206 | 287 | 306 | 333 | - | - |
| C □ 572 □□□ | 33 | 75 | 94 | 112 | 156 | 185 | 200 | - | - |
| C □ 596 □□□ | 54 | 125 | 156 | 187 | 260 | - | - | - | - |
| C □ 610 □□□ | 83 | 192 | 240 | 288 | 400 | - | - | - | - |
| C □ 640 □□□ | 49 | 113 | 141 | 169 | 234 | - | - | - | - |
| C □ 680 □□□ | 62 | 143 | 179 | 215 | 299 | - | - | - | - |
| C □ 740 □□□ | 89 | 206 | 257 | 309 | 429 | - | - | - | - |
| C □ 777 □□□ | 30 | 68 | 85 | 102 | 142 | - | - | - | - |
| C □ 778 □□□ | 37 | 85 | 107 | 128 | 178 | - | - | - | - |
| C □ 888 □□□ | 24 | 57 | 71 | 85 | 119 | - | - | - | - |
| C □ 1016 □□□ | 48 | 112 | 137 | 164 | 228 | - | - | - | - |
| C □ 1325 □□□ | 68 | 156 | 195 | 234 | 325 | - | - | - | - |
| C □ 1650 □□□ | 80 | 184 | 230 | 276 | 384 | - | - | - | - |

* example) AL value of CM270125 is 157(nH/N²)

Core Dimension Table (Millimeters)

| Part Number | Magnetic Path Length l (cm) | Cross Section A (cm ²) | Window Area (cm ²) | Surface Area (cm ²) | | Weight (g) | | | | Dimensions (mm) OD (Max) X ID (Min) X HT (Max) | | Package Unit (pcs/box) |
|--------------|-------------------------------|------------------------------------|--------------------------------|---------------------------------|--------------------|------------|------|------|------|---|-------------------|---------------------------|
| | | | | After Finish | 40% winding factor | CM | CH | CS | CK | Before Finish | After Finish | |
| C □ 035 □□□ | 0.817 | 0.0137 | 0.018 | 0.5 | 0.61 | 0.09 | 0.09 | 0.07 | 0.08 | 3.56X1.78X1.52 | 3.94X1.52X1.96 | 30K |
| C □ 039 □□□ | 0.942 | 0.0211 | 0.0308 | 0.7 | 0.93 | 0.19 | 0.18 | 0.13 | 0.15 | 3.94X2.24X2.54 | 4.32X1.98X2.97 | 30K |
| C □ 046 □□□ | 1.060 | 0.0285 | 0.0290 | 0.9 | 1.13 | 0.26 | 0.25 | 0.20 | 0.23 | 4.65X2.36X2.54 | 5.21X1.93X3.30 | 30K |
| C □ 063 □□□ | 1.361 | 0.0470 | 0.0412 | 1.7 | 2.03 | 0.56 | 0.53 | 0.41 | 0.47 | 6.35X2.79X2.79 | 6.99X2.29X3.43 | 30K |
| C □ 066 □□□ | 1.363 | 0.0476 | 0.0412 | 1.7 | 2.06 | 0.60 | 0.57 | 0.44 | 0.50 | 6.60X2.67X2.54 | 7.24X2.29X3.18 | 30K |
| C □ 067 □□□ | 1.363 | 0.0920 | 0.0384 | 2.4 | 2.76 | 1.12 | 1.07 | 0.83 | 0.96 | 6.60X2.67X4.78 | 7.32X2.21X5.54 | 20K |
| C □ 068 □□□ | 1.650 | 0.0725 | 0.0934 | 2.7 | 3.31 | 1.03 | 0.98 | 0.76 | 0.88 | 6.86X3.96X5.08 | 7.62X3.45X5.72 | 20K |
| C □ 078 □□□ | 1.787 | 0.0615 | 0.0922 | 2.4 | 3.04 | 0.94 | 0.90 | 0.69 | 0.80 | 7.87X3.96X3.18 | 8.51X3.43X3.81 | 12K |
| C □ 096 □□□ | 2.18 | 0.0752 | 0.1429 | 3.1 | 4.14 | 1.41 | 1.34 | 1.04 | 1.21 | 9.65X4.78X3.18 | 10.29X4.27X3.81 | 9K |
| C □ 097 □□□ | 2.18 | 0.0945 | 0.1429 | 3.5 | 4.47 | 1.76 | 1.68 | 1.30 | 1.50 | 9.65X4.78X3.96 | 10.29X4.27X4.57 | 8K |
| C □ 102 □□□ | 2.38 | 0.1000 | 0.164 | 3.7 | 4.85 | 2.09 | 2.00 | 1.55 | 1.79 | 10.16X5.08X3.96 | 10.80X4.57X4.57 | 7K |
| C □ 112 □□□ | 2.69 | 0.0906 | 0.273 | 4.3 | 6.05 | 2.11 | 2.02 | 1.57 | 1.81 | 11.18X6.35X3.96 | 11.90X5.89X4.72 | 5K |
| C □ 127 □□□ | 3.12 | 0.114 | 0.383 | 5.6 | 8.00 | 3.13 | 2.99 | 2.32 | 2.69 | 12.70X7.62X4.75 | 13.46X6.99X5.51 | 4K |
| C □ 147 □□□ | 3.63 | 0.154 | 0.528 | 7.5 | 10.72 | 4.9 | 4.6 | 3.6 | 4.3 | 14.70X8.90X5.60 | 15.50X8.20X6.40 | - |
| C □ 166 □□□ | 4.11 | 0.192 | 0.713 | 9.3 | 13.66 | 6.9 | 6.6 | 5.2 | 6.0 | 16.51X10.16X6.35 | 17.40X9.53X7.11 | 1.96K |
| C □ 172 □□□ | 4.14 | 0.232 | 0.638 | 9.9 | 13.91 | 8.2 | 8.0 | 6.1 | 7.1 | 17.27X9.65X6.35 | 18.03X9.02X7.11 | 1.96K |
| C □ 203 □□□ | 5.09 | 0.226 | 1.14 | 12.1 | 18.95 | 10.0 | 10.0 | 7.4 | 8.7 | 20.32X12.70X6.35 | 21.1X12.07X7.11 | 1.37K |
| C □ 229 □□□ | 5.67 | 0.331 | 1.41 | 15.7 | 24.13 | 15.9 | 15.1 | 11.7 | 13.6 | 22.86X13.97X7.62 | 23.62X13.39X8.38 | 580 |
| C □ 234 □□□ | 5.88 | 0.388 | 1.49 | 17.9 | 26.78 | 19.6 | 19 | 14.5 | 16.8 | 23.57X14.40X8.89 | 24.30X13.77X9.70 | 750 |
| C □ 252 □□□ | 6.10 | 0.504 | 1.52 | 21.1 | 30.39 | 26.6 | 25.4 | 19.6 | 23.2 | 25.20X14.60X10.00 | 26.00X13.90X10.80 | - |
| C □ 270 □□□ | 6.35 | 0.654 | 1.56 | 24.7 | 34.42 | 35.6 | 34.0 | 26.4 | 30.6 | 26.92X14.73X11.18 | 27.70X14.10X11.99 | 360 |
| C □ 300 □□□ | 7.27 | 0.652 | 2.19 | 28.1 | 41.47 | 41 | 39.1 | 30.2 | 35.7 | 30.00X17.40X10.90 | 30.80X16.70X11.80 | - |
| C □ 330 □□□ | 8.15 | 0.672 | 2.93 | 31.5 | 49.01 | 47.0 | 44.8 | 34.8 | 40.4 | 33.02X19.94X10.67 | 33.83X19.30X11.61 | 240 |
| C □ 343 □□□ | 8.95 | 0.454 | 4.01 | 29.3 | 52.34 | 35.3 | 33.7 | 26.2 | 30.3 | 34.29X23.37X8.89 | 35.20X22.60X9.83 | 280 |
| C □ 358 □□□ | 8.98 | 0.678 | 3.64 | 34.5 | 56.09 | 52 | 50 | 39 | 45 | 35.81X22.35X10.46 | 36.70X21.50X11.28 | 240 |
| C □ 378 □□□ | 9.40 | 0.867 | 3.91 | 41.4 | 64.65 | 71 | 68 | 52 | 62 | 37.80X23.20X12.50 | 38.70X22.30X13.40 | - |
| C □ 400 □□□ | 9.84 | 1.072 | 4.27 | 48.4 | 73.77 | 91 | 87 | 67 | 78 | 39.88X24.13X14.48 | 40.70X23.30X15.37 | 120 |
| C □ 434 □□□ | 10.74 | 1.308 | 5.11 | 58.1 | 88.40 | 124 | 118 | 91 | 108 | 43.40X26.40X16.20 | 44.30X25.50X17.10 | - |
| C □ 467 □□□ | 10.74 | 1.990 | 4.27 | 69.2 | 96.50 | 182 | 174 | 134 | 157 | 46.74X24.13X18.03 | 47.60X23.30X18.92 | 72 |
| C □ 468 □□□ | 11.63 | 1.340 | 6.11 | 61.6 | 97.79 | 130 | 124 | 96 | 112 | 46.74X28.70X15.24 | 47.60X27.90X16.13 | 72 |
| C □ 488 □□□ | 11.74 | 1.569 | 5.73 | 67.6 | 102.63 | 163 | 156 | 120 | 142 | 48.80X27.90X15.80 | 49.70X27.00X16.70 | - |
| C □ 500 □□□ | 12.73 | 1.250 | 7.50 | 64.2 | 108.52 | 132 | 126 | 98 | 114 | 50.80X31.75X13.46 | 51.70X30.90X14.35 | 96 |
| C □ 540 □□□ | 12.63 | 1.710 | 6.20 | 74.8 | 114.18 | 193 | 184 | 142 | 168 | 54.00X29.00X14.40 | 54.90X28.10X15.30 | - |
| C □ 571 □□□ | 12.50 | 2.29 | 5.14 | 84.8 | 120.40 | 248 | 237 | 184 | 213 | 57.15X26.39X15.24 | 58.00X25.60X16.10 | 77 |
| C □ 572 □□□ | 14.30 | 1.444 | 9.48 | 77.2 | 133.19 | 181 | 173 | 133 | 155 | 57.15X35.56X13.97 | 58.00X34.70X14.86 | 88 |
| C □ 596 □□□ | 14.33 | 2.371 | 8.55 | 100.9 | 153.11 | 301 | 287 | 222 | 262 | 59.60X34.00X19.50 | 60.60X33.00X20.50 | - |
| C □ 610 □□□ | 14.37 | 3.675 | 7.73 | 125.1 | 173.99 | 444 | 423 | 329 | 381 | 62.0X32.6X25.0 | 63.1X31.37X26.27 | 24 |
| C □ 640 □□□ | 16.04 | 2.394 | 11.95 | 115.0 | 185.01 | 338 | 322 | 249 | 294 | 64.00X40.00X21.00 | 65.10X39.00X22.10 | - |
| C □ 680 □□□ | 15.81 | 3.008 | 9.62 | 124.8 | 233.34 | 430 | 410 | 317 | 374 | 68.00X36.00X20.00 | 69.10X35.00X21.10 | - |
| C □ 740 □□□ | 18.38 | 5.040 | 15.27 | 194.2 | 283.09 | 764 | 729 | 566 | 656 | 74.1X45.3X35.0 | 75.2X44.07X36.27 | 18 |
| C □ 777 □□□ | 20.00 | 1.770 | 17.99 | 117.3 | 224.42 | 301 | 287 | 223 | 258 | 77.8X49.23X12.7 | 78.9X48.0X13.97 | 40 |
| C □ 778 □□□ | 20.00 | 2.270 | 17.99 | 130.2 | 236.84 | 377 | 359 | 279 | 323 | 77.8X49.23X15.9 | 78.9X48.0X17.2 | 35 |
| C □ 888 □□□ | 24.10 | 1.83 | 32.72 | 134.5 | 262.03 | 369 | 351 | 273 | 316 | 88.8X66.0X15.9 | 90.13X64.54X17.4 | 15 |
| C □ 1016 □□□ | 24.27 | 3.522 | 24.37 | 207.0 | 358.37 | 774 | 739 | 572 | 665 | 101.6X57.2X16.5 | 103.1X55.7X17.8 | 12 |
| C □ 1325 □□□ | 32.42 | 6.710 | 46.57 | 367.6 | 648.48 | 1863 | 1779 | 1376 | 1620 | 132.5X78.6X25.4 | 134.2X77.0X26.8 | 4 |
| C □ 1650 □□□ | 38.65 | 9.46 | 59.31 | 538.4 | 389.82 | 3267 | 3120 | 2413 | 2808 | 165.0X88.9X25.4 | 167.2X86.9X27.3 | 4 |

※ CM : MPP Core, CH : High Flux Core, CS : Sendust Core, CK : Mega Flux® Core

※ Window area : area of inner diameter

※ In addition to the cores listed above, customized specifications are also available.

※ Please refer to our web site(www.changsung.com) for the new toroidal cores.

■ Magnetic Design Formulas

Inductance of a Wound Core

The inductance of a wound core at a given number of turns is calculated using the following formula.

$$L = \frac{0.4 \pi \mu N^2 A \times 10^{-2}}{\ell}$$

$$L_N = A_L \times N^2 \times 10^{-3}$$

L = inductance (μH)
 μ = core permeability
 N = number of turns
 A = effective cross section area (cm^2)
 ℓ = mean magnetic path length (cm)
 L_N = Inductance at N turns (μH)
 A_L = nominal Inductance (nH/N^2)

Permeability - Flux Density - Magnetizing Force

Ampere's Law and Faraday's Law show the relations of permeability, flux density and magnetizing force of a wound core.

$$H = \frac{0.4 \pi N l}{\ell} \quad \text{----- Ampere's Law}$$

$$B_{\max} = \frac{E_{\text{rms}} \times 10^8}{4.44 f A N} \quad \text{----- Faraday's Law}$$

$$\mu = \frac{B}{H}$$

H = magnetizing force (oersteds)
 N = number of turns
 l = peak magnetizing current (amperes)
 ℓ = mean magnetic path length (cm)
 B_{\max} = maximum flux density (gausses)
 E_{rms} = voltage across coil (volts)
 f = frequency (hertz)

Inductance Calculation by Permeability vs DC Bias Curves

Inductor specification

- Core : CM270125
- Number of Windings : 22Turns
- Current : DC 10Amperes

solution

a) Formula to calculate L at 0Ampere

$$L_N = A_L \times N^2 \times 10^{-3}$$

The Nominal inductance table on page 22 shows the A_L value of CM270125 to be 157.

$$\text{Therefore, } L(@0A) = 157 \times 22^2 \times 0.001 = 76 \text{ } (\mu\text{H})$$

b) Determine DC magnetizing force (H) by using Ampere's law to achieve the roll off.

$$H = 0.4 \pi N l / \ell$$

$$H = 0.4 \times 3.14 \times 22 \times 10 / 6.35 = 43.5 \text{ (Oe)}$$

The magnetizing force (dc bias) is 43.5 oersteds, yielding 64% of initial permeability. See on page 28.

The inductance at 10Ampere will decrease the inductance by 64% compared with 0Ampere.


$$\begin{aligned} \text{Therefore, } L(@10A) &= 76 \times 0.64 \\ &= 48.6 \text{ } (\mu\text{H}) \end{aligned}$$

* Inductance calculation by A_L vs Nl Curve is also available on page 18.

Mean Magnetic Path Length

For toroidal powder cores, the effective area (A) is the same as the cross sectional area. By definition and Ampere's Law, the effective magnetic path length is the ratio of ampere-turns (NI) to the average magnetizing force. Using Ampere's Law and averaging the magnetizing force gives the formula for effective path length.

$$\ell = \frac{\pi(OD - ID)}{\ln \left(\frac{OD}{ID} \right)}$$



OD = outside diameter of core (cm)

ID = inside diameter of core (cm)

A = core cross section (effective area)

ℓ = mean magnetic path length (cm)

Q Factor

The Q factor is defined as the ratio of reactance to the effective resistance for an inductor and thus indicates its quality. The Q of wound core can be calculated using the following formula, when neglecting the effects of self-resonance caused by the distributed capacitance resulting from the differential voltage between adjacent turns.

$$Q = \frac{\omega L}{R_{dc} + R_{ac} + R_d}$$

Q = quality factor

ω = 2π frequency (hertz)

L = inductance (henries)

R_{dc} = DC winding resistance (ohms)

R_{ac} = resistance due to core loss (ohms)

R_d = resistance due to winding dielectric loss (ohms)

Core Loss

Powder cores have low hysteresis loss, minimizing signal distortion, and low residual loss. The total core loss at low flux Densities is the sum of three frequency dependent losses : hysteresis loss, residual loss, and eddy current loss. The core loss is calculated from the following Legg's equation.

$$\frac{R_{ac}}{\omega L} = \frac{aB_{max}f + cf + ef^2}{| \text{Eddy current loss} | + | \text{Residual loss} | + | \text{Hysteresis loss} | + | \text{Total loss factor} |}$$

Where R_{ac} = core loss resistance (ohms)

a = hysteresis loss coefficient

c = residual loss coefficient

e = eddy current loss coefficient


ω , L, B_{max}, f = same as mentioned before

When a varying magnetic field passes through the core, eddy currents are induced in it. Joule heat loss by these currents is called eddy current loss. Hysteresis loss is due to the irreversible behavior in the hysteresis curve and equal to the enclosed area of the loop.


The other core loss is called residual loss.


■ Permeability vs DC Bias Curves

MPP




High Flux






Sendust


Mega Flux[®]

■ Permeability vs Frequency Curves


MPP




High Flux





Sendust





Mega Flux®




■ MPP Core Loss

MPP 26 μ , 60 μ MPP 125 μ


MPP Core Loss



■ High Flux Core Loss




High Flux 26 μ




High Flux 60 μ

■ High Flux Core Loss



High Flux 125 μ





High Flux 147 μ , 160 μ




■ Sendust Core Loss

Sendust 26 μ Sendust 60 μ , 75 μ , 90 μ , 125 μ


■ Mega Flux® Core Loss




■ Temperature Stability




MPP



High Flux



Sendust



Mega Flux®

Wire Table

| AWG Wire No. | Bare Area | | Resistivity $10^{-8} \Omega \text{ cm}$ at 20 °C | Heavy Synthetics | | | | Current Capacity Amps (listed by columns of amps/cm²) | | | | | |
|--------------------|---------------------------------------|---------|--|--------------------------------|---------|----------|--------|--|---------|---------|--------|--------|--|
| | cm^2 ($\times 10^{-3}$) | Cir-Mil | | Area | | Diameter | | Weight gm/cm | 200 | 400 | 600 | 800 | |
| | | | | $\text{cm}^2 (\times 10^{-3})$ | Cir-Mil | cm | inch | | | | | | |
| 10 | 53.61 | 10384 | 32.70 | 55.9 | 11046 | 0.267 | 0.1051 | 0.468 | 10.4 | 20.8 | 31.2 | 41.6 | |
| 11 | 41.68 | 8226 | 41.37 | 44.5 | 8798 | 0.238 | 0.0938 | 0.3750 | 8.23 | 16.4 | 24.6 | 32.8 | |
| 12 | 33.08 | 6529 | 52.09 | 35.64 | 7022 | 0.213 | 0.0838 | 0.2977 | 6.53 | 13.06 | 19.6 | 26.1 | |
| 13 | 26.26 | 5184 | 65.64 | 28.36 | 5610 | 0.190 | 0.0749 | 0.2367 | 5.18 | 10.4 | 15.5 | 20.8 | |
| 14 | 20.82 | 4109 | 82.80 | 22.95 | 4556 | 0.171 | 0.0675 | 0.1879 | 4.11 | 8.22 | 12.3 | 16.4 | |
| 15 | 16.51 | 3260 | 104.3 | 18.37 | 3624 | 0.153 | 0.0602 | 0.1492 | 3.26 | 6.52 | 9.78 | 13.0 | |
| 16 | 13.07 | 2581 | 131.8 | 14.73 | 2905 | 0.137 | 0.0539 | 0.1184 | 2.58 | 5.16 | 7.74 | 10.3 | |
| 17 | 10.39 | 2052 | 165.8 | 11.68 | 2323 | 0.122 | 0.0482 | 0.0943 | 2.05 | 4.10 | 6.15 | 8.20 | |
| 18 | 8.228 | 1624 | 209.5 | 9.326 | 1857 | 0.109 | 0.0431 | 0.07472 | 1.62 | 3.25 | 4.88 | 6.50 | |
| 19 | 6.531 | 1289 | 263.9 | 7.539 | 1490 | 0.0980 | 0.0386 | 0.05940 | 1.29 | 2.58 | 3.87 | 5.16 | |
| 20 | 5.188 | 1024 | 332.3 | 6.065 | 1197 | 0.0879 | 0.0346 | 0.04726 | 1.02 | 2.05 | 3.08 | 4.10 | |
| 21 | 4.116 | 812.3 | 418.9 | 4.837 | 954.8 | 0.0785 | 0.0309 | 0.03757 | 0.812 | 1.63 | 2.44 | 3.25 | |
| 22 | 3.243 | 640.1 | 531.4 | 3.857 | 761.7 | 0.0701 | 0.0276 | 0.02965 | 0.640 | 1.28 | 1.92 | 2.56 | |
| 23 | 2.588 | 510.8 | 666.0 | 3.135 | 620.0 | 0.0632 | 0.0249 | 0.02372 | 0.511 | 1.02 | 1.53 | 2.04 | |
| 24 | 2.047 | 404.0 | 842.1 | 2.514 | 497.3 | 0.0566 | 0.0223 | 0.01884 | 0.404 | 0.808 | 1.21 | 1.62 | |
| 25 | 1.623 | 320.4 | 1062.0 | 2.002 | 396.0 | 0.0505 | 0.0199 | 0.01498 | 0.320 | 0.641 | 0.962 | 1.28 | |
| 26 | 1.280 | 252.8 | 1345.0 | 1.603 | 316.8 | 0.0452 | 0.0178 | 0.01185 | 0.253 | 0.506 | 0.759 | 1.01 | |
| 27 | 10.21 | 201.6 | 1687.6 | 1.313 | 259.2 | 0.0409 | 0.0161 | 0.00945 | 0.202 | 0.403 | 0.604 | 0.806 | |
| 28 | 0.8046 | 158.8 | 2142.7 | 1.0515 | 207.3 | 0.0366 | 0.0144 | 0.00747 | 0.159 | 0.318 | 0.477 | 0.636 | |
| 29 | 0.6470 | 127.7 | 2664.3 | 0.8548 | 169.0 | 0.0330 | 0.0130 | 0.00602 | 0.128 | 0.255 | 0.382 | 0.510 | |
| 30 | 0.5067 | 100.0 | 3402.2 | 0.6785 | 134.5 | 0.0294 | 0.0116 | 0.00472 | 0.100 | 0.200 | 0.300 | 0.400 | |
| 31 | 0.4013 | 79.21 | 4294.6 | 0.5595 | 110.2 | 0.0267 | 0.0105 | 0.00372 | 0.0792 | 0.158 | 0.237 | 0.316 | |
| 32 | 0.3242 | 64.00 | 5314.9 | 0.4559 | 90.25 | 0.0241 | 0.0095 | 0.00305 | 0.0640 | 0.128 | 0.192 | 0.256 | |
| 33 | 0.2554 | 50.41 | 6748.6 | 0.3662 | 72.25 | 0.0216 | 0.0085 | 0.00214 | 0.0504 | 0.101 | 0.152 | 0.202 | |
| 34 | 0.2011 | 39.69 | 8572.8 | 0.2863 | 56.25 | 0.0191 | 0.0075 | 0.00189 | 0.0397 | 0.0794 | 0.119 | 0.159 | |
| 35 | 0.1589 | 31.36 | 10849 | 0.2268 | 44.89 | 0.0170 | 0.0067 | 0.00150 | 0.0314 | 0.0627 | 0.0940 | 0.125 | |
| 36 | 0.1266 | 25.00 | 13608 | 0.1813 | 36.00 | 0.0152 | 0.0060 | 0.00119 | 0.0250 | 0.0500 | 0.0750 | 0.100 | |
| 37 | 0.1026 | 20.25 | 16801 | 0.1538 | 30.25 | 0.0140 | 0.0055 | 0.000977 | 0.0203 | 0.0405 | 0.0608 | 0.0810 | |
| 38 | 0.08107 | 16.00 | 21266 | 0.1207 | 24.01 | 0.0124 | 0.0049 | 0.000773 | 0.0160 | 0.0320 | 0.0480 | 0.0640 | |
| 39 | 0.06207 | 12.25 | 27775 | 0.0932 | 18.49 | 0.0109 | 0.0043 | 0.000593 | 0.0123 | 0.0245 | 0.0368 | 0.0490 | |
| 40 | 0.04869 | 9.61 | 35400 | 0.0723 | 14.44 | 0.0096 | 0.0038 | 0.000464 | 0.00961 | 0.0192 | 0.0288 | 0.0384 | |
| 41 | 0.03972 | 7.84 | 43405 | 0.0584 | 11.56 | 0.00863 | 0.0034 | 0.000379 | 0.00785 | 0.0157 | 0.0236 | 0.0314 | |
| 42 | 0.03166 | 6.25 | 54429 | 0.04558 | 9.00 | 0.00762 | 0.0030 | 0.000299 | 0.00625 | 0.0125 | 0.0188 | 0.0250 | |
| 43 | 0.02452 | 4.84 | 70308 | 0.03683 | 7.29 | 0.00685 | 0.0027 | 0.000233 | 0.00484 | 0.00968 | 0.0145 | 0.0194 | |
| 44 | 0.0202 | 4.00 | 85072 | 0.03165 | 6.25 | 0.00635 | 0.0025 | 0.000195 | 0.00400 | 0.00800 | 0.0120 | 0.0160 | |

■ Winding Data

| Core Size | Window Area ^a | | Wire Length / Turn | | | | Wound Dimension ^c OD × HT[Max] | |
|-----------|---------------------------|-----------------|--------------------|-------|--------|-------|--|--------------|
| | 100% (unity) ^b | | 0 % | | | | inch | mm |
| | Cir-Mils | cm ² | ft | cm | ft | cm | | |
| 035 | 3,600 | 0.018 | 0.0229 | 0.698 | 0.0195 | 0.594 | 0.195 × 0.108 | 4.95 × 2.74 |
| 039 | 6,080 | 0.0308 | 0.0344 | 1.049 | 0.0293 | 0.894 | 0.227 × 0.187 | 5.77 × 4.75 |
| 046 | 5,780 | 0.029 | 0.0375 | 1.143 | 0.0324 | 0.988 | 0.262 × 0.195 | 6.65 × 4.94 |
| 063 | 8,100 | 0.0412 | 0.0442 | 1.348 | 0.0379 | 1.156 | 0.347 × 0.212 | 8.81 × 5.38 |
| 066 | 8,100 | 0.0412 | 0.0435 | 1.327 | 0.0371 | 1.132 | 0.359 × 0.202 | 9.12 × 5.13 |
| 067 | 7,570 | 0.0384 | 0.0575 | 1.754 | 0.0531 | 1.620 | 0.361 × 0.292 | 9.17 × 7.42 |
| 068 | 18,500 | 0.0934 | 0.0586 | 1.786 | 0.0512 | 1.561 | 0.378 × 0.394 | 9.60 × 10.01 |
| 078 | 18,200 | 0.0922 | 0.0524 | 1.598 | 0.0417 | 1.272 | 0.433 × 0.265 | 11.0 × 6.73 |
| 096 | 28,200 | 0.1429 | 0.0588 | 1.793 | 0.0448 | 1.366 | 0.526 × 0.293 | 13.4 × 7.44 |
| 097 | 28,200 | 0.1429 | 0.0632 | 1.928 | 0.0498 | 1.519 | 0.526 × 0.323 | 13.4 × 8.20 |
| 102 | 32,400 | 0.164 | 0.0651 | 1.986 | 0.0504 | 1.537 | 0.554 × 0.333 | 14.1 × 8.46 |
| 112 | 53,800 | 0.273 | 0.0720 | 2.195 | 0.0507 | 1.545 | 0.618 × 0.353 | 15.7 × 9.0 |
| 127 | 75,600 | 0.383 | 0.0815 | 2.49 | 0.0574 | 1.751 | 0.717 × 0.451 | 18.2 × 11.5 |
| 166 | 140,600 | 0.713 | 0.1057 | 3.22 | 0.0721 | 2.20 | 0.932 × 0.599 | 23.7 × 15.2 |
| 172 | 126,000 | 0.638 | 0.1204 | 3.67 | 0.0763 | 2.33 | 0.980 × 0.641 | 24.9 × 16.3 |
| 203 | 225,600 | 1.14 | 0.1204 | 3.67 | 0.0763 | 2.33 | 1.148 × 0.684 | 29.2 × 17.4 |
| 229 | 277,700 | 1.41 | 0.1405 | 4.29 | 0.0886 | 2.70 | 1.283 × 0.778 | 32.6 × 19.8 |
| 234 | 293,800 | 1.49 | 0.1473 | 4.49 | 0.0982 | 3.00 | 1.319 × 0.843 | 33.5 × 21.4 |
| 270 | 308,000 | 1.56 | 0.1714 | 5.23 | 0.1233 | 3.76 | 1.468 × 0.944 | 37.3 × 24.0 |
| 330 | 577,600 | 2.93 | 0.1943 | 5.93 | 0.1238 | 3.78 | 1.840 × 1.103 | 46.7 × 28.0 |
| 343 | 788,500 | 4.01 | 0.1923 | 5.87 | 0.1059 | 3.23 | 1.974 × 1.142 | 50.1 × 29.0 |
| 358 | 719,100 | 3.64 | 0.204 | 6.22 | 0.1238 | 3.78 | 2.01 × 1.165 | 51.1 × 29.6 |
| 400 | 842,700 | 4.27 | 0.242 | 7.38 | 0.1578 | 4.81 | 2.22 × 1.385 | 56.4 × 35.2 |
| 467 | 842,700 | 4.27 | 0.284 | 8.66 | 0.204 | 6.22 | 2.51 × 1.525 | 63.8 × 38.7 |
| 468 | 1,206,000 | 6.11 | 0.273 | 8.34 | 0.1706 | 5.20 | 2.61 × 1.568 | 66.3 × 39.8 |
| 508 | 1,484,000 | 7.50 | 0.279 | 8.51 | 0.1623 | 4.95 | 2.85 × 1.600 | 72.4 × 40.6 |
| 571 | 1,014,049 | 5.14 | 0.296 | 9.02 | 0.212 | 6.46 | 2.98 × 1.34 | 75.7 × 34.0 |
| 572 | 1,871,000 | 9.48 | 0.306 | 9.33 | 0.1739 | 5.30 | 3.20 × 1.748 | 81.3 × 44.4 |
| 777 | 3,550,000 | 17.99 | 0.340 | 10.40 | 0.193 | 5.90 | 4.40 × 2.14 | 112.0 × 54.3 |

* a : Window Area ($= \pi/4 \times ID^2$: Core inside diameter), b : Winding Factor (k= Usable window area / Total window area), c : 100% Winding Assumed

■ Single Layer Winding Capacity

OD035

OD 3.56mm / 0.140inch



Available Cores

| MPP | Part No. | | A _L (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|--|--------------------|
| | High Flux | Sendust | | |
| - | - | - | - | 26 |
| CM035060 | CH035060 | CS035060 | CK035060 | 13 60 |
| - | - | CS035075 | CK035075 | 16 75 |
| - | - | CS035090 | CK035090 | 19 90 |
| CM035125 | CH035125 | CS035125 | - | 26 125 |
| CM035147 | - | - | - | 31 147 |
| CM035160 | - | - | - | 33 160 |
| - | - | - | - | 173 |
| - | - | - | - | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) | |
|-------------------------------|----------------|---------------|---------------|---------------|
| Before coating | (mm) (inch) | 3.56 0.140 | 1.78 0.070 | 1.52 0.060 |
| After coating (parylene-C) | (mm) (inch) | 3.76 0.148 | 1.58 0.062 | 1.72 0.068 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|-----------------------|--------------------|----------------------|-------------------------|
| 0.0137cm ² | 0.817cm | 0.018cm ² | 0.010746cm ³ |
| 0.002in ² | 0.317in | 3,600cmil | 0.000656in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|---------------|-------------------------|--------------|---------------|
| | Turn | Rdc, Ω | | Turn | Rdc, Ω |
| 28 | 0.0366 | 9 | 0.0237 | 37 | 0.0140 |
| 29 | 0.0330 | 10 | 0.0314 | 38 | 0.0124 |
| 30 | 0.0294 | 11 | 0.0431 | 39 | 0.0199 |
| 31 | 0.0267 | 13 | 0.0581 | 40 | 0.0096 |
| 32 | 0.0241 | 14 | 0.0768 | 41 | 0.00863 |
| 33 | 0.0216 | 16 | 0.105 | 42 | 0.00762 |
| 34 | 0.0191 | 19 | 0.146 | 43 | 0.00685 |
| 35 | 0.0170 | 21 | 0.200 | 44 | 0.00635 |
| 36 | 0.0152 | 24 | 0.272 | 56 | 2.67 |
| | | | | 60 | 3.45 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(125 μ)



OD039

OD 3.94mm / 0.155inch

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | (mm) | 3.94 | 2.24 | 2.54 |
| | (inch) | 0.155 | 0.088 | 0.100 |
| After coating | (mm) | 4.41 | 2.04 | 2.74 |
| (parylene-C) | (inch) | 0.163 | 0.080 | 0.108 |


Magnetic Dimensions

| Cross Section (A) | Path Length (ℓ) | Window Area (Wa) | Volume (V) |
|-------------------------|---------------------------|-----------------------|-------------------------|
| 0.0211cm ² | 0.942cm | 0.0308cm ² | 0.019670cm ³ |
| 0.003245in ² | 0.370inch | 6,080cmil | 0.001200in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------------|----------|---------|--------------|---------------|
| No. | Dia(cm) | Turn | Rdc, Ω | No. | Dia(cm) | Turn | Rdc, Ω |
| 27 | 0.0409 | 11 | 0.0248 | 36 | 0.0152 | 33 | 0.430 |
| 28 | 0.0366 | 12 | 0.0342 | 37 | 0.0140 | 36 | 0.579 |
| 29 | 0.0330 | 14 | 0.0458 | 38 | 0.0124 | 41 | 0.807 |
| 30 | 0.0294 | 16 | 0.0638 | 39 | 0.0109 | 47 | 1.18 |
| 31 | 0.0267 | 18 | 0.0869 | 40 | 0.0096 | 53 | 1.67 |
| 32 | 0.0241 | 20 | 0.116 | 41 | 0.00863 | 59 | 2.25 |
| 33 | 0.0216 | 23 | 0.161 | 42 | 0.00762 | 67 | 3.15 |
| 34 | 0.0191 | 26 | 0.226 | 43 | 0.00685 | 74 | 4.45 |
| 35 | 0.0170 | 29 | 0.313 | 44 | 0.00635 | 80 | 5.76 |


Single layer winding with 1 inch leads



Available Cores

| MPP | Part No. | | | AL (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|------------|----------------------------|--------------------|
| | High Flux | Sendust | Mega Flux® | | |
| - | - | - | - | - | 26 |
| CM039060 | CH039060 | CS039060 | CK039060 | 17 | 60 |
| - | - | CS039075 | CK039075 | 21 | 75 |
| - | - | CS039090 | CK039090 | 25 | 90 |
| CM039125 | CH039125 | CS039125 | - | 35 | 125 |
| CM039147 | - | - | - | 41 | 147 |
| CM039160 | - | - | - | 45 | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

■ AL vs NI Curve(125 μ)



OD046

OD 4.65mm / 0.183inch



Available Cores

| MPP | Part No. | | | A_L | Perm. |
|----------|-----------|----------|------------|---------|-----------|
| | High Flux | Sendust | Mega Flux® | (nH/N²) | (μ) |
| - | - | - | - | - | 26 |
| CM046060 | CH046060 | CS046060 | CK046060 | 20 | 60 |
| - | - | CS046075 | CK046075 | 25 | 75 |
| - | - | CS046090 | CK046090 | 30 | 90 |
| CM046125 | CH046125 | CS046125 | - | 42 | 125 |
| CM046147 | - | - | - | 49 | 147 |
| CM046160 | - | - | - | 53 | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|-------------------------------|----------------|---------------|---------------|---------------|
| Before coating | (mm) (inch) | 4.65 0.183 | 2.36 0.093 | 2.54 0.100 |
| After coating (parylene-C) | (mm) (inch) | 4.85 0.191 | 2.16 0.085 | 2.74 0.108 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|-------------------|-----------------|------------------|-------------|
| 0.0285cm² | 1.060cm | 0.029cm² | 0.0302cm³ |
| 0.00442in² | 0.418in | 5,780cml | 0.001837in³ |

Winding Information

| AWG Wire No. | Dia(cm) | Single Layer | | AWG Wire No. | Single Layer | | |
|--------------|---------|--------------|--------|--------------|--------------|--------|-------|
| | | Turn | Rdc, Ω | | Turn | Rdc, Ω | |
| 26 | 0.0452 | 9 | 0.0205 | 35 | 0.0170 | 28 | 0.371 |
| 27 | 0.0409 | 10 | 0.0280 | 36 | 0.0152 | 31 | 0.511 |
| 28 | 0.0366 | 12 | 0.0388 | 37 | 0.0140 | 35 | 0.691 |
| 29 | 0.0330 | 13 | 0.0524 | 38 | 0.0124 | 39 | 0.968 |
| 30 | 0.0294 | 15 | 0.0734 | 39 | 0.0109 | 45 | 1.42 |
| 31 | 0.0267 | 17 | 0.101 | 40 | 0.0096 | 51 | 2.02 |
| 32 | 0.0241 | 19 | 0.135 | 41 | 0.0083 | 57 | 2.73 |
| 33 | 0.0216 | 22 | 0.188 | 42 | 0.00762 | 64 | 3.83 |
| 34 | 0.0191 | 25 | 0.266 | 43 | 0.00685 | 71 | 5.42 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD063

OD 6.35mm / 0.250inch

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | (mm) | 6.35 | 2.79 | 2.79 |
| | (inch) | 0.250 | 0.110 | 0.110 |
| After coating | (mm) | 6.99 | 2.29 | 3.43 |
| (parylene-C) | (inch) | 0.275 | 0.090 | 0.135 |


Magnetic Dimensions

| Cross Section (A) | Path Length (ℓ) | Window Area (W_a) | Volume (V) |
|------------------------|---------------------------|--------------------------|-------------------------|
| 0.0470cm ² | 1.361cm | 0.0412cm ² | 0.064219cm ³ |
| 0.00729in ² | 0.536inch | 8,100cmil | 0.003919in ³ |

Winding Information

| AWG Wire No. | Single Layer | | AWG Wire No. | Single Layer | |
|-----------------|--------------|--------------------|-----------------|--------------|--------------------|
| | Dia(cm) | Turn Rdc, Ω | | Dia(cm) | Turn Rdc, Ω |
| 24 | 0.0566 | 8 | 0.0132 | 33 | 0.0216 |
| 25 | 0.0505 | 10 | 0.0183 | 34 | 0.0191 |
| 26 | 0.0452 | 11 | 0.0253 | 35 | 0.0170 |
| 27 | 0.0409 | 13 | 0.0346 | 36 | 0.0152 |
| 28 | 0.0366 | 14 | 0.0482 | 37 | 0.0140 |
| 29 | 0.0330 | 16 | 0.0653 | 38 | 0.0124 |
| 30 | 0.0294 | 19 | 0.0918 | 39 | 0.0109 |
| 31 | 0.0267 | 21 | 0.126 | 40 | 0.0096 |
| 32 | 0.0241 | 23 | 0.170 | 41 | 0.00863 |


Single layer winding with 1 inch leads



Available Cores

| MPP | Part No. | | | AL (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|------------|----------------------------|--------------------|
| | High Flux | Sendust | Mega Flux® | | |
| - | - | - | - | - | 26 |
| CM063060 | CH063060 | CS063060 | CK063060 | 24 | 60 |
| - | - | CS063075 | CK063075 | 30 | 75 |
| - | - | CS063090 | CK063090 | 36 | 90 |
| CM063125 | CH063125 | CS063125 | - | 50 | 125 |
| CM063147 | CH063147 | - | - | 59 | 147 |
| CM063160 | CH063160 | - | - | 64 | 160 |
| CM063173 | - | - | - | 69 | 173 |
| CM063200 | - | - | - | 80 | 200 |

■ AL vs NI Curve(60 μ , 125 μ)



OD066

OD 6.6mm / 0.260inch



Available Cores

| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-------|
| | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM066026 | CH066026 | - | - | 11 | 26 |
| CM066060 | CH066060 | CS066060 | CK066060 | 26 | 60 |
| - | - | CS066075 | CK066075 | 32 | 75 |
| - | - | CS066090 | CK066090 | 39 | 90 |
| CM066125 | CH066125 | CS066125 | - | 54 | 125 |
| CM066147 | CH066147 | - | - | 64 | 147 |
| CM066160 | CH066160 | - | - | 69 | 160 |
| CM066173 | - | - | - | 75 | 173 |
| CM066200 | - | - | - | 86 | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|--------------------------|---------------|---------------|---------------|
| Before coating | (mm) 0.260 | 6.6 0.105 | 2.54 0.100 |
| After coating (Epoxy) | (mm) 0.285 | 7.24 0.090 | 3.18 0.125 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|------------------------|--------------------|-----------------------|-------------------------|
| 0.0476cm ² | 1.363cm | 0.0412cm ² | 0.063971m ³ |
| 0.00738in ² | 0.537in | 8,100cmil | 0.003904in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|--------|----------|---------|--------------|-------|
| No. | Dia(cm) | Turn | Rdc,Ω | No. | Dia(cm) | Turn | Rdc,Ω |
| 25 | 0.0505 | 10 | 0.0180 | 34 | 0.0191 | 30 | 0.330 |
| 26 | 0.0452 | 11 | 0.0249 | 35 | 0.0170 | 34 | 0.461 |
| 27 | 0.0409 | 13 | 0.0341 | 36 | 0.0152 | 38 | 0.637 |
| 28 | 0.0366 | 14 | 0.0474 | 37 | 0.0140 | 42 | 0.862 |
| 29 | 0.0330 | 16 | 0.0642 | 38 | 0.0124 | 47 | 1.21 |
| 30 | 0.0294 | 19 | 0.0902 | 39 | 0.0109 | 54 | 1.78 |
| 31 | 0.0267 | 21 | 0.124 | 40 | 0.0096 | 61 | 2.53 |
| 32 | 0.0241 | 23 | 0.167 | 41 | 0.00863 | 68 | 3.43 |
| 33 | 0.0216 | 26 | 0.233 | 42 | 0.00762 | 77 | 4.81 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60μ, 125μ)



OD067

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 6.6 | 2.67 | 4.78 |
| | [inch] | 0.260 | 0.105 | 0.188 |

| | | OD(max) | ID(min) | HT(max) |
|-----------------------|--------|---------|---------|---------|
| After coating (Epoxy) | [mm] | 7.32 | 2.21 | 5.54 |
| | [inch] | 0.288 | 0.087 | 0.218 |

OD 6.6mm / 0.260inch

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|------------------------|-----------------|-----------------------|-------------------------|
| 0.0920cm ² | 1.363cm | 0.0384cm ² | 0.1254cm ³ |
| 0.01426in ² | 0.537inch | 7,570cmil | 0.007443in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|--------|----------|---------|--------------|-------|
| No. | Dia(cm) | Turn | Rdc,Ω | No. | Dia(cm) | Turn | Rdc,Ω |
| 25 | 0.0505 | 9 | 0.0223 | 34 | 0.0191 | 29 | 0.440 |
| 26 | 0.0452 | 11 | 0.0312 | 35 | 0.0170 | 32 | 0.617 |
| 27 | 0.0409 | 12 | 0.0431 | 36 | 0.0152 | 36 | 0.857 |
| 28 | 0.0366 | 14 | 0.0605 | 37 | 0.0140 | 40 | 1.17 |
| 29 | 0.0330 | 16 | 0.0826 | 38 | 0.0124 | 45 | 1.64 |
| 30 | 0.0294 | 18 | 0.117 | 39 | 0.0109 | 52 | 2.42 |
| 31 | 0.0267 | 20 | 0.162 | 40 | 0.0096 | 59 | 3.46 |
| 32 | 0.0241 | 22 | 0.220 | 41 | 0.00863 | 66 | 4.70 |
| 33 | 0.0216 | 25 | 0.309 | 42 | 0.00762 | 74 | 6.62 |

Single layer winding with 1 inch leads

■ AL vs NI Curve(60μ, 125μ)



OD068

OD 6.86mm / 0.270inch



Available Cores

| MPP | Part No. | | | A_L | Perm. |
|----------|-----------|----------|------------|---------|-----------|
| | High Flux | Sendust | Mega Flux® | (nH/N²) | (μ) |
| CM068026 | CH068026 | - | - | 14 | 26 |
| CM068060 | CH068060 | CS068060 | CK068060 | 33 | 60 |
| - | - | CS068075 | CK068075 | 42 | 75 |
| - | - | CS068090 | CK068090 | 50 | 90 |
| CM068125 | CH068125 | CS068125 | - | 70 | 125 |
| CM068147 | CH068147 | - | - | 81 | 147 |
| CM068160 | CH068160 | - | - | 89 | 160 |
| CM068173 | - | - | - | 95 | 173 |
| CM068200 | - | - | - | 112 | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) | |
|--------------------------|----------------|---------------|---------------|---------------|
| Before coating | (mm) [inch] | 6.86 0.270 | 3.96 0.156 | 5.08 0.200 |
| After coating [Epoxy] | (mm) [inch] | 7.62 0.300 | 3.45 0.136 | 5.72 0.225 |

Magnetic Dimensions


| Cross Section [A] | Path Length [l] | Window Area [Wa] | Volume [V] |
|----------------------|--------------------|---------------------|---------------|
| 0.0725cm² | 1.65cm | 0.0934cm² | 0.126009m³ |
| 0.01124in² | 0.605in | 18,500cmil | 0.007693in³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|---------------|-------------------------|--------------|---------------|
| | Turn | Rdc, Ω | | Turn | Rdc, Ω |
| 21 0.0785 | 9 | 0.00902 | 30 0.0294 | 29 | 0.177 |
| 22 0.0701 | 11 | 0.0126 | 31 0.0267 | 33 | 0.244 |
| 23 0.0632 | 12 | 0.0174 | 32 0.0241 | 36 | 0.331 |
| 24 0.0566 | 14 | 0.0242 | 33 0.0216 | 41 | 0.466 |
| 25 0.0505 | 16 | 0.0338 | 34 0.0191 | 46 | 0.664 |
| 26 0.0452 | 18 | 0.0472 | 35 0.0170 | 52 | 0.932 |
| 27 0.0409 | 21 | 0.0651 | 36 0.0152 | 58 | 1.29 |
| 28 0.0366 | 23 | 0.0915 | 37 0.0140 | 65 | 1.76 |
| 29 0.0330 | 26 | 0.125 | 38 0.0124 | 73 | 2.48 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD078

OD 7.87mm / 0.310inch

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 7.87 | 3.96 | 3.18 |
| | [inch] | 0.310 | 0.156 | 0.125 |

| | | OD(max) | ID(min) | HT(max) |
|--------------------------|--------|---------|---------|---------|
| After coating (Epoxy) | [mm] | 8.51 | 3.43 | 3.81 |
| | [inch] | 0.335 | 0.135 | 0.150 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|------------------------|--------------------|-----------------------|-----------------------|
| 0.0615cm ² | 1.787cm | 0.0922cm ² | 0.1099cm ³ |
| 0.00953in ² | 0.704inch | 18,200cmil | 0.0067in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|--------|----------|---------|--------------|--------|
| No. | Dia(cm) | Turn | Rdc, Ω | No. | Dia(cm) | Turn | Rdc, Ω |
| 21 | 0.0785 | 9 | 0.0078 | 30 | 0.0294 | 29 | 0.146 |
| 22 | 0.0701 | 11 | 0.0108 | 31 | 0.0267 | 33 | 0.201 |
| 23 | 0.0632 | 12 | 0.0148 | 32 | 0.0241 | 36 | 0.272 |
| 24 | 0.0566 | 14 | 0.0206 | 33 | 0.0216 | 41 | 0.382 |
| 25 | 0.0505 | 16 | 0.0285 | 34 | 0.0191 | 46 | 0.543 |
| 26 | 0.0452 | 18 | 0.0397 | 35 | 0.0170 | 52 | 0.760 |
| 27 | 0.0409 | 20 | 0.0545 | 36 | 0.0152 | 58 | 1.05 |
| 28 | 0.0366 | 23 | 0.0762 | 37 | 0.0140 | 64 | 1.43 |
| 29 | 0.0330 | 26 | 0.104 | 38 | 0.0124 | 72 | 2.01 |


Single layer winding with 1 inch leads



Available Cores

| MPP | Part No. | | | AL (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|------------|----------------------------|--------------|
| | High Flux | Sendust | Mega Flux® | | |
| CM078026 | CH078026 | — | — | 11 | 26 |
| CM078060 | CH078060 | CS078060 | CK078060 | 25 | 60 |
| — | — | CS078075 | CK078075 | 31 | 75 |
| — | — | CS078090 | CK078090 | 37 | 90 |
| CM078125 | CH078125 | CS078125 | — | 52 | 125 |
| CM078147 | CH078147 | — | — | 62 | 147 |
| CM078160 | CH078160 | — | — | 66 | 160 |
| CM078173 | — | — | — | 73 | 173 |
| CM078200 | — | — | — | 83 | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD096

OD 9.65mm / 0.380inch



Available Cores

| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-----------|
| | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM096026 | CH096026 | - | - | 11 | 26 |
| CM096060 | CH096060 | CS096060 | CK096060 | 25 | 60 |
| - | - | CS096075 | CK096075 | 32 | 75 |
| - | - | CS096090 | CK096090 | 38 | 90 |
| CM096125 | CH096125 | CS096125 | - | 53 | 125 |
| CM096147 | CH096147 | - | - | 63 | 147 |
| CM096160 | CH096160 | - | - | 68 | 160 |
| CM096173 | - | - | - | 74 | 173 |
| CM096200 | - | - | - | 84 | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|--------------------------|----------------|----------------|---------------|
| Before coating | [mm] [inch] | 9.65 0.380 | 4.78 0.188 |
| After coating (Epoxy) | [mm] [inch] | 10.29 0.405 | 3.18 0.125 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|------------------------|-----------------|-----------------------|-----------------------|
| 0.0725cm ² | 2.18cm | 0.1429cm ² | 0.1639m ³ |
| 0.01166in ² | 0.859in | 128,200cmil | 0.0100in ³ |

Winding Information

| AWG Wire No. | Dia(cm) | Single Layer | | AWG Wire No. | Dia(cm) | Single Layer | |
|--------------|---------|--------------|---------------|--------------|---------|--------------|---------------|
| | | Turn | Rdc, Ω | | | Turn | Rdc, Ω |
| 19 | 0.0980 | 9 | 0.0053 | 28 | 0.0366 | 29 | 0.100 |
| 20 | 0.0879 | 11 | 0.0073 | 29 | 0.0330 | 33 | 0.136 |
| 21 | 0.0785 | 12 | 0.0101 | 30 | 0.0294 | 37 | 0.193 |
| 22 | 0.0701 | 14 | 0.0141 | 31 | 0.0267 | 41 | 0.266 |
| 23 | 0.0632 | 16 | 0.0193 | 32 | 0.0241 | 46 | 0.360 |
| 24 | 0.0566 | 18 | 0.0268 | 33 | 0.0216 | 51 | 0.505 |
| 25 | 0.0505 | 21 | 0.0372 | 34 | 0.0191 | 58 | 0.719 |
| 26 | 0.0452 | 23 | 0.0519 | 35 | 0.0170 | 65 | 1.01 |
| 27 | 0.0409 | 26 | 0.0714 | 36 | 0.0152 | 73 | 1.40 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD097

OD 9.65mm / 0.380inch

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 9.65 | 4.78 | 3.96 |
| | [inch] | 0.380 | 0.188 | 0.156 |
| After coating | [mm] | 10.29 | 4.27 | 4.57 |
| (Epoxy) | [inch] | 0.405 | 0.168 | 0.180 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|------------------------|--------------------|-----------------------|------------------------|
| 0.0945cm ² | 2.18cm | 0.1429cm ² | 0.2060cm ³ |
| 0.01465in ² | 0.859inch | 28,200cmil | 0.01258in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|---------|-------------------------|--------------|--------|
| | Turn | Rdc, Ω | | Turn | Rdc, Ω |
| 19 0.0980 | 9 | 0.00567 | 28 0.0366 | 29 | 0.110 |
| 20 0.0879 | 11 | 0.00783 | 29 0.0330 | 33 | 0.150 |
| 21 0.0785 | 12 | 0.0109 | 30 0.0294 | 37 | 0.212 |
| 22 0.0701 | 14 | 0.0152 | 31 0.0267 | 41 | 0.293 |
| 23 0.0632 | 16 | 0.0209 | 32 0.0241 | 46 | 0.397 |
| 24 0.0566 | 18 | 0.0291 | 33 0.0216 | 51 | 0.558 |
| 25 0.0505 | 21 | 0.0405 | 34 0.0191 | 58 | 0.795 |
| 26 0.0452 | 23 | 0.0567 | 35 0.0170 | 65 | 1.12 |
| 27 0.0409 | 26 | 0.0782 | 36 0.0152 | 73 | 1.55 |


Single layer winding with 1 inch leads



Available Cores

| Part No. | MPP | High Flux | Sendust | Mega Flux® | AL | Perm. |
|----------|----------|-----------|----------|------------|----------------------|-------|
| | | | | | (nH/N ²) | (μ) |
| CM097026 | CH097026 | - | - | - | 14 | 26 |
| CM097060 | CH097060 | CS097060 | CK097060 | CS097075 | 32 | 60 |
| - | - | - | CS097075 | CK097075 | 40 | 75 |
| - | - | - | CS097090 | CK097090 | 48 | 90 |
| CM097125 | CH097125 | CS097125 | - | - | 66 | 125 |
| CM097147 | CH097147 | - | - | - | 78 | 147 |
| CM097160 | CH097160 | - | - | - | 84 | 160 |
| CM097173 | - | - | - | - | 92 | 173 |
| CM097200 | - | - | - | - | 105 | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD102

OD 10.16mm / 0.400inch



Available Cores

| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-----------|
| | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM102026 | CH102026 | - | - | 14 | 26 |
| CM102060 | CH102060 | CS102060 | CK102060 | 32 | 60 |
| - | - | CS102075 | CK102075 | 40 | 75 |
| - | - | CS102090 | CK102090 | 48 | 90 |
| CM102125 | CH102125 | CS102125 | - | 66 | 125 |
| CM102147 | CH102147 | - | - | 78 | 147 |
| CM102160 | CH102160 | - | - | 84 | 160 |
| CM102173 | - | - | - | 92 | 173 |
| CM102200 | - | - | - | 105 | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|----------------|-----------------|----------------|---------------|
| Before coating | (mm) [inch] | 10.16 0.400 | 5.08 0.200 |
| After coating | (mm) [Epoxy] | 10.80 0.425 | 4.57 0.180 |
| | | | 3.96 0.156 |
| | | | 4.57 0.180 |

Magnetic Dimensions


| Cross Section [A] | Path Length (l) | Window Area (Wa) | Volume (V) |
|------------------------|-----------------|----------------------|-----------------------|
| 0.1000cm ² | 2.38cm | 0.164cm ² | 0.2380cm ³ |
| 0.01550in ² | 0.906in | 32,400cmil | 0.0140in ³ |

Winding Information

| AWG Wire No. | Dia(cm) | Single Layer | | AWG Wire No. | Dia(cm) | Single Layer | |
|--------------|---------|--------------|---------------|--------------|---------|--------------|---------------|
| | | Turn | Rdc, Ω | | | Turn | Rdc, Ω |
| 18 | 0.109 | 9 | 0.00442 | 27 | 0.0409 | 28 | 0.0846 |
| 19 | 0.0980 | 10 | 0.00613 | 28 | 0.0366 | 32 | 0.119 |
| 20 | 0.0879 | 12 | 0.00847 | 29 | 0.0330 | 35 | 0.162 |
| 21 | 0.0785 | 13 | 0.0118 | 30 | 0.0294 | 40 | 0.230 |
| 22 | 0.0701 | 15 | 0.0164 | 31 | 0.0267 | 44 | 0.317 |
| 23 | 0.0632 | 17 | 0.0226 | 32 | 0.0241 | 49 | 0.430 |
| 24 | 0.0566 | 20 | 0.0315 | 33 | 0.0216 | 55 | 0.605 |
| 25 | 0.0505 | 22 | 0.0439 | 34 | 0.0191 | 62 | 0.862 |
| 26 | 0.0452 | 25 | 0.0614 | 35 | 0.0170 | 70 | 1.21 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD112

OD 11.18mm / 0.440inch

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 11.18 | 6.35 | 3.96 |
| | [inch] | 0.440 | 0.250 | 0.156 |
| After coating | [mm] | 11.90 | 5.89 | 4.72 |
| (Epoxy) | [inch] | 0.468 | 0.232 | 0.186 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|------------------------|--------------------|----------------------|------------------------|
| 0.0906cm ² | 2.69cm | 0.273cm ² | 0.2437cm ³ |
| 0.01403in ² | 1.08in | 53,800cmil | 0.01515in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------|----------|---------|--------------|--------|
| No. | Dia(cm) | Turn | Rdc, Ω | No. | Dia(cm) | Turn | Rdc, Ω |
| 16 | 0.137 | 9 | 0.00299 | 25 | 0.0505 | 29 | 0.0566 |
| 17 | 0.122 | 11 | 0.00412 | 26 | 0.0452 | 33 | 0.0792 |
| 18 | 0.109 | 12 | 0.00572 | 27 | 0.0409 | 37 | 0.109 |
| 19 | 0.0980 | 14 | 0.00792 | 28 | 0.0366 | 42 | 0.153 |
| 20 | 0.0879 | 16 | 0.0109 | 29 | 0.0330 | 46 | 0.209 |
| 21 | 0.0785 | 18 | 0.0152 | 30 | 0.0294 | 52 | 0.297 |
| 22 | 0.0701 | 21 | 0.0212 | 31 | 0.0267 | 58 | 0.410 |
| 23 | 0.0632 | 23 | 0.0292 | 32 | 0.0241 | 64 | 0.556 |
| 24 | 0.0566 | 26 | 0.0406 | 33 | 0.0216 | 72 | 0.782 |


Single layer winding with 1 inch leads



Available Cores

| MPP | Part No. | | | Al | Perm. |
|----------|-----------|----------|------------|----------------------|-------|
| | High Flux | Sendust | Mega Flux® | [nH/N ²] | (μ) |
| CM112026 | CH112026 | CS112026 | CK112026 | 11 | 26 |
| CM112060 | CH112060 | CS112060 | CK112060 | 26 | 60 |
| - | - | CS112075 | CK112075 | 32 | 75 |
| - | - | CS112090 | CK112090 | 38 | 90 |
| CM112125 | CH112125 | CS112125 | - | 53 | 125 |
| CM112147 | CH112147 | - | - | 63 | 147 |
| CM112160 | CH112160 | - | - | 68 | 160 |
| CM112173 | - | - | - | 74 | 173 |
| CM112200 | - | - | - | 85 | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD127

OD 12.70mm / 0.500inch



Available Cores

| MPP | Part No. | | Sendust | Mega Flux® | A_L (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|----------|------------|-------------------------------|--------------------|
| | High Flux | CK127026 | | | | |
| CM127026 | CH127026 | CS127026 | CK127026 | 12 | 26 | |
| CM127060 | CH127060 | CS127060 | CK127060 | 27 | 60 | |
| - | - | CS127075 | CK127075 | 34 | 75 | |
| - | - | CS127090 | CK127090 | 40 | 90 | |
| CM127125 | CH127125 | CS127125 | - | 56 | 125 | |
| CM127147 | CH127147 | - | - | 67 | 147 | |
| CM127160 | CH127160 | - | - | 72 | 160 | |
| CM127173 | - | - | - | 79 | 173 | |
| CM127200 | - | - | - | 90 | 200 | |

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|--------------------------|----------------|----------------|---------------|---------------|
| Before coating | [mm] [inch] | 12.70 0.500 | 7.62 0.300 | 4.75 0.187 |
| After coating (Epoxy) | [mm] [inch] | 13.46 0.530 | 6.99 0.275 | 5.51 0.217 |

Magnetic Dimensions


| Cross Section (A) | Path Length (ℓ) | Window Area (Wa) | Volume (V) |
|------------------------|---------------------------|----------------------|-------------------------|
| 0.114cm ² | 3.12cm | 0.383cm ² | 0.35568cm ³ |
| 0.01767in ² | 1.229in | 75,600cmil | 0.002172in ³ |

Winding Information

| AWG Wire No. | Dia(cm) | Single Layer | | AWG Wire No. | Single Layer | | |
|-----------------|---------|--------------|---------------|-----------------|--------------|---------------|--------|
| | | Turn | Rdc, Ω | | Turn | Rdc, Ω | |
| 15 | 0.153 | 10 | 0.00271 | 24 | 0.0566 | 31 | 0.0518 |
| 16 | 0.137 | 11 | 0.00376 | 25 | 0.0505 | 35 | 0.0723 |
| 17 | 0.122 | 13 | 0.00520 | 26 | 0.0452 | 40 | 0.101 |
| 18 | 0.109 | 15 | 0.00722 | 27 | 0.0409 | 45 | 0.140 |
| 19 | 0.0980 | 17 | 0.0100 | 28 | 0.0366 | 50 | 0.197 |
| 20 | 0.0879 | 19 | 0.0139 | 29 | 0.0330 | 56 | 0.269 |
| 21 | 0.0785 | 22 | 0.0193 | 30 | 0.0294 | 63 | 0.381 |
| 22 | 0.0701 | 25 | 0.0270 | 31 | 0.0267 | 69 | 0.527 |
| 23 | 0.0632 | 28 | 0.0371 | 32 | 0.0241 | 77 | 0.716 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD166

OD 16.51mm / 0.650inch

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 16.51 | 10.16 | 6.35 |
| | [inch] | 0.650 | 0.400 | 0.250 |
| After coating | [mm] | 17.40 | 9.53 | 7.11 |
| (Epoxy) | [inch] | 0.680 | 0.375 | 0.280 |

Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|-----------------------|--------------------|----------------------|-----------------------|
| 0.1920cm ² | 4.11cm | 0.713cm ² | 0.7891cm ³ |
| 0.0298in ² | 1.619in | 140,600mil | 0.0438in ³ |

Winding Information

| AWG Wire | Single Layer | | AWG Wire | Single Layer | |
|----------|--------------|-------------|----------|--------------|-------------|
| | No. Dia(cm) | Turn Rdc, Ω | | No. Dia(cm) | Turn Rdc, Ω |
| 12 | 0.213 | 10 | 0.00165 | 21 | 0.0785 |
| 13 | 0.190 | 11 | 0.00230 | 22 | 0.0701 |
| 14 | 0.171 | 13 | 0.00318 | 23 | 0.0632 |
| 15 | 0.153 | 15 | 0.00443 | 24 | 0.0566 |
| 16 | 0.137 | 17 | 0.00617 | 25 | 0.0505 |
| 17 | 0.122 | 19 | 0.00856 | 26 | 0.0452 |
| 18 | 0.109 | 21 | 0.01119 | 27 | 0.0409 |
| 19 | 0.0980 | 24 | 0.0166 | 28 | 0.0366 |
| 20 | 0.0879 | 27 | 0.0231 | 29 | 0.0330 |
| | | | | 62 | 0.239 |
| | | | | 69 | 0.336 |
| | | | | 77 | 0.460 |


Single layer winding with 1 inch leads



Available Cores

| MPP | Part No. | | AL (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|----------------------------|--------------|
| | High Flux | Sendust | | |
| CM166026 | CH166026 | CS166026 | CK166026 | 15 26 |
| CM166060 | CH166060 | CS166060 | CK166060 | 35 60 |
| - | - | CS166075 | CK166075 | 43 75 |
| - | - | CS166090 | CK166090 | 52 90 |
| CM166125 | CH166125 | CS166125 | - | 72 125 |
| CM166147 | CH166147 | - | - | 88 147 |
| CM166160 | CH166160 | - | - | 92 160 |
| CM166173 | - | - | - | 104 173 |
| CM166200 | - | - | - | 115 200 |

■ AL vs NI Curve(60μ, 125μ)



OD172

OD 17.27mm / 0.680inch



Available Cores

| MPP | Part No. | | Mega Flux® | A _L [nH/N ²] | Perm. [μ] |
|----------|-----------|----------|------------|-------------------------------------|-----------------|
| | High Flux | Sendust | | | |
| CM172026 | CH172026 | CS172026 | CK172026 | 19 | 26 |
| CM172060 | CH172060 | CS172060 | CK172060 | 43 | 60 |
| - | - | CS172075 | CK172075 | 53 | 75 |
| - | - | CS172090 | CK172090 | 64 | 90 |
| CM172125 | CH172125 | CS172125 | - | 89 | 125 |
| CM172147 | CH172147 | - | - | 105 | 147 |
| CM172160 | CH172160 | - | - | 114 | 160 |
| CM172173 | - | - | - | 123 | 173 |
| CM172200 | - | - | - | 142 | 200 |

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|--------------------------|----------------|----------------|---------------|---------------|
| Before coating | [mm] [inch] | 17.27 0.680 | 9.65 0.380 | 6.35 0.250 |
| After coating (Epoxy) | [mm] [inch] | 18.03 0.710 | 9.02 0.355 | 7.11 0.280 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|---|------------------|-------------------------------------|--|
| 0.232cm ² 0.0360in ² | 4.14cm 1.63in | 0.683cm ² 126,000cmil | 0.9605cm ³ 0.005868in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------------|----------|---------|--------------|---------------|
| No. | Dia(cm) | Turn | Rdc, Ω | No. | Dia(cm) | Turn | Rdc, Ω |
| 12 | 0.213 | 9 | 0.00161 | 21 | 0.0785 | 29 | 0.0319 |
| 13 | 0.190 | 10 | 0.00225 | 22 | 0.0701 | 33 | 0.0449 |
| 14 | 0.171 | 12 | 0.00311 | 23 | 0.0632 | 37 | 0.0621 |
| 15 | 0.153 | 14 | 0.00434 | 24 | 0.0566 | 41 | 0.0869 |
| 16 | 0.137 | 16 | 0.00606 | 25 | 0.0505 | 47 | 0.122 |
| 17 | 0.122 | 18 | 0.00843 | 26 | 0.0452 | 52 | 0.171 |
| 18 | 0.109 | 20 | 0.0118 | 27 | 0.0409 | 58 | 0.237 |
| 19 | 0.0980 | 23 | 0.0164 | 28 | 0.0366 | 65 | 0.334 |
| 20 | 0.0879 | 26 | 0.0228 | 29 | 0.0330 | 73 | 0.458 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD203

OD 20.32mm / 0.800inch

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 20.32 | 12.70 | 6.35 |
| | [inch] | 0.800 | 0.500 | 0.250 |
| After coating | [mm] | 21.1 | 12.07 | 7.11 |
| (Epoxy) | [inch] | 0.830 | 0.475 | 0.280 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|---------------------|------------------------|
| 0.226cm ² | 5.09cm | 1.14cm ² | 1.1510cm ³ |
| 0.035in ² | 2.01in | 225,600mil | 0.07035in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------|----------|---------|--------------|--------|
| No. | Dia(cm) | Turn | Rdc,Ω | No. | Dia(cm) | Turn | Rdc,Ω |
| 12 | 0.213 | 13 | 0.00221 | 21 | 0.0785 | 40 | 0.0430 |
| 13 | 0.190 | 15 | 0.00307 | 22 | 0.0701 | 45 | 0.0604 |
| 14 | 0.171 | 17 | 0.00424 | 23 | 0.0632 | 50 | 0.0834 |
| 15 | 0.153 | 19 | 0.00590 | 24 | 0.0566 | 56 | 0.117 |
| 16 | 0.137 | 22 | 0.00822 | 25 | 0.0505 | 63 | 0.164 |
| 17 | 0.122 | 25 | 0.0114 | 26 | 0.0452 | 71 | 0.230 |
| 18 | 0.109 | 28 | 0.0159 | 27 | 0.0409 | 79 | 0.318 |
| 19 | 0.0980 | 32 | 0.0222 | 28 | 0.0366 | 89 | 0.448 |
| 20 | 0.0879 | 35 | 0.0308 | 29 | 0.0330 | 98 | 0.614 |


Single layer winding with 1 inch leads



Available Cores


| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-------|
| | High Flux | Sendust | Mega Flux® | [nH/N ²] | [μ] |
| CM203026 | CH203026 | CS203026 | CK203026 | 14 | 26 |
| CM203060 | CH203060 | CS203060 | CK203060 | 32 | 60 |
| - | - | CS203075 | CK203075 | 41 | 75 |
| - | - | CS203090 | CK203090 | 49 | 90 |
| CM203125 | CH203125 | CS203125 | - | 68 | 125 |
| CM203147 | CH203147 | - | - | 81 | 147 |
| CM203160 | CH203160 | - | - | 87 | 160 |
| CM203173 | - | - | - | 96 | 173 |
| CM203200 | - | - | - | 109 | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD229

OD 22.86mm / 0.900inch



Available Cores

| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-----------|
| | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM229026 | CH229026 | CS229026 | CK229026 | 19 | 26 |
| CM229060 | CH229060 | CS229060 | CK229060 | 43 | 60 |
| - | - | CS229075 | CK229075 | 54 | 75 |
| - | - | CS229090 | CK229090 | 65 | 90 |
| CM229125 | CH229125 | CS229125 | - | 90 | 125 |
| CM229147 | CH229147 | - | - | 106 | 147 |
| CM229160 | CH229160 | - | - | 115 | 160 |
| CM229173 | - | - | - | 124 | 173 |
| CM229200 | - | - | - | 200 | |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|--|----------------|----------------|---------------|
| Before coating (mm) (inch) | 22.86 0.900 | 13.97 0.550 | 7.62 0.300 |
| After coating (Epoxy) (mm) (inch) | 23.62 0.930 | 13.39 0.527 | 8.38 0.330 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|--|------------------|------------------------------------|---|
| 0.331cm ² 00.0513in ² | 5.67cm 2.23in | 1.41cm ² 277,700cmil | 1.8771cm ³ 0.11455in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|----------------------|--------------|---------------|----------------------|--------------|---------------|
| | Turn | Rdc, Ω | | Turn | Rdc, Ω |
| 12 0.213 | 15 | 0.00276 | 21 0.0785 | 45 | 0.0548 |
| 13 0.190 | 17 | 0.00384 | 22 0.0701 | 50 | 0.0771 |
| 14 0.171 | 19 | 0.00532 | 23 0.0632 | 56 | 0.107 |
| 15 0.153 | 22 | 0.00742 | 24 0.0566 | 63 | 0.150 |
| 16 0.137 | 25 | 0.0104 | 25 0.0505 | 71 | 0.210 |
| 17 0.122 | 28 | 0.0144 | 26 0.0452 | 79 | 0.295 |
| 18 0.109 | 31 | 0.0202 | 27 0.0409 | 88 | 0.409 |
| 19 0.0980 | 35 | 0.0281 | 28 0.0366 | 99 | 0.577 |
| 20 0.0879 | 40 | 0.0392 | 29 0.0330 | 109 | 0.791 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD234

OD 23.57mm / 0.928inch

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 23.57 | 14.40 | 8.89 |
| | [inch] | 0.928 | 0.567 | 0.350 |
| After coating | [mm] | 24.30 | 13.77 | 9.70 |
| (Epoxy) | [inch] | 0.956 | 0.542 | 0.382 |

Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|---------------------|-----------------------|
| 0.388cm ² | 5.88cm | 1.49cm ² | 2.2814cm ³ |
| 0.061in ² | 2.32in | 293,800cmil | 0.1415in ³ |

Winding Information


| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------|----------|---------|--------------|--------|
| No. | Dia(cm) | Turn | Rdc,Ω | No. | Dia(cm) | Turn | Rdc,Ω |
| 12 | 0.213 | 15 | 0.00307 | 21 | 0.0785 | 46 | 0.0620 |
| 13 | 0.190 | 17 | 0.00429 | 22 | 0.0701 | 52 | 0.0874 |
| 14 | 0.171 | 20 | 0.00595 | 23 | 0.0632 | 58 | 0.1210 |
| 15 | 0.153 | 22 | 0.00832 | 24 | 0.0566 | 65 | 0.170 |
| 16 | 0.137 | 25 | 0.0116 | 25 | 0.0505 | 73 | 0.238 |
| 17 | 0.122 | 29 | 0.0162 | 26 | 0.0452 | 81 | 0.336 |
| 18 | 0.109 | 32 | 0.0227 | 27 | 0.0409 | 91 | 0.465 |
| 19 | 0.0980 | 36 | 0.0318 | 28 | 0.0366 | 101 | 0.657 |
| 20 | 0.0879 | 41 | 0.0443 | 29 | 0.0330 | 112 | 0.901 |

Single layer winding with 1 inch leads

Available Cores


| MPP | Part No. | | | AL (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|------------|----------------------------|--------------|
| | High Flux | Sendust | Mega Flux® | | |
| CM234026 | CH234026 | CS234026 | CK234026 | 22 | 26 |
| CM234060 | CH234060 | CS234060 | CK234060 | 51 | 60 |
| - | - | CS234075 | CK234075 | 63 | 75 |
| - | - | CS234090 | CK234090 | 76 | 90 |
| CM234125 | CH234125 | CS234125 | - | 105 | 125 |
| CM234147 | CH234147 | - | - | 124 | 147 |
| CM234160 | CH234160 | - | - | 135 | 160 |
| CM234173 | - | - | - | 146 | 173 |
| CM234200 | - | - | - | 169 | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD270

OD 26.92mm / 1.060inches



Available Cores

| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-----------|
| | High Flux | Sendust | Mega Flux® | [nH/N ²] | (μ) |
| CM270026 | CH270026 | CS270026 | CK270026 | 32 | 26 |
| CM270060 | CH270060 | CS270060 | CK270060 | 75 | 60 |
| - | - | CS270075 | CK270075 | 94 | 75 |
| - | - | CS270090 | CK270090 | 113 | 90 |
| CM270125 | CH270125 | CS270125 | - | 157 | 125 |
| CM270147 | CH270147 | - | - | 185 | 147 |
| CM270160 | CH270160 | - | - | 201 | 160 |
| CM270173 | - | - | - | 217 | 173 |
| CM270200 | - | - | - | 251 | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|----------------|---------|---------|---------|
| Before coating | [mm] | 26.92 | 14.73 |
| | [inch] | 1.060 | 0.580 |
| After coating | [mm] | 27.70 | 14.10 |
| (Epoxy) | [inch] | 1.090 | 0.555 |
| | | | 0.472 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|-----------------------|-----------------|---------------------|-----------------------|
| 0.654cm ² | 6.35cm | 1.56cm ² | 4.154cm ³ |
| 0.1014in ² | 2.50in | 308,000cmil | 0.2536in ³ |

Winding Information

| AWG Wire No. Dial(cm) | Single Layer | | AWG Wire No. Dial(cm) | Single Layer | |
|-----------------------|--------------|---------------|-----------------------|--------------|---------------|
| | Turn | Rdc, Ω | | Turn | Rdc, Ω |
| 12 | 0.213 | 16 | 0.00367 | 21 | 0.0785 |
| 13 | 0.190 | 18 | 0.00514 | 22 | 0.0701 |
| 14 | 0.171 | 20 | 0.00715 | 23 | 0.0632 |
| 15 | 0.153 | 23 | 0.0100 | 24 | 0.0566 |
| 16 | 0.137 | 26 | 0.0141 | 25 | 0.0505 |
| 17 | 0.122 | 29 | 0.0197 | 26 | 0.0452 |
| 18 | 0.109 | 33 | 0.0276 | 27 | 0.0409 |
| 19 | 0.0980 | 37 | 0.0387 | 28 | 0.0366 |
| 20 | 0.0879 | 42 | 0.0541 | 29 | 0.0330 |
| | | | | 115 | 1.11 |

Single layer winding with 1 inch leads

■ AL vs NI Curve(60 μ , 125 μ)



OD330

OD 33.02mm / 1.300inches

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 33.02 | 19.94 | 10.67 |
| | [inch] | 1.300 | 0.785 | 0.420 |
| After coating | [mm] | 33.83 | 19.30 | 11.61 |
| (Epoxy) | [inch] | 1.332 | 0.760 | 0.457 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|-----------------------|--------------------|---------------------|-----------------------|
| 00.672cm ² | 8.15cm | 2.93cm ² | 5.4768cm ³ |
| 0.1042in ² | 3.21in | 577,600mil | 0.3345in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|---------|-------------------------|--------------|-----------|
| | Turn | Rdc, Ω | | Turn | Rdc, Ω |
| 12 0.213 | 23 | 0.00517 | 21 | 0.0785 | 66 0.105 |
| 13 0.190 | 26 | 0.00722 | 22 | 0.0701 | 74 0.148 |
| 14 0.171 | 29 | 0.0100 | 23 | 0.0632 | 82 0.206 |
| 15 0.153 | 32 | 0.0140 | 24 | 0.0566 | 92 0.289 |
| 16 0.137 | 37 | 0.0197 | 25 | 0.0505 | 103 0.406 |
| 17 0.122 | 41 | 0.0274 | 26 | 0.0452 | 115 0.572 |
| 18 0.109 | 46 | 0.0384 | 27 | 0.0409 | 128 0.794 |
| 19 0.0980 | 52 | 0.0538 | 28 | 0.0366 | 143 1.12 |
| 20 0.0879 | 58 | 0.0750 | 29 | 0.0330 | 159 1.54 |


Single layer winding with 1 inch leads



Available Cores


| Part No. | MPP | High Flux | Sendust | Mega Flux® | AL | Perm. |
|----------|----------|-----------|----------|------------|----------------------|-------|
| | | | | | [nH/N ²] | [μ] |
| CM330026 | CH330026 | CS330026 | CK330026 | 28 | 26 | |
| CM330060 | CH330060 | CS330060 | CK330060 | 61 | 60 | |
| - | - | CS330075 | CK330075 | 76 | 75 | |
| - | - | CS330090 | CK330090 | 91 | 90 | |
| CM330125 | CH330125 | CS330125 | - | - | 127 | 125 |
| CM330147 | CH330147 | - | - | - | 150 | 147 |
| CM330160 | CH330160 | - | - | - | 163 | 160 |
| CM330173 | - | - | - | - | 176 | 173 |
| - | - | - | - | - | 203 | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD343

OD 34.29mm / 1.350inches



Available Cores

| MPP | Part No. | | A _L (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|--|--------------|
| | High Flux | Sendust | | |
| CM343026 | CH343026 | CS343026 | CK343026 | 16 26 |
| CM343060 | CH343060 | CS343060 | CK343060 | 38 60 |
| - | - | CS343075 | CK343075 | 47 75 |
| - | - | CS343090 | CK343090 | 57 90 |
| CM343125 | CH343125 | CS343125 | - | 79 125 |
| CM343147 | CH343147 | - | - | 93 147 |
| CM343160 | CH343160 | - | - | 101 160 |
| CM343173 | - | - | - | 109 173 |
| - | - | - | - | 126 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|--------------------------|----------------|----------------|----------------|
| Before coating | [mm] [inch] | 34.29 1.350 | 23.37 0.920 |
| After coating (Epoxy) | [mm] [inch] | 35.20 1.385 | 22.60 0.888 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|-----------------------|--------------------|---------------------|-----------------------|
| 0.454cm ² | 8.95cm | 4.01cm ² | 4.0633cm ³ |
| 0.0704in ² | 3.53in | 788,500cmil | 0.2485in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------|----------|---------|--------------|--------|
| No. | Dia(cm) | Turn | Rdc, Ω | No. | Dia(cm) | Turn | Rdc, Ω |
| 12 | 0.213 | 27 | 0.00533 | 21 | 0.0785 | 77 | 0.105 |
| 13 | 0.190 | 30 | 0.00740 | 22 | 0.0701 | 87 | 0.148 |
| 14 | 0.171 | 34 | 0.0102 | 23 | 0.0632 | 96 | 0.206 |
| 15 | 0.153 | 38 | 0.0143 | 24 | 0.0566 | 108 | 0.288 |
| 16 | 0.137 | 43 | 0.0199 | 25 | 0.0505 | 121 | 0.404 |
| 17 | 0.122 | 49 | 0.0277 | 26 | 0.0452 | 135 | 0.569 |
| 18 | 0.109 | 55 | 0.0388 | 27 | 0.0409 | 150 | 0.789 |
| 19 | 0.0980 | 61 | 0.0541 | 28 | 0.0366 | 168 | 1.11 |
| 20 | 0.0879 | 69 | 0.0754 | 29 | 0.0330 | 186 | 1.53 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60μ, 125μ)




OD358

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | (mm) | 35.81 | 22.35 | 10.46 |
| | (inch) | 1.410 | 0.0880 | 0.412 |
| After coating | (mm) | 36.70 | 21.50 | 11.28 |
| (Epoxy) | (inch) | 1.445 | 0.848 | 0.444 |

OD 35.81mm / 1.410inches



Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|-----------------------|--------------------|---------------------|-----------------------|
| 0.678cm ² | 8.98cm | 3.64cm ² | 6.0884cm ³ |
| 0.1051in ² | 3.54in | 719,100mil | 0.3721in ³ |

Winding Information


| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|---------|-------------------------|--------------|-----------|
| | Turn | Rdc,Ω | | Turn | Rdc,Ω |
| 12 0.213 | 25 | 0.00579 | 21 | 0.0785 | 74 0.117 |
| 13 0.190 | 29 | 0.00809 | 22 | 0.0701 | 82 0.166 |
| 14 0.171 | 32 | 0.0112 | 23 | 0.0632 | 92 0.229 |
| 15 0.153 | 37 | 0.0157 | 24 | 0.0566 | 103 0.322 |
| 16 0.137 | 41 | 0.0220 | 25 | 0.0505 | 115 0.452 |
| 17 0.122 | 46 | 0.0306 | 26 | 0.0452 | 129 0.637 |
| 18 0.109 | 52 | 0.0429 | 27 | 0.0409 | 143 0.885 |
| 19 0.0980 | 58 | 0.0600 | 28 | 0.0366 | 160 1.25 |
| 20 0.0879 | 65 | 0.0837 | 29 | 0.0330 | 177 1.71 |

Single layer winding with 1 inch leads

Available Cores


| Part No. | Part No. | | | | A _L | Perm. |
|----------|----------|-----------|----------|------------|----------------------|-------|
| | MPP | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM358026 | CH358026 | CS358026 | CK358026 | 24 | 26 | |
| CM358060 | CH358060 | CS358060 | CK358060 | 56 | 60 | |
| - | - | CS358075 | CK358075 | 70 | 75 | |
| - | - | CS358090 | CK358090 | 84 | 90 | |
| CM358125 | CH358125 | CS358125 | - | 117 | 125 | |
| CM358147 | CH358147 | - | - | 138 | 147 | |
| CM358160 | CH358160 | - | - | 150 | 160 | |
| CM358173 | - | - | - | 162 | 173 | |
| - | - | - | - | 187 | 200 | |

■ A_L vs NI Curve(60μ, 125μ)



OD400

OD 39.88mm / 1.570inches



Available Cores

| MPP | Part No. | | A _L (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|--|--------------------|
| | High Flux | Sendust | | |
| CM400026 | CH400026 | CS400026 | CK400026 | 35 26 |
| CM400060 | CH400060 | CS400060 | CK400060 | 81 60 |
| - | - | CS400075 | CK400075 | 101 75 |
| - | - | CS400090 | CK400090 | 121 90 |
| CM400125 | CH400125 | CS400125 | - | 168 125 |
| CM400147 | CH400147 | - | - | 198 147 |
| CM400160 | CH400160 | - | - | 215 160 |
| CM400173 | - | - | - | 233 173 |
| - | - | - | - | 269 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|----------------|---------|---------|---------|
| Before coating | [mm] | 39.88 | 24.13 |
| | [inch] | 1.570 | 0.950 |
| After coating | [mm] | 40.70 | 23.30 |
| [Epoxy] | [inch] | 1.602 | 0.918 |
| | | | 0.605 |

Magnetic Dimensions


| Cross Section (A) | Path Length (ℓ) | Window Area (Wa) | Volume (V) |
|-----------------------|---------------------------|---------------------|------------------------|
| 1.072cm ² | 9.84cm | 4.27cm ² | 10.5485cm ³ |
| 0.1662in ² | 3.88in | 842,700cmil | 0.6449in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------------|----------|---------|--------------|---------------|
| No. | Dia(cm) | Turn | Rdc, Ω | No. | Dia(cm) | Turn | Rdc, Ω |
| 10 | 0.213 | 22 | 0.00389 | 19 | 0.0785 | 64 | 0.0804 |
| 11 | 0.190 | 25 | 0.00545 | 20 | 0.0701 | 71 | 0.112 |
| 12 | 0.171 | 28 | 0.00762 | 21 | 0.0632 | 80 | 0.158 |
| 13 | 0.153 | 31 | 0.0107 | 22 | 0.0566 | 90 | 0.223 |
| 14 | 0.137 | 35 | 0.0148 | 23 | 0.0505 | 100 | 0.309 |
| 15 | 0.122 | 40 | 0.0208 | 24 | 0.0452 | 112 | 0.435 |
| 16 | 0.109 | 45 | 0.0292 | 25 | 0.0409 | 125 | 0.611 |
| 17 | 0.0980 | 50 | 0.0408 | 26 | 0.0366 | 140 | 0.862 |
| 18 | 0.0879 | 57 | 0.0574 | 27 | 0.0330 | 155 | 1.20 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD467

OD 46.74mm / 1.840inches

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | (mm) | 46.74 | 24.13 | 18.03 |
| | (inch) | 1.840 | 0.950 | 0.710 |
| After coating | (mm) | 47.60 | 23.30 | 18.92 |
| (Epoxy) | (inch) | 1.875 | 0.918 | 0.745 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|---------------------|-----------------------|
| 1.990cm ² | 10.74cm | 4.27cm ² | 21.373cm ³ |
| 0.308in ² | 4.23in | 842,700cmil | 1.303in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|--------|-------------------------|--------------|-------|
| | Turn | Rdc,Ω | | Turn | Rdc,Ω |
| 10 0.213 | 22 | 0.0488 | 19 0.0785 | 64 | 0.104 |
| 11 0.190 | 25 | 0.0688 | 20 0.0701 | 71 | 0.146 |
| 12 0.171 | 28 | 0.0966 | 21 0.0632 | 80 | 0.205 |
| 13 0.153 | 31 | 0.0136 | 22 0.0566 | 90 | 0.290 |
| 14 0.137 | 35 | 0.0189 | 23 0.0505 | 100 | 0.403 |
| 15 0.122 | 40 | 0.0267 | 24 0.0452 | 112 | 0.567 |
| 16 0.109 | 45 | 0.0375 | 25 0.0409 | 125 | 0.798 |
| 17 0.0980 | 50 | 0.0526 | 26 0.0366 | 140 | 1.13 |
| 18 0.0879 | 57 | 0.0740 | 27 0.0330 | 155 | 1.57 |


Single layer winding with 1 inch leads



Available Cores


| MPP | Part No. | | | AL | Perm. |
|----------|-----------|----------|------------|----------------------|-------|
| | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM467026 | CH467026 | CS467026 | CK467026 | 59 | 26 |
| CM467060 | CH467060 | CS467060 | CK467060 | 135 | 60 |
| - | - | CS467075 | CK467075 | 169 | 75 |
| - | - | CS467090 | CK467090 | 202 | 90 |
| CM467125 | CH467125 | CS467125 | - | 281 | 125 |
| CM467147 | - | - | - | 330 | 147 |
| CM467160 | - | - | - | 360 | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD468

OD 46.74mm / 1.840inches



Available Cores

| MPP | Part No. | | Sendust | Mega Flux® | A _L (nH/N ²) | Perm. (μ) |
|----------|-----------|----------|----------|------------|-------------------------------------|-----------------|
| | High Flux | CK | | | | |
| CM468026 | CH468026 | CS468026 | CK468026 | 37 | 26 | |
| CM468060 | CH468060 | CS468060 | CK468060 | 86 | 60 | |
| - | - | CS468075 | CK468075 | 107 | 75 | |
| - | - | CS468090 | CK468090 | 128 | 90 | |
| CM468125 | CH468125 | CS468125 | - | 178 | 125 | |
| CM468147 | - | - | - | 210 | 147 | |
| CM468160 | - | - | - | 228 | 160 | |
| - | - | - | - | - | 173 | |
| - | - | - | - | - | 200 | |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|----------------|---------|---------|---------|
| Before coating | [mm] | 46.74 | 28.70 |
| | [inch] | 1.840 | 1.130 |
| After coating | [mm] | 47.60 | 27.90 |
| (Epoxy) | [inch] | 1.875 | 1.098 |
| | | | 0.635 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|-----------------|---------------------|-----------------------|
| 1.340cm ² | 11.63cm | 6.11cm ² | 15.584cm ³ |
| 0.208in ² | 4.58in | 1,206,000cmil | 0.9526in ³ |

Winding Information

| AWG Wire No. | Dia(cm) | Single Layer | | AWG Wire No. | Single Layer | | |
|--------------|---------|--------------|---------------|--------------|--------------|---------------|-------|
| | | Turn | Rdc, Ω | | Turn | Rdc, Ω | |
| 10 | 0.267 | 26 | 0.00505 | 19 | 0.0980 | 77 | 0.104 |
| 11 | 0.238 | 30 | 0.00708 | 20 | 0.0879 | 86 | 0.146 |
| 12 | 0.213 | 34 | 0.0099 | 21 | 0.0785 | 96 | 0.205 |
| 13 | 0.190 | 38 | 0.0139 | 22 | 0.0701 | 108 | 0.290 |
| 14 | 0.171 | 43 | 0.0193 | 23 | 0.0632 | 120 | 0.402 |
| 15 | 0.153 | 48 | 0.0270 | 24 | 0.0566 | 134 | 0.565 |
| 16 | 0.137 | 54 | 0.0380 | 25 | 0.0505 | 150 | 0.795 |
| 17 | 0.122 | 61 | 0.0530 | 26 | 0.0452 | 168 | 1.12 |
| 18 | 0.109 | 68 | 0.0745 | 27 | 0.0409 | 186 | 1.56 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD508

OD 50.80mm / 2.000inches

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | (mm) | 50.80 | 31.75 | 13.46 |
| | (inch) | 2.000 | 1.250 | 0.530 |
| After coating | (mm) | 51.70 | 30.90 | 14.35 |
| (Epoxy) | (inch) | 2.035 | 1.218 | 0.565 |

Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|---------------------|-----------------------|
| 1.251cm ² | 12.73cm | 7.50cm ² | 15.929cm ³ |
| 0.194in ² | 5.02in | 1,484,000cmil | 0.9739in ³ |

Winding Information


| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------|----------|---------|--------------|-------|
| No. | Dia(cm) | Turn | Rdc,Ω | No. | Dia(cm) | Turn | Rdc,Ω |
| 10 | 0.267 | 30 | 0.00539 | 19 | 0.0980 | 85 | 0.110 |
| 11 | 0.238 | 33 | 0.00754 | 20 | 0.0879 | 95 | 0.154 |
| 12 | 0.213 | 38 | 0.0105 | 21 | 0.0785 | 107 | 0.216 |
| 13 | 0.190 | 43 | 0.0147 | 22 | 0.0701 | 120 | 0.306 |
| 14 | 0.171 | 48 | 0.0205 | 23 | 0.0632 | 133 | 0.424 |
| 15 | 0.153 | 54 | 0.0287 | 24 | 0.0566 | 149 | 0.596 |
| 16 | 0.137 | 60 | 0.0402 | 25 | 0.0505 | 167 | 0.838 |
| 17 | 0.122 | 68 | 0.0562 | 26 | 0.0452 | 186 | 1.18 |
| 18 | 0.109 | 76 | 0.0788 | 27 | 0.0409 | 207 | 1.64 |

Single layer winding with 1 inch leads

Available Cores


| Part No. | MPP | High Flux | Sendust | Mega Flux® | AL | Perm. |
|----------|----------|-----------|----------|------------|----------------------|-------|
| | | | | | [nH/N ²] | [μ] |
| CM508026 | CH508026 | CS508026 | CK508026 | | 32 | 26 |
| CM508060 | CH508060 | CS508060 | CK508060 | | 73 | 60 |
| - | - | CS508075 | CK508075 | | 91 | 75 |
| - | - | CS508090 | CK508090 | | 109 | 90 |
| CM508125 | CH508125 | CS508125 | - | | 152 | 125 |
| CM508147 | - | - | - | | 179 | 147 |
| CM508160 | - | - | - | | 195 | 160 |
| - | - | - | - | | - | 173 |
| - | - | - | - | | - | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD571

OD 57.15mm / 2.250inches



Available Cores

| MPP | Part No. | | | A_L | Perm. |
|----------|-----------|----------|------------|----------------------|-----------|
| | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM571026 | CH571026 | CS571026 | CK571026 | 60 | 26 |
| CM571060 | CH571060 | CS571060 | CK571060 | 138 | 60 |
| - | - | CS571075 | CK571075 | 172 | 75 |
| - | - | CS571090 | CK571090 | 206 | 90 |
| CM571125 | CH571125 | CS571125 | - | 287 | 125 |
| CM571147 | - | - | - | 306 | 147 |
| CM571160 | - | - | - | 333 | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|--------------------------|----------------|----------------|----------------|
| Before coating | [mm] [inch] | 57.15 2.250 | 26.39 1.039 |
| After coating (Epoxy) | [mm] [inch] | 58.00 2.285 | 25.60 1.007 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|-----------------|---------------------|---------------------|
| 2.29cm ² | 12.5cm | 5.14cm ² | 28.6cm ³ |
| 0.355in ² | 4.93in | 1,014,049cmil | 1.75in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------------|----------|---------|--------------|---------------|
| No. | Dia(cm) | Turn | Rdc, Ω | No. | Dia(cm) | Turn | Rdc, Ω |
| 10 | 0.267 | 26 | 0.00551 | 19 | 0.0980 | 78 | 0.133 |
| 11 | 0.238 | 30 | 0.00801 | 20 | 0.0879 | 88 | 0.189 |
| 12 | 0.213 | 34 | 0.0115 | 21 | 0.0785 | 99 | 0.269 |
| 13 | 0.190 | 39 | 0.0165 | 22 | 0.0701 | 111 | 0.381 |
| 14 | 0.171 | 43 | 0.0230 | 23 | 0.0632 | 124 | 0.534 |
| 15 | 0.153 | 49 | 0.0330 | 24 | 0.0566 | 138 | 0.752 |
| 16 | 0.137 | 55 | 0.0469 | 25 | 0.0505 | 156 | 1.07 |
| 17 | 0.122 | 62 | 0.0664 | 26 | 0.0452 | 174 | 1.51 |
| 18 | 0.109 | 70 | 0.0948 | 27 | 0.0409 | 193 | 2.10 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD572

OD 57.15mm / 2.250inches

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | (mm) | 57.15 | 35.56 | 13.97 |
| | (inch) | 2.250 | 1.400 | 0.550 |
| After coating | (mm) | 58.00 | 34.70 | 14.86 |
| (Epoxy) | (inch) | 2.285 | 1.368 | 0.585 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|---------------------|----------------------|
| 1.444cm ² | 14.30cm | 9.48cm ² | 20.65cm ³ |
| 0.244in ² | 5.63in | 1,871,000cmil | 1.261in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|---------|-------------------------|--------------|--------|
| | Turn | Rdc, Ω | | Turn | Rdc, Ω |
| 10 0.267 | 37 | 0.00644 | 19 0.0980 | 108 | 0.152 |
| 11 0.238 | 42 | 0.00920 | 20 0.0879 | 120 | 0.211 |
| 12 0.213 | 48 | 0.0133 | 21 0.0785 | 135 | 0.300 |
| 13 0.190 | 54 | 0.0188 | 22 0.0701 | 152 | 0.428 |
| 14 0.171 | 60 | 0.0263 | 23 0.0632 | 169 | 0.596 |
| 15 0.153 | 68 | 0.0376 | 24 0.0566 | 189 | 0.845 |
| 16 0.137 | 76 | 0.0531 | 25 0.0505 | 212 | 1.19 |
| 17 0.122 | 85 | 0.0746 | 26 0.0452 | 237 | 1.69 |
| 18 0.109 | 96 | 0.107 | 27 0.0409 | 263 | 2.35 |


Single layer winding with 1 inch leads



Available Cores


| Part No. | AL (nH/N ²) | Perm. (μ) | MPP | | |
|----------|----------------------------|--------------|-----------|---------|------------|
| | | | High Flux | Sendust | Mega Flux® |
| CM572026 | CH572026 | CS572026 | CK572026 | 33 | 26 |
| CM572060 | CH572060 | CS572060 | CK572060 | 75 | 60 |
| - | - | CS572075 | CK572075 | 94 | 75 |
| - | - | CS572090 | CK572090 | 112 | 90 |
| CM572125 | CH572125 | CS572125 | - | 156 | 125 |
| CM572147 | - | - | - | 185 | 147 |
| CM572160 | - | - | - | 200 | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD610

OD 62.0mm / 2.441inches



Available Cores

| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-----------|
| | High Flux | Sendust | Mega Flux® | [nH/N ²] | (μ) |
| CM610026 | CH610026 | CS610026 | CK610026 | 83 | 26 |
| CM610060 | CH610060 | CS610060 | CK610060 | 192 | 60 |
| - | - | CS610075 | CK610075 | 240 | 75 |
| - | - | CS610090 | CK610090 | 288 | 90 |
| CM610125 | CH610125 | CS610125 | - | 400 | 125 |
| - | - | - | - | - | 147 |
| - | - | - | - | - | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|--------------------------|----------------|---------------|----------------|
| Before coating | (mm) [inch] | 62.0 2.441 | 32.6 1.283 |
| After coating (Epoxy) | (mm) [inch] | 63.1 2.484 | 31.37 1.235 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|-----------------|---------------------|----------------------|
| 3.675cm ² | 14.37cm | 7.73cm ² | 52.81cm ³ |
| 0.570in ² | 5.66in | 1,525,610cmil | 3.223in ³ |

Winding Information

| AWG Wire No. | Dia(cm) | Single Layer | | AWG Wire No. | Dia(cm) | Single Layer | |
|--------------|---------|--------------|---------------|--------------|---------|--------------|---------------|
| | | Turn | Rdc, Ω | | | Turn | Rdc, Ω |
| 10 | 0.267 | | | 19 | 0.0980 | | |
| 11 | 0.238 | | | 20 | 0.0879 | | |
| 12 | 0.213 | | | 21 | 0.0785 | | |
| 13 | 0.190 | | | 22 | 0.0701 | | |
| 14 | 0.171 | N · A | | 23 | 0.0632 | N · A | |
| 15 | 0.153 | | | 24 | 0.0566 | | |
| 16 | 0.137 | | | 25 | 0.0505 | | |
| 17 | 0.122 | | | 26 | 0.0452 | | |
| 18 | 0.109 | | | 27 | 0.0409 | | |

Single layer winding with 1 inch leads

■ AL vs NI Curve(60 μ , 125 μ)



OD740

OD 74.1mm / 2.917inches

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 74.1 | 45.3 | 35.0 |
| | [inch] | 2.917 | 1.783 | 1.378 |
| After coating | [mm] | 75.2 | 44.07 | 36.27 |
| (Epoxy) | [inch] | 2.961 | 1.735 | 1.428 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|----------------------|----------------------|
| 5.040cm ² | 18.38cm | 15.25cm ² | 92.64cm ³ |
| 0.781in ² | 7.24in | 3,009, 310cmil | 5.653in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|--------|-------------------------|--------------|--------|
| | Turn | Rdc, Ω | | Turn | Rdc, Ω |
| 10 0.267 | | | 19 | 0.0980 | |
| 11 0.238 | | | 20 | 0.0879 | |
| 12 0.213 | | | 21 | 0.0785 | |
| 13 0.190 | | | 22 | 0.0701 | |
| 14 0.171 | N · A | | 23 | 0.0632 | N · A |
| 15 0.153 | | | 24 | 0.0566 | |
| 16 0.137 | | | 25 | 0.0505 | |
| 17 0.122 | | | 26 | 0.0452 | |
| 18 0.109 | | | 27 | 0.0409 | |

Single layer winding with 1 inch leads




ID 45.3mm
HT 35.0mm

Available Cores


| MPP | Part No. | | | AL | Perm. |
|----------|-----------|----------|------------|----------------------|-------|
| | High Flux | Sendust | Mega Flux® | [nH/N ²] | (μ) |
| CM740026 | CH740026 | CS740026 | CK740026 | 89 | 26 |
| CM740060 | CH740060 | CS740060 | CK740060 | 206 | 60 |
| - | - | CS740075 | CK740075 | 257 | 75 |
| - | - | CS740090 | CK740090 | 309 | 90 |
| CM740125 | CH740125 | CS740125 | - | 429 | 125 |
| - | - | - | - | - | 147 |
| - | - | - | - | - | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD777

OD 77.8mm / 3.063inches



Available Cores

| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-----------|
| | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM777026 | CH777026 | CS777026 | CK777026 | 30 | 26 |
| CM777060 | CH777060 | CS777060 | CK777060 | 68 | 60 |
| - | - | CS777075 | CK777075 | 85 | 75 |
| - | - | CS777090 | CK777090 | 102 | 90 |
| CM777125 | CH777125 | CS777125 | - | 142 | 125 |
| - | - | - | - | - | 147 |
| - | - | - | - | - | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) | |
|--------------------------|----------------|----------------|----------------|----------------|
| Before coating | (mm) [inch] | 77.80 3.063 | 49.23 1.938 | 12.70 0.50 |
| After coating (Epoxy) | (mm) [inch] | 78.90 3.108 | 48.0 1.888 | 13.97 0.550 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|-----------------|----------------------|-----------------------|
| 1.770cm ² | 20.0cm | 17.99cm ² | 34.770cm ³ |
| 0.274in ² | 7.72in | 3,550,000cmil | 2.122in ³ |

Winding Information

| AWG Wire | | Single Layer | | AWG Wire | | Single Layer | |
|----------|---------|--------------|---------------|----------|---------|--------------|---------------|
| No. | Dia(cm) | Turn | Rdc, Ω | No. | Dia(cm) | Turn | Rdc, Ω |
| 10 | 0.267 | 53 | 0.0113 | 19 | 0.0980 | 150 | 0.258 |
| 11 | 0.238 | 60 | 0.0162 | 20 | 0.0879 | 168 | 0.364 |
| 12 | 0.213 | 67 | 0.0228 | 21 | 0.0785 | 188 | 0.514 |
| 13 | 0.190 | 76 | 0.0325 | 22 | 0.0701 | 211 | 0.732 |
| 14 | 0.171 | 84 | 0.0454 | 23 | 0.0632 | 235 | 1.02 |
| 15 | 0.153 | 95 | 0.0646 | 24 | 0.0566 | 263 | 1.30 |
| 16 | 0.137 | 106 | 0.0912 | 25 | 0.0505 | 295 | 1.84 |
| 17 | 0.122 | 119 | 0.129 | 26 | 0.0452 | 330 | 2.61 |
| 18 | 0.109 | 134 | 0.183 | 27 | 0.0409 | 365 | 3.62 |

Single layer winding with 1 inch leads

■ A_L vs NI Curve(60 μ , 125 μ)



OD778

OD 77.8mm / 3.063inches

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 77.80 | 49.23 | 15.9 |
| | [inch] | 3.063 | 1.938 | 0.626 |
| After coating | [mm] | 78.90 | 48.0 | 17.2 |
| (Epoxy) | [inch] | 3.108 | 1.888 | 0.677 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|----------------------|-----------------------|
| 2.270cm ² | 20.0cm | 17.99cm ² | 43.531cm ³ |
| 0.352in ² | 7.72in | 3,550,000cmil | 2.656in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer | | AWG Wire No. Dia(cm) | Single Layer | |
|-------------------------|--------------|-------|-------------------------|--------------|-------|
| | Turn | Rdc,Ω | | Turn | Rdc,Ω |
| 10 0.267 | | | 19 0.0980 | | |
| 11 0.238 | | | 20 0.0879 | | |
| 12 0.213 | | | 21 0.0785 | | |
| 13 0.190 | | | 22 0.0701 | | |
| 14 0.171 | N · A | | 23 0.0632 | N · A | |
| 15 0.153 | | | 24 0.0566 | | |
| 16 0.137 | | | 25 0.0505 | | |
| 17 0.122 | | | 26 0.0452 | | |
| 18 0.109 | | | 27 0.0409 | | |


Single layer winding with 1 inch leads



Available Cores


| MPP | Part No. | | | AL | Perm. |
|----------|-----------|----------|------------|----------------------|-------|
| | High Flux | Sendust | Mega Flux® | [nH/N ²] | (μ) |
| CM778026 | CH778026 | CS778026 | CK778026 | 37 | 26 |
| CM778060 | CH778060 | CS778060 | CK778060 | 85 | 60 |
| - | - | CS778075 | CK778075 | 107 | 75 |
| - | - | CS778090 | CK778090 | 128 | 90 |
| CM778125 | CH778125 | CS778125 | - | 178 | 125 |
| - | - | - | - | - | 147 |
| - | - | - | - | - | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD888

OD 88.9mm / 3.500inches



Available Cores

| MPP | Part No. | | | A _L | Perm. |
|----------|-----------|----------|------------|----------------------|-------|
| | High Flux | Sendust | Mega Flux® | (nH/N ²) | (μ) |
| CM888026 | CH888026 | CS888026 | CK888026 | 24 | 26 |
| CM888060 | CH888060 | CS888060 | CK888060 | 57 | 60 |
| - | - | CS888075 | CK888075 | 71 | 75 |
| - | - | CS888090 | CK888090 | 85 | 90 |
| CM888125 | CH888125 | CS888125 | - | 119 | 125 |
| - | - | - | - | - | 147 |
| - | - | - | - | - | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

Core Dimensions

| | OD(max) | ID(min) | HT(max) | |
|--------------------------|----------------|----------------|----------------|----------------|
| Before coating | (mm) [inch] | 88.90 3.500 | 66.00 2.598 | 15.90 0.626 |
| After coating (Epoxy) | (mm) [inch] | 90.03 3.544 | 64.74 2.549 | 17.20 0.677 |

Magnetic Dimensions


| Cross Section (A) | Path Length (ℓ) | Window Area (Wa) | Volume (V) |
|---|-------------------|--------------------------------------|---|
| 1.83cm ² 0.284in ² | 24.10cm 9.46in | 32.92cm ² 6,00,140cmil | 44.103cm ³ 2.691in ³ |

Winding Information

| AWG Wire No. | Dia(cm) | Single Layer | | AWG Wire No. | Dia(cm) | Single Layer | |
|--------------|---------|--------------|--------|--------------|---------|--------------|--------|
| | | Turn | Rdc, Ω | | | Turn | Rdc, Ω |
| 10 | 0.267 | | | 19 | 0.0980 | | |
| 11 | 0.238 | | | 20 | 0.0879 | | |
| 12 | 0.213 | | | 21 | 0.0785 | | |
| 13 | 0.190 | | | 22 | 0.0701 | | |
| 14 | 0.171 | N · A | | 23 | 0.0632 | N · A | |
| 15 | 0.153 | | | 24 | 0.0566 | | |
| 16 | 0.137 | | | 25 | 0.0505 | | |
| 17 | 0.122 | | | 26 | 0.0452 | | |
| 18 | 0.109 | | | 27 | 0.0409 | | |

Single layer winding with 1 inch leads

■ AL vs NI Curve(60μ, 125μ)



OD1016

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 101.6 | 57.2 | 16.5 |
| | [inch] | 3.980 | 2.252 | 0.650 |

| | | OD(max) | ID(min) | HT(max) |
|---------------|--------|---------|---------|---------|
| After coating | [mm] | 103.1 | 55.7 | 17.8 |
| (Epoxy) | [inch] | 4.059 | 2.193 | 0.701 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|----------------------|-----------------------|
| 3.522cm ² | 24.27cm | 24.36cm ² | 85.495cm ³ |
| 0.546in ² | 9.56in | 4,807,425cmil | 5.217in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer Turn Rdc, Ω | AWG Wire No. Dia(cm) | Single Layer Turn Rdc, Ω |
|-------------------------|-----------------------------|-------------------------|-----------------------------|
| 10 0.267 | | 19 0.0980 | |
| 11 0.238 | | 20 0.0879 | |
| 12 0.213 | | 21 0.0785 | |
| 13 0.190 | | 22 0.0701 | |
| 14 0.171 | N · A | 23 0.0632 | N · A |
| 15 0.153 | | 24 0.0566 | |
| 16 0.137 | | 25 0.0505 | |
| 17 0.122 | | 26 0.0452 | |
| 18 0.109 | | 27 0.0409 | |

Single layer winding with 1 inch leads

OD 101.6mm / 3.980inches




ID 57.2mm
HT 16.5mm

Available Cores


| MPP | Part No. | | | AL [nH/N ²] | Perm. (μ) |
|-----------|-----------|-----------|------------|----------------------------|--------------|
| | High Flux | Sendust | Mega Flux® | | |
| CM1016026 | CH1016026 | CS1016026 | CK1016026 | 48 | 26 |
| CM1016060 | CH1016060 | CS1016060 | CK1016060 | 112 | 60 |
| CM1016125 | CH1016125 | CS1016125 | - | 228 | 125 |
| - | - | - | - | - | 147 |
| - | - | - | - | - | 160 |
| - | - | - | - | - | 173 |
| - | - | - | - | - | 200 |

■ AL vs NI Curve(60μ, 125μ)



OD1325

OD 132.5mm / 5.217inches



Available Cores

| MPP | Part No. | | Mega Flux® | AL (nH/N ²) | Perm. (μ) |
|-----------|-----------|-----------|------------|----------------------------|--------------------|
| | High Flux | Sendust | | | |
| CM1325026 | CH1325026 | CS1325026 | CK1325026 | 68 | 26 |
| CM1325060 | CH1325060 | CS1325060 | CK1325060 | 156 | 60 |
| CM1325125 | CH1325125 | CS1325125 | - | 325 | 125 |
| - | - | - | - | 147 | |
| - | - | - | - | 160 | |
| - | - | - | - | 173 | |
| - | - | - | - | 200 | |

Core Dimensions

| | OD(max) | ID(min) | HT(max) |
|--------------------------|----------------|----------------|---------------|
| Before coating | [mm] [inch] | 132.5 5.217 | 78.6 3.094 |
| After coating (Epoxy) | [mm] [inch] | 134.2 5.283 | 77.0 3.032 |

Magnetic Dimensions


| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|---|--------------------|---------------------------------------|---|
| 6.71cm ² 1.040in ² | 32.42cm 12.77in | 46.61cm ² 9,199,089cmil | 217.58cm ³ 13.28in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer Turn Rdc, Ω | AWG Wire No. Dia(cm) | Single Layer Turn Rdc, Ω |
|-------------------------|------------------------------------|-------------------------|------------------------------------|
| | | | N • A |
| 10 | 0.267 | 19 | 0.0980 |
| 11 | 0.238 | 20 | 0.0879 |
| 12 | 0.213 | 21 | 0.0785 |
| 13 | 0.190 | 22 | 0.0701 |
| 14 | 0.171 | 23 | 0.0632 |
| 15 | 0.153 | 24 | 0.0566 |
| 16 | 0.137 | 25 | 0.0505 |
| 17 | 0.122 | 26 | 0.0452 |
| 18 | 0.109 | 27 | 0.0409 |

Single layer winding with 1 inch leads

■ AL vs NI Curve(60 μ , 125 μ)



OD1625

OD 165.0mm / 6.496inches

Core Dimensions

| | | OD(max) | ID(min) | HT(max) |
|----------------|--------|---------|---------|---------|
| Before coating | [mm] | 165.0 | 88.9 | 25.4 |
| | [inch] | 6.496 | 3.500 | 1.000 |
| After coating | [mm] | 167.2 | 86.9 | 27.3 |
| (Epoxy) | [inch] | 6.583 | 3.421 | 1.075 |


Magnetic Dimensions

| Cross Section (A) | Path Length (l) | Window Area (Wa) | Volume (V) |
|----------------------|--------------------|----------------------|-----------------------|
| 9.46cm ² | 38.65cm | 59.31cm ² | 365.63cm ³ |
| 1.466in ² | 15.22in | 11,704,978cmil | 22.31in ³ |

Winding Information

| AWG Wire No. Dia(cm) | Single Layer Turn Rdc,Ω | AWG Wire No. Dia(cm) | Single Layer Turn Rdc,Ω |
|-------------------------|----------------------------|-------------------------|----------------------------|
| 10 0.267 | | 19 0.0980 | |
| 11 0.238 | | 20 0.0879 | |
| 12 0.213 | | 21 0.0785 | |
| 13 0.190 | | 22 0.0701 | |
| 14 0.171 | N · A | 23 0.0632 | N · A |
| 15 0.153 | | 24 0.0566 | |
| 16 0.137 | | 25 0.0505 | |
| 17 0.122 | | 26 0.0452 | |
| 18 0.109 | | 27 0.0409 | |


Single layer winding with 1 inch leads



Available Cores

| Part No. | MPP | High Flux | Sendust | Mega Flux® | AL | Perm. |
|-----------|-----------|-----------|-----------|------------|----------------------|-------|
| | | | | | [nH/N ²] | (μ) |
| CM1625026 | CH1625026 | CS1625026 | CK1625026 | 80 | 26 | |
| CM1625060 | CH1625060 | CS1625060 | CK1625060 | 184 | 60 | |
| CM1625125 | CH1625125 | CS1625125 | - | 384 | 125 | |
| - | - | - | - | - | - | 147 |
| - | - | - | - | - | - | 160 |
| - | - | - | - | - | - | 173 |
| - | - | - | - | - | - | 200 |

■ AL vs NI Curve(60μ, 125μ)





SPECIAL MAGNETIC POWDER CORES

BLOCK CORES




Features


- Large energy storage capacity
- No magnetic flux leakage
- Good temperature stability
- Low core loss at high frequency

Applications

- High inductance choke coils
- Flyback transformers
- Multiple circuit choke coils
- Output chokes for SMPS



■ Product Identification




| Part No. | Dimensions (mm) | | | Cross Section Area(cm ²) |
|----------------|---------------------|--------------------|---------------------|--------------------------------------|
| | A Length (mm) | B Width (mm) | C Height (mm) | |
| BK5315 | 50.5±0.5 | 30.3±0.3 | 15±0.2 | 4.5 |
| BK5320 | 50.5±0.5 | 30.3±0.3 | 20±0.2 | 6 |
| BK6315 | 60.5±0.5 | 30.3±0.3 | 15±0.2 | 4.5 |
| BK6320 | 60.5±0.5 | 30.3±0.3 | 20±0.2 | 6 |
| BK7315 | 70.5±0.5 | 30.3±0.3 | 15±0.2 | 4.5 |
| BK7320 | 70.5±0.5 | 30.3±0.3 | 20±0.2 | 6 |
| BK8315 | 80.5±0.5 | 30.3±0.3 | 15±0.2 | 4.5 |
| BK8320 | 80.5±0.5 | 30.3±0.3 | 20±0.2 | 6 |
| BK9315 | 90.5±0.5 | 30.3±0.3 | 15±0.2 | 4.5 |
| BK9320 | 90.5±0.5 | 30.3±0.3 | 20±0.2 | 6 |
| BK5020A | 50.5±0.5 | 20.3±0.3 | 20±0.2 | 4 |
| BK6020A | 60.5±0.5 | 20.3±0.3 | 20±0.2 | 4 |
| BK6020B | 60.5±0.5 | 20.3±0.3 | 25±0.2 | 5 |
| BK7020A | 70.5±0.5 | 20.3±0.3 | 20±0.2 | 4 |
| BK7020B | 70.5±0.5 | 20.3±0.3 | 25±0.2 | 5 |
| BK8020A | 80.5±0.5 | 20.3±0.3 | 20±0.2 | 4 |
| BK8020B | 80.5±0.5 | 20.3±0.3 | 25±0.2 | 5 |

* BS(Sendust Block Core), BH(High Flux Core) and customized designs are also available.

■ BLOCK CORES ASSEMBLY



■ Permeability vs DC Bias Curves



| Part No. | Dimensions (mm) | | | Path Length [cm] | Cross Section Area [cm²] | 4PCS AL value (nH/N²) ± 12% | | |
|----------------|-----------------|--------------|---------------|------------------|--------------------------|-----------------------------|------|------|
| | A Length (mm) | B Width (mm) | C Height (mm) | | | 026μ | 040μ | 060μ |
| BK5315 | 50.5±0.5 | 30.3±0.3 | 15±0.2 | 18.71 | 4.5 | 95 | 121 | 181 |
| BK5320 | 50.5±0.5 | 30.3±0.3 | 20±0.2 | 18.28 | 6 | 130 | 165 | 247 |
| BK6315 | 60.5±0.5 | 30.3±0.3 | 15±0.2 | 22.71 | 4.5 | 79 | 100 | 149 |
| BK6320 | 60.5±0.5 | 30.3±0.3 | 20±0.2 | 22.28 | 6 | 107 | 135 | 203 |
| BK7315 | 70.5±0.5 | 30.3±0.3 | 15±0.2 | 26.71 | 4.5 | 67 | 85 | 127 |
| BK7320 | 70.5±0.5 | 30.3±0.3 | 20±0.2 | 26.28 | 6 | 91 | 115 | 172 |
| BK8315 | 80.5±0.5 | 30.3±0.3 | 15±0.2 | 30.71 | 4.5 | 58 | 74 | 110 |
| BK8320 | 80.5±0.5 | 30.3±0.3 | 20±0.2 | 30.28 | 6 | 78 | 100 | 149 |
| BK9315 | 90.5±0.5 | 30.3±0.3 | 15±0.2 | 34.71 | 4.5 | 51 | 65 | 98 |
| BK9320 | 90.5±0.5 | 30.3±0.3 | 20±0.2 | 34.28 | 6 | 68 | 88 | 132 |
| BK5020A | 50.5±0.5 | 20.3±0.3 | 20±0.2 | 18.28 | 4 | 87 | 110 | 165 |
| BK6020A | 60.5±0.5 | 20.3±0.3 | 20±0.2 | 22.28 | 4 | 74 | 90 | 135 |
| BK6020B | 60.5±0.5 | 20.3±0.3 | 25±0.2 | 21.85 | 5 | 91 | 115 | 173 |
| BK7020A | 70.5±0.5 | 20.3±0.3 | 20±0.2 | 26.28 | 4 | 60 | 77 | 115 |
| BK7020B | 70.5±0.5 | 20.3±0.3 | 25±0.2 | 25.85 | 5 | 77 | 97 | 146 |
| BK8020A | 80.5±0.5 | 20.3±0.3 | 20±0.2 | 30.28 | 4 | 52 | 66 | 100 |
| BK8020B | 80.5±0.5 | 20.3±0.3 | 25±0.2 | 29.85 | 5 | 66 | 84 | 126 |

※ BS(Sendust Block Core), BH(High Flux Core), KH(KH Core), KS(KS Core) and customized designs are also available.

ELLIPSE CORES



Features

- Shorter wire length than rectangular posts
- Good DC Bias characteristics
- Larger energy storage capacity
- Low core loss at high frequency


Applications

- Choke filters for solar cell inverters
- Boost inductors for solar cell inverters




Product Identification

• Post



• Plate



LK 35 15 A - 060

Permeability : 60 μ Available perm. : 26, 40, 60 μ

Height(A) : 20mm Available size : A=20mm B=25mm

Width : 15mm Available size : 15mm

Length : 35mm Available size : 35mm

Ellipse Core LK : Mega Flux

LK 70 35 A - 060

Permeability : 60 μ Available Perm : 26, 40, 60 μ

Height : 13.5mm Available Size : A=13.5mm B=18.5mm

Width : 35mm Available Size : 35mm

Length : 70mm Available Size : 50 ~ 80 mm

Ellipse Core LK : Mega Flux

Plate Ellipse Cores

Post Ellipse Cores

| Part No. | Dimensions | | | |
|----------|---------------|--------------|----------------|---------------|
| | A Length (mm) | B Width (mm) | RC Radius (mm) | D Height (mm) |
| LK3515A | 35.3±0.3 | 15.2±0.2 | 7.5±0.2 | 20.0±0.2 |
| LK3515B | 35.3±0.3 | 15.2±0.2 | 7.5±0.2 | 25.0±0.2 |
| LK3520A | 35.3±0.3 | 20.2±0.2 | 7.5±0.2 | 20.0±0.2 |
| LK3520B | 35.3±0.3 | 20.2±0.2 | 7.5±0.2 | 25.0±0.2 |


| Part No. | Dimensions | | | |
|----------|---------------|--------------|----------------|---------------|
| | A Length (mm) | B Width (mm) | RC Radius (mm) | D Height (mm) |
| LK5035A | 50.5±0.5 | 35.3±0.3 | 7.5±0.2 | 13.5±0.2 |
| LK5035B | 50.5±0.5 | 35.3±0.3 | 7.5±0.2 | 18.5±0.2 |
| LK6035A | 60.5±0.5 | 35.3±0.3 | 7.5±0.2 | 13.5±0.2 |
| LK6035B | 60.5±0.5 | 35.3±0.3 | 7.5±0.2 | 18.5±0.2 |
| LK7035A | 70.5±0.5 | 35.3±0.3 | 7.5±0.2 | 13.5±0.2 |
| LK7035B | 70.5±0.5 | 35.3±0.3 | 7.5±0.2 | 18.5±0.2 |
| LK8035A | 80.5±0.5 | 35.3±0.3 | 7.5±0.2 | 13.5±0.2 |
| LK8035B | 80.5±0.5 | 35.3±0.3 | 7.5±0.2 | 18.5±0.2 |

* LS(Sendust Ellipse Core), LH(High Flux Ellipse Core) and customized designs are also available.

■ ELLIPSE CORES ASSEMBLY



■ Permeability vs DC Bias Curves



| PLATE Part No. | POST Dimensions | | | | | | Path Length (cm) | Cross Section Area(cm ²) | Window Area (cm ²) | AL value [nH/N ²] ± 12% | | | |
|-------------------|--------------------|----------------|---------------------|--------------------|---------------------|------------------------------|------------------------------|--|--------------------------------------|-------------------------------------|------|------|-----|
| | Part No. | 1 LEG STACK | A Length (mm) | B Width (mm) | C Height (mm) | D Inner Height (mm) | E Inner Length (mm) | | | 026µ | 040µ | 060µ | |
| LK5035A | LK3515A | 2 | 50.5±0.5 | 35.3±0.3 | 67.0±0.5 | 40.0±0.4 | 20.0±0.4 | 16.47 | 4.77 | 8 | 113 | 146 | 218 |
| | LK3515B | 2 | 50.5±0.5 | 35.3±0.3 | 77.0±0.5 | 50.0±0.4 | 20.0±0.4 | 18.47 | 4.77 | 10 | 101 | 130 | 195 |
| | LK3515A | 3 | 50.5±0.5 | 35.3±0.3 | 87.0±0.5 | 60.0±0.4 | 20.0±0.4 | 20.74 | 4.77 | 12 | 91 | 117 | 176 |
| LK5035B | LK3520A | 2 | 50.5±0.5 | 35.3±0.3 | 77.0±0.5 | 40.0±0.4 | 10.0±0.4 | 16.04 | 6.52 | 4 | 158 | 204 | 306 |
| | LK3520B | 2 | 50.5±0.5 | 35.3±0.3 | 87.0±0.5 | 50.0±0.4 | 10.0±0.4 | 18.04 | 6.52 | 5 | 141 | 182 | 273 |
| | LK3520A | 3 | 50.5±0.5 | 35.3±0.3 | 97.0±0.5 | 60.0±0.4 | 10.0±0.4 | 20.04 | 6.52 | 6 | 127 | 164 | 245 |
| LK6035A | LK3515A | 2 | 60.5±0.5 | 35.3±0.3 | 67.0±0.5 | 40.0±0.4 | 30.0±0.4 | 18.47 | 4.77 | 12 | 101 | 130 | 195 |
| | LK3515B | 2 | 60.5±0.5 | 35.3±0.3 | 77.0±0.5 | 50.0±0.4 | 30.0±0.4 | 20.47 | 4.77 | 15 | 91 | 117 | 176 |
| | LK3515A | 3 | 60.5±0.5 | 35.3±0.3 | 87.0±0.5 | 60.0±0.4 | 30.0±0.4 | 22.47 | 4.77 | 18 | 83 | 107 | 160 |
| LK6035B | LK3520A | 2 | 60.5±0.5 | 35.3±0.3 | 77.0±0.5 | 40.0±0.4 | 20.0±0.4 | 18.04 | 6.52 | 8 | 141 | 182 | 273 |
| | LK3520B | 2 | 60.5±0.5 | 35.3±0.3 | 87.0±0.5 | 50.0±0.4 | 20.0±0.4 | 20.04 | 6.52 | 10 | 127 | 164 | 245 |
| | LK3520A | 3 | 60.5±0.5 | 35.3±0.3 | 97.0±0.5 | 60.0±0.4 | 20.0±0.4 | 22.04 | 6.52 | 12 | 115 | 149 | 223 |
| LK7035A | LK3515A | 2 | 70.5±0.5 | 35.3±0.3 | 67.0±0.5 | 40.0±0.4 | 40.0±0.4 | 20.47 | 4.77 | 16 | 91 | 117 | 176 |
| | LK3515B | 2 | 70.5±0.5 | 35.3±0.3 | 77.0±0.5 | 50.0±0.4 | 40.0±0.4 | 22.47 | 4.77 | 20 | 83 | 107 | 160 |
| | LK3515A | 3 | 70.5±0.5 | 35.3±0.3 | 87.0±0.5 | 60.0±0.4 | 40.0±0.4 | 24.47 | 4.77 | 24 | 76 | 98 | 147 |
| LK7035B | LK3520A | 2 | 70.5±0.5 | 35.3±0.3 | 77.0±0.5 | 40.0±0.4 | 30.0±0.4 | 20.04 | 6.52 | 12 | 127 | 164 | 245 |
| | LK3520B | 2 | 70.5±0.5 | 35.3±0.3 | 87.0±0.5 | 50.0±0.4 | 30.0±0.4 | 22.04 | 6.52 | 15 | 115 | 149 | 223 |
| | LK3520A | 3 | 70.5±0.5 | 35.3±0.3 | 97.0±0.5 | 60.0±0.4 | 30.0±0.4 | 24.04 | 6.52 | 18 | 106 | 136 | 204 |
| LK8035A | LK3515A | 2 | 80.5±0.5 | 35.3±0.3 | 67.0±0.5 | 40.0±0.4 | 50.0±0.4 | 22.47 | 4.77 | 16 | 83 | 107 | 160 |
| | LK3515B | 2 | 80.5±0.5 | 35.3±0.3 | 77.0±0.5 | 50.0±0.4 | 50.0±0.4 | 24.47 | 4.77 | 20 | 76 | 98 | 147 |
| | LK3515A | 3 | 80.5±0.5 | 35.3±0.3 | 87.0±0.5 | 60.0±0.4 | 50.0±0.4 | 26.47 | 4.77 | 24 | 70 | 91 | 136 |
| LK8035B | LK3520A | 2 | 80.5±0.5 | 35.3±0.3 | 77.0±0.5 | 40.0±0.4 | 40.0±0.4 | 22.04 | 6.52 | 12 | 115 | 149 | 223 |
| | LK3520B | 2 | 80.5±0.5 | 35.3±0.3 | 87.0±0.5 | 50.0±0.4 | 40.0±0.4 | 24.04 | 6.52 | 15 | 106 | 136 | 204 |
| | LK3520A | 3 | 80.5±0.5 | 35.3±0.3 | 97.0±0.5 | 60.0±0.4 | 40.0±0.4 | 26.04 | 6.52 | 18 | 98 | 126 | 189 |

CYLINDER+ROUNDBLOCK CORES



Features


- Large energy storage capacity
- Low core loss at high frequency

Applications

- Power inductors for large currents
- Buck/Boost inductors for inverters



■ Product Identification


CK 30 30 - 060
Permeability : 60 μ Available perm. A:26 μ , B:40 μ , C:60 μ

HT : 30mm


OD : 30mm

Available size : 20mm ~ 68mm

Mega Flux® Cylinder Core

CS : Sendust, CH : High Flux

• Plate


RBK 74 28 A - 060
Permeability : 60 μ Available perm : 26, 40, 60 μ

Height(A) : 21.7mm

Width : 27.5mm

Available size : 20mm ~ 30mm

Length : 74.5mm

Available size : 54.5mm ~ 80.5mm

RB : Round Block

K : Mega Flux

| Plate Part No. | Cylinder Dimensions | | | | | | Path Length (cm) | Cross Section Area (cm²) | Window Area (cm²) | AL value (nH/N²) ± 12% | | | |
|----------------|---------------------|-------------|---------------|--------------|---------------|---------------------|---------------------|--------------------------|-------------------|------------------------|-----------|-----------|-----|
| | Part No. | 1 LEG STACK | A Length (mm) | B Width (mm) | C Height (mm) | D Inner Height (mm) | E Inner Length (mm) | | | 026 μ | 040 μ | 060 μ | |
| RBK5420A | CK2020 | 1 | 54 | 20 | 51.4 | 20 | 14 | 12.41 | 3.14 | 2.8 | 99 | 127 | 191 |
| | | 2 | 54 | 20 | 71.4 | 40 | 14 | 16.41 | 3.14 | 5.6 | 75 | 96 | 144 |
| | | 3 | 54 | 20 | 91.4 | 60 | 14 | 20.41 | 3.14 | 8.4 | 60 | 77 | 116 |
| RBK6424A | CK2424 | 1 | 64 | 24 | 61.6 | 24 | 16 | 14.72 | 4.52 | 3.84 | 120 | 154 | 232 |
| | | 2 | 64 | 24 | 85.6 | 48 | 16 | 19.52 | 4.52 | 7.68 | 90 | 116 | 175 |
| | | 3 | 64 | 24 | 109.6 | 72 | 16 | 24.32 | 4.52 | 11.52 | 72 | 93 | 140 |
| RBK6725A | CK2525 | 1 | 67 | 25 | 64.2 | 25 | 17 | 15.41 | 4.91 | 4.25 | 124 | 160 | 240 |
| | | 2 | 67 | 25 | 89.2 | 50 | 17 | 20.41 | 4.91 | 8.5 | 94 | 121 | 181 |
| | | 3 | 67 | 25 | 114.2 | 75 | 17 | 25.41 | 4.91 | 12.75 | 75 | 97 | 146 |
| RBK7428A | CK2828 | 1 | 74 | 27.5 | 71.4 | 28 | 19 | 17.13 | 6.00 | 5.32 | 136 | 176 | 264 |
| | | 2 | 74 | 27.5 | 99.4 | 56 | 19 | 22.73 | 6.00 | 10.64 | 103 | 133 | 199 |
| | | 3 | 74 | 27.5 | 127.4 | 84 | 19 | 28.33 | 6.00 | 15.96 | 83 | 106 | 160 |
| RBK8030A | CK3030 | 1 | 80 | 30 | 77 | 30 | 20 | 18.4 | 7.07 | 6 | 150 | 193 | 290 |
| | | 2 | 80 | 30 | 107 | 60 | 20 | 24.4 | 7.07 | 12 | 113 | 146 | 218 |
| | | 3 | 80 | 30 | 137 | 90 | 20 | 30.4 | 7.07 | 18 | 91 | 117 | 175 |

CYLINDER CORES



Features


- Large energy storage capacity
- Low core loss at high frequency

Applications

- Power inductors for large currents
- Buck/Boost inductors for inverters



■ DC Bias Characteristics



| Part No. | Dimensions | | Cross Section Area (cm ²) |
|----------|------------|-------------|---------------------------------------|
| | OD (mm) | HT (mm) | |
| CK2020 | 20.2 ± 0.2 | 20.0 ± 0.2 | 3.14 |
| CK2424 | 24.0 ± 0.2 | 24.0 ± 0.2 | 4.50 |
| CK2525 | 25.0 ± 0.2 | 25.0 ± 0.2 | 4.91 |
| CK2825 | 27.6 ± 0.3 | 25.0 ± 0.2 | 6.00 |
| CK2830 | 27.6 ± 0.3 | 30.0 ± 0.2 | 6.00 |
| CK3026 | 30.0 ± 0.5 | 26.0 ± 0.2 | 7.07 |
| CK3030 | 30.0 ± 0.5 | 30.0 ± 0.2 | 7.07 |
| CK3035 | 30.0 ± 0.5 | 34.7 ± 0.2 | 7.07 |
| CK3530 | 35.0 ± 0.5 | 30.0 ± 0.2 | 9.62 |
| CK3735 | 37.0 ± 0.5 | 35.25 ± 0.2 | 10.75 |
| CK4030 | 40.0 ± 0.6 | 30.0 ± 0.3 | 12.56 |
| CK4230 | 42.0 ± 0.6 | 30.0 ± 0.3 | 13.85 |
| CK4630 | 46.0 ± 0.6 | 30.0 ± 0.3 | 16.61 |
| CK5030 | 50.0 ± 0.7 | 30.0 ± 0.4 | 19.63 |
| CK5530 | 55.0 ± 0.7 | 30.0 ± 0.4 | 23.76 |
| CK6030 | 60.0 ± 0.8 | 30.0 ± 0.5 | 28.27 |
| CK6330 | 63.0 ± 0.8 | 30.0 ± 0.5 | 31.17 |
| CK6830 | 68.0 ± 0.8 | 30.0 ± 0.5 | 36.31 |

EE CORES



Features


- Large energy storage capacity
- No magnetic flux leakage
- Good temperature stability
- Low core loss at high frequency

Applications

- High inductance choke coils
- Flyback transformers
- Multiple circuit choke coils
- Output chokes for SMPS



■ Product Identification



ES 43 21 A - 060

Permeability : 60 μ Available perm. 26, 40, 60, 90 μ

Height of E core

Width : 21mm Available size : 8.0mm ~ 38.1mm

Length : 43mm Available size : 19.0mm ~ 80.0mm

Sendust E core EK : Mega Flux®

| Part No. | Dimensions (mm) | | | | | | | | Path Length (cm) | Cross Section Area (cm²) | AL value (nH/N²) ±12% | | | |
|----------|-----------------|------|------|---------|---------|------|--------|---------|------------------|--------------------------|-----------------------|-----------|-----------|-----------|
| | A | B | C | D(min.) | E(min.) | F | L(nom) | M(min.) | | | 026 μ | 040 μ | 060 μ | 090 μ |
| ES 1908A | 19.3 | 8.1 | 4.8 | 5.5 | 13.9 | 4.8 | 2.3 | 4.7 | 4.01 | 0.228 | 26 | 35 | 48 | 69 |
| ES 2510A | 25.1 | 9.6 | 6.5 | 6.2 | 18.8 | 6.1 | 3.0 | 6.3 | 4.85 | 0.385 | 39 | 52 | 70 | 100 |
| ES 3015A | 30.1 | 15.0 | 7.1 | 9.7 | 19.5 | 7.0 | 5.1 | 6.4 | 6.56 | 0.601 | 33 | 46 | 71 | 92 |
| ES 3515A | 34.5 | 14.1 | 9.3 | 9.6 | 25.3 | 9.3 | 4.4 | 7.9 | 6.94 | 0.840 | 56 | 75 | 102 | 146 |
| ES 4117A | 40.9 | 16.5 | 12.5 | 10.4 | 28.3 | 12.5 | 6.0 | 7.9 | 7.75 | 1.520 | 88 | 119 | 163 | 234 |
| ES 4321A | 42.8 | 21.1 | 10.8 | 15.0 | 30.4 | 11.7 | 5.9 | 9.5 | 9.84 | 1.280 | 56 | 76 | 105 | 151 |
| ES 4321B | 42.8 | 21.1 | 15.4 | 15.0 | 30.4 | 11.7 | 5.9 | 9.5 | 9.84 | 1.830 | 80 | 108 | 150 | 217 |
| ES 4321C | 42.8 | 21.1 | 20.0 | 15.0 | 30.4 | 11.7 | 5.9 | 9.5 | 9.84 | 2.370 | 104 | 140 | 194 | 281 |
| ES 5528A | 54.9 | 27.6 | 20.6 | 18.5 | 37.5 | 16.8 | 8.4 | 10.3 | 12.30 | 3.500 | 116 | 157 | 219 | |
| ES 5528B | 54.9 | 27.6 | 24.6 | 18.5 | 37.5 | 16.8 | 8.4 | 10.3 | 12.30 | 4.170 | 138 | 187 | 261 | |
| ES 6533A | 65.1 | 32.5 | 27.0 | 22.2 | 44.2 | 19.7 | 10.0 | 12.1 | 14.70 | 5.400 | 162 | 230 | 300 | |
| ES 7228A | 72.4 | 27.9 | 19.0 | 17.8 | 52.6 | 19.1 | 9.5 | 16.9 | 13.70 | 3.680 | 130 | 173 | 236 | |
| ES 8038A | 80.0 | 38.1 | 19.8 | 28.1 | 59.3 | 19.8 | 9.9 | 19.8 | 18.50 | 3.890 | 103 | 145 | 190 | |

* EK(Mega Flux® EE Core) and customized designs are also available.

EER CORES



Features


- Large energy storage capacity
- No magnetic flux leakage
- Good temperature stability
- Excellent DC bias characteristics



Applications

- Power inductors for large currents
- Multiple circuit choke coils
- Output chokes for SMPS

■ Product Identification



| Part No. | Dimensions (mm) | | | | | | Path Length (cm) | Cross Section Area (cm^2) | A_L value (nH/N ²) $\pm 12\%$ | | |
|-----------|-----------------|------|------|------|------|------|------------------|--------------------------------------|---|-----------|-----------|
| | A | B | C | D | E | F | | | 026 μ | 040 μ | 060 μ |
| HER 2507A | 25.5 | 9.3 | 7.5 | 7.5 | 19.8 | 6.2 | 5.10 | 0.450 | 39 | 53 | 73 |
| HER 2507B | 25.5 | 11.0 | 7.5 | 7.5 | 19.8 | 7.9 | 5.78 | 0.450 | 34 | 47 | 65 |
| HER 3010A | 30.6 | 15.8 | 9.8 | 9.8 | 22.0 | 11 | 8.66 | 0.754 | 38 | 53 | 72 |
| HER 3511A | 35.0 | 15.8 | 11.3 | 11.3 | 25.6 | 9.8 | 8.30 | 1.078 | 57 | 78 | 108 |
| HER 3511B | 35.0 | 20.7 | 11.3 | 11.3 | 25.6 | 14.7 | 10.27 | 1.078 | 46 | 63 | 87 |
| HER 4013A | 40.0 | 17.4 | 13.3 | 13.3 | 29.0 | 10.4 | 9.13 | 1.491 | 72 | 99 | 135 |
| HER 4013B | 40.0 | 22.4 | 13.3 | 13.3 | 29.0 | 15.4 | 11.13 | 1.491 | 59 | 81 | 111 |
| HER 4215A | 42.0 | 22.4 | 15.5 | 15.5 | 29.4 | 15.4 | 10.64 | 2.026 | 84 | 115 | 158 |
| HER 4215B | 42.0 | 25.4 | 15.5 | 15.5 | 29.4 | 18.4 | 11.84 | 2.026 | 75 | 103 | 142 |
| HER 4917A | 49.0 | 18.8 | 17.2 | 17.2 | 36.5 | 12.2 | 9.57 | 2.353 | 99 | 136 | 185 |
| HER 4917B | 49.0 | 24.7 | 17.2 | 17.2 | 36.5 | 18.1 | 11.93 | 2.353 | 79 | 109 | 149 |

* KER(Mega Flux[®] EER Core), SER(Sendust EER Core)and customized designs are also available.

EQ CORES



Features


- Small dimensions for large currents
- No magnetic flux leakage
- Excellent DC bias characteristics
- Good temperature stability
- Large energy storage capacity

Applications

- Small dimension DC/DC converters
- Large current choke coils
- Smoothing choke coils
- CPU cores for lap-top computers



■ Product Identification



KEQ 41 28 A - 040

Permeability : 40 μ Available perm. 26, 40, 60 μ

Height of EQ core

Width : 28mm Available size : 14mm ~ 32mm

Length : 41.5mm Available size : 20.5mm ~ 50mm

Mega Flux® EQ core HEQ : High Flux, SEQ : Sendust

| Part No. | Dimensions (mm) | | | | | | Path Length (cm) | Cross Section Area (cm ²) | A _L value (nH/N ²) ±12% | | |
|-----------|-----------------|------|------|------|------|------|---------------------|--|--|-----------|-----------|
| | A | B | C | D | E | F | | | 026 μ | 040 μ | 060 μ |
| KEQ 2014A | 20.5 | 14.0 | 8.1 | 8.8 | 18.0 | 5.7 | 4.52 | 0.608 | 44 | 68 | 101 |
| KEQ 2014B | 20.5 | 14.0 | 10.1 | 8.8 | 18.0 | 7.7 | 5.32 | 0.608 | 37 | 57 | 86 |
| KEQ 2619A | 26.5 | 19.0 | 10.1 | 12.0 | 22.6 | 6.8 | 5.47 | 1.198 | 72 | 110 | 165 |
| KEQ 2619B | 26.5 | 19.0 | 12.4 | 12.0 | 22.6 | 9.1 | 6.39 | 1.198 | 61 | 94 | 141 |
| KEQ 3222A | 32.0 | 22.0 | 10.3 | 13.5 | 27.6 | 6.6 | 6.03 | 1.523 | 83 | 127 | 190 |
| KEQ 3222B | 32.0 | 22.0 | 15.2 | 13.5 | 27.6 | 11.5 | 7.99 | 1.523 | 62 | 96 | 144 |
| KEQ 3626A | 36.0 | 26.0 | 17.4 | 14.4 | 32.0 | 13.4 | 9.47 | 1.808 | 62 | 96 | 144 |
| KEQ 4128A | 41.5 | 28.0 | 19.9 | 14.9 | 36.5 | 15.4 | 11.52 | 1.997 | 57 | 87 | 131 |
| KEQ 5032A | 50.0 | 32.0 | 25.0 | 20.0 | 44.0 | 19.5 | 13.34 | 3.141 | 77 | 118 | 178 |


* HEQ(High Flux EQ Core), SEQ(Sendust EQ core) and customized designs are also available.

ER II CORES



Features


- Round Center Leg
- High Flux, Mega Flux Available
- Good Temperature Stability
- No Bulk Gap
- Rectangular Winding is Possible (DCR Reduction)



Applications

- High Current, Low Inductance Applications
- Hybrid, Electrical Vehicles
- PFC Chokes
- Output Chokes

■ Product Identification



RH 32 22 B - 060

| | |
|-------------------------|----------------------------------|
| Permeability : 60 μ | Available perm. 26, 40, 60 μ |
| Height | |
| Width : 22mm | Available size : 11mm ~ 28mm |
| Length : 32mm | Available size : 19mm ~ 42mm |

High Flux ER II Core | RK : MEGA FLUX

| Part No. | Dimensions (mm) | | | | | | Weight [g] | Path Length [cm] | Cross Section Area [cm ²] | AL value (nH/N ²) ±12% | | |
|----------|-----------------|-----------|----------|----------|-----------|----------|---------------|------------------------|--|------------------------------------|-----------|-----------|
| | A (mm) | B (mm) | C (mm) | D (mm) | E (mm) | F (mm) | | | | 026 μ | 040 μ | 060 μ |
| RH1911A | 18.8 ±0.3 | 11.0 ±0.2 | 6.0 ±0.2 | 7.4 ±0.2 | 15.6 ±0.2 | 4.0±0.2 | 5.4 | 3.54 | 0.425 | 39 | 60 | 90 |
| RH2314A | 23.4 ±0.3 | 14.0 ±0.2 | 8.7 ±0.2 | 9.2 ±0.2 | 19.4 ±0.2 | 6.2±0.2 | 11.8 | 4.91 | 0.670 | 45 | 69 | 103 |
| RH2518A | 25.0 ±0.3 | 18.0 ±0.2 | 8.4 ±0.2 | 11.0±0.2 | 21.0 ±0.3 | 5.4±0.2 | 17.1 | 4.97 | 0.960 | 63 | 97 | 146 |
| RH2518B | 25.0 ±0.3 | 18.0 ±0.2 | 10.8±0.2 | 11.0±0.2 | 21.0 ±0.3 | 7.8±0.2 | 20.4 | 5.93 | 0.960 | 53 | 81 | 122 |
| RH3020A | 30.0 ±0.4 | 20.0 ±0.3 | 9.2 ±0.2 | 12.0±0.2 | 25.6 ±0.3 | 5.9±0.2 | 23.7 | 5.81 | 1.140 | 64 | 99 | 148 |
| RH3020B | 30.0 ±0.4 | 20.0 ±0.3 | 11.8±0.2 | 12.0±0.2 | 25.6 ±0.3 | 8.5±0.2 | 27.9 | 6.85 | 1.140 | 54 | 84 | 125 |
| RH3222A | 32.0 ±0.4 | 22.0 ±0.3 | 10.3±0.2 | 13.5±0.2 | 27.0 ±0.3 | 6.6±0.2 | 32.0 | 6.25 | 1.430 | 75 | 115 | 172 |
| RH3222B | 32.0 ±0.4 | 22.0 ±0.3 | 13.4±0.2 | 13.5±0.2 | 27.0 ±0.3 | 9.7±0.2 | 38.2 | 7.49 | 1.430 | 62 | 96 | 144 |
| RH3222C | 32.0 ±0.4 | 22.0 ±0.3 | 15.2±0.2 | 13.5±0.2 | 27.0 ±0.3 | 11.5±0.2 | 42.0 | 8.21 | 1.430 | 57 | 88 | 131 |
| RH3624A | 36.2 ±0.4 | 24.0 ±0.3 | 11.2±0.2 | 15.0±0.2 | 30.4 ±0.4 | 7.2±0.2 | 43.0 | 6.78 | 1.770 | 85 | 131 | 197 |
| RH3624B | 36.2 ±0.4 | 24.0 ±0.3 | 14.4±0.2 | 15.0±0.2 | 30.4 ±0.4 | 10.4±0.2 | 51.1 | 8.06 | 1.770 | 72 | 110 | 166 |
| RH4225A | 42.0 ±0.5 | 25.0 ±0.3 | 12.3±0.2 | 16.2±0.3 | 35.2 ±0.4 | 7.9±0.2 | 56.1 | 7.61 | 2.060 | 88 | 136 | 204 |
| RH4225B | 42.0 ±0.5 | 25.0 ±0.3 | 15.8±0.2 | 16.2±0.3 | 35.2 ±0.4 | 11.4±0.2 | 66.4 | 9.01 | 2.060 | 75 | 115 | 172 |
| RH4628A | 46.5 ±0.6 | 28.0 ±0.5 | 19.4±0.4 | 14.9±0.4 | 39.3 ±0.5 | 14.5±0.3 | 84.7 | 9.81 | 2.080 | 69 | 106 | 159 |

U CORES



Features


- Large energy storage capacity
- No magnetic flux leakage
- Good temperature stability
- Low core loss at high frequencies

Applications

- High inductance choke coils
- Flyback transformers
- Multiple circuit choke coils
- Output chokes for SMPS



■ Product Identification



UK 41 41 C - 060

| | |
|-------------------------|----------------------------------|
| Permeability : 60 μ | Available perm. 26, 40, 60 μ |
| Height of U core | |
| Width : 41mm | Available size : 36mm ~ 65mm |
| Length : 41mm | Available size : 35mm ~ 79mm |
| Mega Flux® U core | UH : High Flux, US : Sendust |

| Part No. | Dimensions (mm) | | | | | | Path Length (cm) | Cross Section Area(cm ²) | A _L value (nH/N ²) ±12% | | |
|----------|-----------------|------|------|------|------|------|------------------|--------------------------------------|--|-----------|-----------|
| | A | B | C | D | E | F | | | 026 μ | 040 μ | 060 μ |
| UK3536A | 35.0 | 36.0 | 20.0 | 25.0 | 13.0 | 11.0 | 16.90 | 2.200 | 43 | 65 | 98 |
| UK3536B | 35.0 | 36.0 | 25.0 | 25.0 | 13.0 | 11.0 | 16.90 | 2.750 | 53 | 82 | 123 |
| UK4141A | 41.0 | 41.0 | 20.0 | 28.0 | 15.0 | 13.0 | 19.30 | 2.600 | 44 | 68 | 102 |
| UK4141B | 41.0 | 41.0 | 25.0 | 28.0 | 15.0 | 13.0 | 19.30 | 3.250 | 55 | 85 | 127 |
| UK4141C | 41.0 | 41.0 | 30.0 | 28.0 | 15.0 | 13.0 | 19.30 | 3.900 | 66 | 102 | 152 |
| UK5251A | 52.0 | 51.0 | 25.0 | 35.0 | 20.0 | 16.0 | 24.30 | 4.000 | 54 | 83 | 124 |
| UK5251B | 52.0 | 51.0 | 30.0 | 35.0 | 20.0 | 16.0 | 24.30 | 4.800 | 65 | 99 | 149 |
| UK6361A | 63.0 | 60.5 | 30.0 | 41.5 | 25.0 | 19.0 | 29.10 | 5.700 | 64 | 98 | 148 |
| UK6361B | 63.0 | 60.5 | 35.0 | 41.5 | 25.0 | 19.0 | 29.10 | 6.650 | 75 | 115 | 172 |
| UK7965A | 79.0 | 64.5 | 30.0 | 42.5 | 35.0 | 22.0 | 32.60 | 6.600 | 66 | 102 | 153 |
| UK7965B | 79.0 | 64.5 | 35.0 | 42.5 | 35.0 | 22.0 | 32.60 | 7.700 | 77 | 119 | 178 |

* UH(High Flux U Core), US(Sendust U Core) and customized designs are also available.

WASHER CORES




Features

- High permeability powder cores
- Low core loss at high frequencies
- High efficiency washer cores
- Minimum magnetic flux leakage
- Excellent DC bias characteristics
- Good temperature stability
- Large energy storage capacity
- Choke coils for mobile phones
- Inductors for handheld devices
- Power inductors for PDA, LCD



Applications

■ Product Identification



DM 46 12 P

Parylene - C coated


Height : 1.2mm Available HT 0.8mm ~ 1.2mm

OD size : 4.6mm Available size : 3.5mm ~ 6.3mm


Washer Core DM : Washer MPP Core

| Part No. | Core Dimensions (mm) Before Finish | | | A_L value (nH/N ²) $\pm 12\%$ | Path Length (cm) | Typical Inductance L@ 0A, 20T (μ H) | Recommended Inductance L (μ H) at 0A |
|----------|------------------------------------|------|-----|---|------------------|--|---|
| | OD | ID | HT | | | | |
| DM 3508P | 3.56 | 1.78 | 0.8 | 14 | 0.817 | 5.6 | 3.3, 4.7, 6.8, 10 |
| DM 3510P | | | 1.0 | 17 | | 6.8 | |
| DM 3908P | 3.94 | 2.24 | 0.8 | 11 | | 4.4 | |
| DM 3910P | | | 1.0 | 14 | 0.942 | 5.6 | 3.3, 4.7, 6.8, |
| DM 3912P | | | 1.2 | 17 | | 6.8 | 10, 15, 22 |
| DM 4610P | 4.65 | 2.36 | 1.0 | 16 | | 6.4 | |
| DM 4612P | | | 1.2 | 20 | 1.060 | 8 | 3.3, 4.7, 6.8, |
| DM 4614P | | | 1.4 | 22 | | 8.8 | 10, 15, 22 |
| DM 6310P | 6.35 | 3.79 | 1.0 | 18 | | | 4.7, 6.8, 10, 15, |
| DM 6312P | | | 1.2 | 22 | 1.361 | 8.8 | 22, 33, 47, 56 |

BIG TOROIDAL CORES



■ Product Identification



| CS | 16 | 25 | 026 | E | | |
|----|----|----|-----|------------------|--|--|
| | | | | Epoxy coated | E : Epoxy, C : Plastic case, U : uncoated | |
| | | | | Perm. : 26 μ | Available perm. 26, 50, 60, 125 μ | |
| | | | | Height : 25mm | Available HT 13.6mm ~ 40.6mm | |
| | | | | OD size : 165mm | Available size : 101.6mm ~ 165.0mm | |
| | | | | Sendust Core | CM : MPP, CH : High Flux, CK : Mega Flux [®] HS : HS | |

CSC's big toroidal cores produced by a 3000 ton press are ideal for high current applications, especially in UPS, renewable energy(solar/wind), high power industrial power systems. The maximum diameter is 165mm(6.5")OD and the electrical characteristics are the same as small toroidal cores. CSC cores are the world's biggest and strongest on the market today.

| Part No. | Before Finish Dimensions (mm) | | | After Finish Dimensions (mm) | | | Weight (g) | Path Length (cm) | Cross Section Area (cm ²) | AL value (nH/N ²) \pm 8% | | |
|----------|-------------------------------|------------|------------|------------------------------|------------|------------|------------|------------------|---------------------------------------|--|-----------|-----------|
| | OD(mm) Max | ID(mm) Min | HT(mm) Max | OD(mm) Max | ID(mm) Min | HT(mm) Max | | | | 026 μ | 060 μ | 125 μ |
| CS1013 | 101.6 | 57.2 | 13.6 | 103.1 | 55.7 | 14.9 | 548.6 | 24.27 | 2.972 | 40 | 92 | 192 |
| CS1016 | 101.6 | 57.2 | 16.5 | 103.1 | 55.7 | 17.8 | 665.6 | 24.27 | 3.522 | 48 | 112 | 228 |
| CS1027 | 101.6 | 57.2 | 27.2 | 103.1 | 55.7 | 28.5 | 1097.3 | 24.27 | 5.944 | 80 | 184 | 384 |
| CS1033 | 101.6 | 57.2 | 33.0 | 103.1 | 55.7 | 34.3 | 1331.3 | 24.27 | 7.044 | 94 | 224 | 456 |
| CS1320 | 132.5 | 78.6 | 20.3 | 134.2 | 77 | 21.7 | 1280.1 | 32.42 | 5.347 | 54 | 124 | 259 |
| CS1325 | 132.5 | 78.6 | 25.4 | 134.2 | 77 | 26.8 | 1601.7 | 32.42 | 6.710 | 68 | 156 | 325 |
| CS1333 | 132.5 | 78.6 | 33.0 | 134.2 | 77 | 34.4 | 2080.9 | 32.42 | 8.717 | 88 | 202 | 422 |
| CS1340 | 132.5 | 78.6 | 40.6 | 134.2 | 77 | 42 | 2560.2 | 32.42 | 10.694 | 108 | 248 | 518 |
| CS1625 | 165.0 | 88.9 | 25.4 | 167.2 | 86.9 | 27.3 | 2808.0 | 38.65 | 9.460 | 80 | 184 | 384 |

* CM(MPP core), CH(High Flux core), CK(Mega Flux[®] core) and customer specifications are also available.

Terminology

AL Value [nH/N²]

The inductance (nanohenries) of a core for 1 turn winding. It is measured at peak AC flux density of 10 gauss and frequency of 10kHz. $1\text{nH}/\text{N}^2 = 1\text{mH}/(1000\text{turns})^2$

Ambient Temperature

Temperature surrounding the devices or circuits. The ambient temperature is measured at 0.5inch(1.27cm) away from the devices or circuits.

Attenuation

The ratio of output parameter (voltage, current, power, etc.) to input parameter. Unit is [dB]. In the case of power, dB is $10\log(\text{output power}/\text{input power})$. In the case of current and voltage, dB is $20\log(\text{output current}/\text{input current})$, $20\log(\text{output voltage}/\text{input voltage})$ respectively.

Coercive Force (Hc) Refer to Hysteresis Curve.

Common-Mode Noise

Electrical interference that is common to both lines in relation to the ground.

Copper Loss [watts]

The power loss (I^2R) or heat generated by current (I) flowing in a winding with resistance (R).

Core loss [watts]

Core loss is composed of eddy current loss, hysteresis loss and residual loss. Refer to Magnetic Design Formulae.

Cross Sectional Area (A)

The effective cross sectional area of a core available for magnetic flux. The cross sectional area listed for toroidal cores is based on bare core dimensions.

Curie Temperature, Tc [°C]

The transition temperature above which a core loses its ferromagnetic properties. Usually defined as the temperature at which falls to 10% of its room temperature value.

DC Resistance [Ω]

Resistance of winding when AC current is not applied.

Differential Mode Noise

Electrical interference that is not common to both lines but is present between both lines. This is also known as normal mode noise.

Disaccommodation

The proportional change of permeability after a disturbance of a magnetic material. It is measured at a constant temperature over a given time interval.

Distributed Capacitance

In an inductor, each winding behaves as a capacitor having the distributed capacitance. Distributed capacitance is parallel with inductance in the circuit and causes self-resonance at a certain

frequency. An inductor which has a smaller distributed capacitance extends a much higher self resonant frequency. So the inductor should be wound to have as small a distributed capacitance as possible.

Eddy Current

When a varying electric or magnetic field passes through the conducting material, current which opposes the change of field is induced in it. This current is called eddy current. Because a conducting material has electric resistance, the eddy current results in heat loss. This is referred to as the eddy current loss.




Figure 1. Eddy Current in Powder Cores

Effective Permeability (μe)

Refer to Permeability.

EMI

The acronym for Electromagnetic Interference is EMI.

Generally, EMI refers to unnecessary electrical energies such as noise.

EMC Electromagnetic Compatibility

Hysteresis Curve (B-H Loop)




Figure 2. B-H Loop

When the magnetic material is taken through a complete cycle of magnetization and demagnetization, the magnetic flux density in that material behaves irreversibly according to the change of the magnetizing force.

The results are as shown in Figure 2. As H is increased in the neutral magnetic material, flux density B increases along the dashed line (initial magnetization curve) to the saturation point, B_s .

Terminology

When H is now decreased, the B - H loop transverses a path to B_r (remanent flux density), where H is zero and the core is still magnetized. The magnetizing force H is now reversed to give a negative value. The magnetizing force required to reduce the flux B_r to zero is called the coercive force (H_c). Along the initial magnetization curve, B increases from the origin nonlinearly with H until the material saturates. In practice, the magnetization of a core in an excited inductor never follows this curve because the core is never in a totally demagnetized state when the magnetizing force is first applied.

Flux Density, Magnetic Induction, B [Gauss ; Tesla]

The corresponding parameter for the induced magnetic field in an area perpendicular to the flux path. Flux density is determined by the field strength and permeability of the medium in which it is measured.
 $1T = 10^4$ Gauss

Incremental Permeability ($\Delta\mu$) Refer to Permeability.

Inductor

A passive device that prevents a variance of the current. Magnetic flux is induced in the inductor when current flows through the inductor, and the voltage induced by magnetic flux prevents the change of current.
 Induced voltage

$$\xi = L \cdot di/dt.$$

Initial Permeability (μ_i) Refer to Permeability.

Leakage Flux

Leakage flux is the small fraction of the total magnetic flux in a transformer or common mode choke that does not contribute to the magnetic coupling of the windings of the device. The presence of leakage flux in a transformer or common mode choke is modeled as a small "leakage" inductance in series with each winding. In a multi-winding choke or transformer, leakage inductance is the inductance measured at one winding with all other windings short circuited.

Litz Wire

A wire made by twisting and bundling some insulated wire. It can decrease the copper loss at high frequency by reducing the skin effect.

Magnetic Hysteresis Refer to Hysteresis Loop.

Magnetizing Force, H [Oe ; A/m]

The magnetic field strength which produces magnetic flux. The mmf per unit length. H can be considered to be a measure of the strength or effort that the magnetomotive force applies to magnetic circuit to establish a magnetic field. H may be expressed as $H=NI/\ell$, where ℓ is the mean length of the magnetic circuit in meters.
 $1 \text{ oersted} = 79.58 \text{ A/m}$

Mean Magnetic Path Length (ℓ)

The effective magnetic path length of a core structure (cm). Refer to Magnetic Design Formulae.

Normal Mode Noise Refer to Differential Mode Noise.

Noise

Unnecessary electrical energy that rises in a circuit.

Operating Temperature Range

The temperature at which a device can be operated normally. Above this temperature, the characteristics of the device can become inferior or the device may operate abnormally. In the case of the inductor, this temperature refers to the temperature rise by the copper loss or core loss. Refer to temperature rise.

Permeability (μ)

In magnetics, permeability is the ability of a material to conduct flux. The magnitude of the permeability at a given induction is a measure of the ease with which a core material can be magnetized to that induction. It is defined as the ratio of the flux density B to the magnetizing force H .




Figure 3. Variation of μ along the Magnetization Curve

$$\text{Permeability : } \mu = B/H \text{ [Gauss/Oersted]}$$

The slope of the initial magnetization curve at any given point gives the permeability at that point. Permeability can be plotted against a typical B-H curve as shown in Figure 3. Permeability is not constant, therefore its value can be stated only at a given value of B or H . There are many different kinds of permeability.

Absolute Permeability (μ_0)

Permeability in a vacuum
Initial Permeability (μ_i)
 Slope of the initial magnetization curve at the origin, that is, the value of permeability at a peak AC flux density of 10 gauss (1 millitesla).

$$\mu = B/H \text{ (Figure 4)}$$




Figure 4. Initial Permeability

Incremental Permeability ($\Delta\mu$)

The slope of the magnetization curve for finite values of peak-to-peak flux density with superimposed DC magnetization (Figure 5). Initial permeability can be thought of as incremental permeability with 0 DC magnetization at small inductions. The incremental permeability is expressed as the slope of the B-H characteristic at around the given operating point.

Terminology

$$\Delta\mu = \frac{\Delta B}{\Delta H}$$




Figure 5. Incremental Permeability

Effective Permeability (μ_e)

If a magnetic circuit is not homogeneous (i.e. contains an air gap), the effective permeability is the permeability of a hypothetical homogeneous (ungapped) structure of the same shape, dimensions, and reluctance that would give the inductance equivalent to the gapped structure.

Relative Permeability (μ_r)

Permeability of a material relative to that of free space.

Maximum permeability (μ_{max})

The slope of a straight line drawn from the origin tangent to the curve at its knee. (Figure 6)




Figure 6. Maximum Permeability

Rated Current

Continuous DC current that can flow in the inductor. It is determined by the maximum temperature rise at the maximum storage temperature range. As rated current is related to power loss of the inductor, DC resistance of the inductor should be lowered or the inductor size should be increased in order to increase the rated current.

Saturation Current

The current at which the inductance decreases below a critical percent inductance (10% or 20% of the initial inductance) by applying DC current to an inductor. In general the critical percent inductance is 10% for ferrite cores and 20% for metal powder cores. The decrease in inductance is caused by the magnetic characteristics of cores. Cores can store a certain amount of flux density, but above that flux density the permeability and inductance of the cores decrease.

Self Resonant Frequency, SRF

The frequency at which the resonance appears between distributed capacitance and inductance of an inductor. At this frequency, inductance and capacitance are canceled out and the inductor is almost a resistor having high impedance. Distributed capacitance that

arises between wires and between wires and cores is parallel with inductance in circuits. Above the self resonant frequency, the capacitive reactance is dominant and the inductor works like the capacitor.

Skin Effect

As the frequency is higher, the current flow is limited to the surface of the wire because the magnetic field in the center of the wire increases. The depth from the wire surface at which the current density at the wire surface decreases by $1/e$ (37%) is called "skin depth", and this is determined by the conductivity of the wire. As the frequency is higher, skin depth decreases, the reactance of wire increases and current flow is interfered. Litz wire may be used in order to decrease the skin effect.

Storage Temperature Range

Temperature range in which the characteristics of a device can be preserved.

Remanence, Br [Gauss ; Tesla] Refer to Hysteresis Curve.

Saturation

The point at which the flux density B in a magnetic material does not increase with further applications of greater magnetization force H. At saturation, the slope of a material's B-H characteristic curve becomes extremely small, with the instantaneous permeability approaching that of free space. (relative permeability = 1.0)

Saturation Flux Density, Bs [Gauss ; Tesla]

The maximum intrinsic induction possible in a material. This is the flux level at which additional H-field produces no additional B-field.

Temperature Rise (ΔT)

The increase in surface temperature of a component in free-standing air due to the total power dissipation (both copper and core loss).

Approximate temperature rise is as follows ;

$$\Delta T(^{\circ}\text{C}) = \left[\frac{\text{Total Power Dissipation (Milliwatts)}}{\text{Surface Area (cm}^2\text{)}} \right]^{0.833}$$

Total Power Dissipation = Copper Losses + Core Losses

RESEARCH & DEVELOPMENT

Chang Sung Corporation has become a global leader through its outstanding R&D center, which is constantly striving to develop new technologies and products.

In particular, CSC magnetic powder cores have raised the company's profile and competitiveness in the world market.



THE CSC PRODUCT LINE IS CONSTANTLY EVOLVING AND IMPROVING THROUGH OUR HIGHLY ADVANCED R&D CENTER EQUIPPED WITH THE MOST MODERN RESEARCH FACILITIES.

▼ EQUIPMENT

- B-H Analyser
- B-H Loop Tracer
- DC Bias Tracer
- Precision LCR Meter
- AC Power Supply
- Electrical Load
- Oscilloscope
- Puncture Tester
- Vibrating Sample Magnetometer (VSM)
- PFC Test Kit
- Impedance Analyser
- Scanning Electron Microscope (SEM)
- Optical Microscope
- Laser Particle Size Analyser
- Specific Surface Area Analyser (BET)
- Oxygen / Nitrogen Analyser
- Atomic Absorption Spectrophotometer
- Heat Treating Furnaces
- Optical Emission Spectrometer
- Electrolysis Analyser
- Thermal Analysis Equipment (DSC, TG, DTA)
- Constant Temperature & Humidity Chamber
- Universal Testing Machine (UTM)
- Hardness Testers, etc.




VSM



SEM




BET



B-H LOOP




Anechoic Chamber



LCR



AC Power Supply



INNOVATIVE TECHNOLOGICAL ADVANCEMENTS

SPECIAL SHAPED MAGNETIC POWDER CORES

